

TECHNICAL DATA SHEET CORROSTOP ULTRA 635-104

CONDITIONER AND RUST REMOVER FOR METAL

Water-based product, liquid

PRODUCT DESCRIPTION

Phosphoric acid based conditionner and rust remover specially formulated to improve the adhesion of paint to any metal and to delay the rust propagation under the paint coats.

TECHNOLOGY

Leaves a thin layer of metallic phosphate behind, which delays the formation of rust.

ADVANTAGES

- Easy to use.
- Improves the adhesion of paint to any metal, particularly new galvanized metal.
- Removes rust, oxidation and other corrosion products.
- Provides a tighter bond of the paint coatings.

PROJECTS

USF

New and maintenance work.

Residential and commercial sites.

Vehicles, machinery, equipment, tools, exterior of tanks, pumps, pipes, furniture, roofs, gutters, signs, structures, fences, doors, guards, staiways, etc.

SURFACES

New or rusted metals, any shape.

Any metal: iron, steel, cast iron, stainless steel, light alloys, aluminum (not anodized), copper, brass, bronze, tin, zinc, galvanized metal, chrome, etc.

ENVIRONMENT

Interior and exterior.

NOTES

Handle carefully: Wear rubber gloves, apron and protective glasses. Avoid contact with skin and eyes.

Do not breathe vapours during use.

Do not mix this product with other cleaner, paints or thinner.

Do not mix this product with other chemical product.

TECHNICAL SPECIFICATIONS (21°C (70°F))

| Appearance | Transparent |
|-------------------------|---|
| Gloss Level | Not applicable • Gloss at 60°: Not applicable |
| | Gloss at 85°: Not applicable |
| Composition | Diluent: Water |
| | Binder: None |
| Volatile Organic | According to ASTM D3960-05: Not available |
| Compounds (VOCs)* | Canadian standard: Not available |
| Spreading Rate per Coat | Varies with application methods and surface porosity. |
| | (Excluding losses caused by variations in application methods or surface porosity). |
| Minimal Film Thickness* | Not applicable |
| | |
| Solids by Volume* | Not applicable |
| Flammability | Non flammable |
| 1 | |

DRYING TIME*



Not applicable

*Technical data source: 635-104



PPG Architectural Coatings Canada, Inc. warrants performance of its products to its intended use if properly applied in accordance with the label directions and the specifications of the technical data sheet. Having no control over the application methods and conditions or the circumstances related to its use, no other warranty, expressed or implied, statutory or otherwise is given. This limited warranty extends only to the original purchaser of the product and is not transferable or assignable. If the product fails to conform to this limited warranty, we will, at your option, furnish replacement product or refund the purchase price. This limited warranty excludes (1) labour or costs of labour for the application or removal of any product and (2) all other direct, incidental, special or consequential damages.



SURFACE PREPARATION

Before treating a surface, it must be clean, solid and free from dust, dirt, oil, soot, wax, mildew, chalking, loose paint or all other contaminants. Follow the preparation steps, as described below:

- ► Clean surface with Polyprep cleaner 771-135, 771-136, or the appropriate cleaner for removing the contaminant. Rinse thoroughly with clear water.
- New metal: Remove grease and oil with mineral spirits.
- Rusted metal: Remove all loose rust and other foreign matter with a wire brush, a scraper, an abrasive cloth or other suitable means.

APPLICATION

This is a ready-to-use product, do not thin. Pour the quantity of product needed into a acid resisting container (plastic or stainless steel).

Note: Slightly rusty iron can be treated with a solution of 2 parts cleaner and 1 part water. Always add the product to the water. Never add the water to the product.

Wear gloves, apron and protective glasses.

Apply by stiff brush, brush or with a clean cloth. Let the product work. Avoid breathing vapours.

Rinse well with clear water and wipe dry. Outdoor, rinse the surface with clean water under pressure.

Repeat these steps if needed.

Paint immediately after cleaning to prevent oxidation.

For more information on application methods, visit the website at www.corrostop.ca or call our customer service: 1-800-463-7426.

APPLICATION CONDITIONS

Temperature: 5 to 30°C (40 to 90°F) (ideal 20°C ± 5°C [68°F ± 9°F]).
Relative humidity: Ideal between 15 and 50%, maximum 85%.

TOOLS

- · Paintbrush: Natural or synthetic bristles.
- · Others: Stiff bristle brush, clean cloth, sponge or soak.

CLEANING TOOLS

Rinse tools with water.

SURFACE MAINTENANCE

· Apply a protective coating on dry surfaces.

STORAGE AND TRANSPORTATION

Keep product in a dry and ventilated area between 10 and 30°C (50 and 86°F).

DISPOSAL

Consult your municipality about proper disposal procedure of leftover product in accordance with the laws and environmental respect or give it to a neighbour or a friend, a recreation centre or a non-profit organisation. Do not empty into drains.

SAFETY MEASURES

Read the Material Safety Data Sheet. Avoid contact with eyes. Content may be harmful. Do not swallow. Keep out of reach of children. Wear a protective mask, rubber gloves and safety goggles. Only use in a well-ventilated area.

FIRST AID TREATMENT: If in contact with eyes, rinse thoroughly with clear water. If swallowed, do not induce vomiting. Call Poison Control Centre or physician immediately.

This technical data sheet, No. 635-104, replaces all earlier versions.

SICO, CORROSTOP, POLYPREP and GOPRIME are trademarks of the PPG group of companies.

Edition of 2014-06-18

Page 2 of 2