

2.1/2.8 VOC Tintable Polyurethane Primer

HSP-2128

HSP-2128 is a high performance polyurethane primer providing superior film build, strong corrosion resistance, and fast dry properties. It has excellent adhesion over a wide variety of substrates, is heavy metal free, and may be custom tinted.

HSP-2128 is particularly suited for application over sandblasted metals—example applications include castings, hot rolled steel, and fabrications.

Features and Benefits:

- Excellent adhesion properties
- Fast dry for improved productivity
- Strong corrosion resistance
- Choice of low VOC options (2.1 and 2.8 lbs/gal)

Associated Products:

- HSP-2128 Low VOC Tintable Polyurethane Primer
- HSP-211 Catalyst for HSP-2128 Primers
- UA-11 Urethane Accelerator

Physical Constants: *All values are theoretical, depend on color and are Ready-to-Spray. Actual values could vary slightly due to manufacturing variability.*

	HSP-2128 w/tint	HSP-2128 w/tint : HSP-211 : UA-11
Percent solids (by weight)	79.9 – 80.6%	80.0 – 80.5%
Percent solids (by volume)	62.2 – 62.8%	65.3 – 65.8%
HAPs	≤ 0.01 lbs/gal	≤ 0.01 lbs/gal
Photo-chemically reactive	No	No
Flash Point		
HSP-2128 = 1°F (-17°C)		
HSP-211 = 334°F (168°C)		
UA-11 = 96°F (36°C)		
RTS Combinations:	HSP-2128 w/tint	HSP-2128 w/tint : HSP-211 : UA-11
Volume Ratio	As is	102 : 20 : 6
Applicable Use Category	Primer Sealer	Primer Sealer
VOC Actual (g/L)	222 -228	222 – 226
VOC Actual (lbs/gal)	1.85 - 1.90	1.85 - 1.89
VOC Regulatory (less water less exempt) (g/L)	248 – 254	242 – 247
VOC Regulatory (less water less exempt) (lbs/gal)	2.07 - 2.12	2.02 - 2.06
Density (g/L)	1,546 – 1,570	1,457 – 1,477
Density (lbs/gal)	12.89 - 13.09	12.15 - 12.31
Volatiles wt. %	19.4 - 20.1	19.5 – 20.0
Water wt. %	0.0	0.0
Exempt wt. %	5.2 - 5.3	4.4 - 4.5
Water vol. %	0.0	0.0
Exempt vol. %	10.4	8.3

HSP-2128

Directions for Use

Substrate Preparation: The surface to be coated must be free of all contamination (including dust, dirt, oil, grease, and oxidation). A chemical treatment (or conversion coating) will improve adhesion and performance properties of the finished coat. Variability can occur with substrates, preparation, application method or environment. We recommend that adhesion and system compatibility be checked prior to full application.

Metal	Direct to Substrate
Cold Rolled Steel	Excellent
Hot Rolled Steel	Excellent
Galvaneal	Excellent
Galvanized	Excellent* (see note)
Aluminum	Excellent
Plastic / Fiberglass	Surface should be free of all contamination. Because of the variability of plastic/fiberglass substrates, coating performance should be confirmed on the actual plastic/fiberglass substrate being used.

Note: For acceptable compatibility between this primer and CPC topcoats please see the CPC Primer/Topcoat compatibility chart (CPCTB01).

* Galvanized surfaces will need chemical treatment or a conversion coat such as PLC-900 for exterior and/or harsh environments.

Mix Directions:



Stir thoroughly prior to and occasionally during use.

For a one-gallon RTS kit: to each gallon (102 oz. net) of tinted HSP-2128, add the entire contents of a one quart (20 oz. net) container of HSP-211 catalyst, and 6 oz. of UA-11 accelerator.

For one-quart RTS: mix 25.5 oz. tinted HSP-2128 with 5 oz. HSP-211 and 1.5 oz. UA-11.

Note: Moisture contamination in components can result in poor properties of applied films or gelation of the material. Do not open until ready to use.

DO NOT USE LACQUER THINNERS FOR CLEANING LINES.

Thinning: For improved application properties and pot life, thinning is recommended between 10% - 25% by volume with Acetone (Q30).



Blend Ratio	For a one-gallon RTS kit			For one-quart RTS		
	HSP-2128	HSP-211	UA-11	HSP-2128	HSP-211	UA-11
	102 oz	20 oz	6 oz	25.5 oz	5 oz	1.5 oz



Pot Life @ 77°F (25°C): 1.5-2 hours at 77°F thinned 10% by volume with Acetone (Q30). Additional Acetone may be added for longer pot life. Do not exceed 25% Acetone reduction by volume in non-VOC regulated areas. Mix only enough material that can be used in two hours or less.

Note: Higher temperatures will shorten pot life.

Spray Viscosity Range: #3 Zahn: 10 – 20 seconds

Shelf Life: Unopened = 4 years Opened = 2 years

Application Equipment:



Conventional (with or without pressure pot): 1.3 mm needle/nozzle, 50 – 60 psi at the gun

HVLP (with or without pressure pot): 1.3 mm needle/nozzle, 10 psi at cap or per manufacturer's recommendation

Airless: No recommendation

Air-Assisted Airless: 0.009 - 0.013 tip, 800 – 1,200 psi fluid pressure, 40 psi atomization

Brush or Roll: Not recommended

Electrostatic: Not recommended

Application:



Apply: 1 – 2 medium coats with 15 minute flash between coats.

Wet Film Build: 3.0 – 3.8 mils

Recommended Dry Film Build: 2.0 – 2.5 mils

Square Foot Coverage @ 1mil no loss: 1,047 – 1,055 sq. ft.

Dry Times:



Air Dry @ 77°F 50% RH:

To Touch* 45 minutes

To Handle* 2 hours

Air Dry 8 hours

To Topcoat** After 1 hour to 4 days

Force Dry @ 160°F: N/A

* Paint film is not fully cured for 7 days. Drying time listed may vary, depending upon film build, color selection, temperature, humidity and degree of air movement.

** After 4 days, the coating must be mechanically abraded and cleaned prior to topcoating or recoating.

HSP-2128

Technical Data*

Performance Properties:

*System:
Bonderite 1000
HSP-2128 (tinted gray)
No topcoat*

Test	ASTM Method	Result
Pencil Hardness	D3363	F
Gravelometer	D3170	9
Mandrel	D522	Pass
Impact (direct/indirect)	D2794	70/30 in-lbs
In Service Temperature Limit		300°F

Chemical Resistance:

*System:
Bonderite 1000
HSP-2128 (tinted gray)
No topcoat*

Chemical	ASTM Method	Result
Toluene	D1308	Pass
10% NaOH (Sodium Hydroxide)	D1308	Pass
10% HCl (Hydrochloric acid)	D1308	Mild Blisters
10% H ₂ SO ₄ (Sulphuric acid)	D1308	Mild Blisters
Gasoline	D1308	Slight Ring
Isopropanol	D1308	Slight Ring
Distilled Water**	D1308	Pass

** Although resistant to intermittent exposure, this product is not recommended for immersion.

Weather Resistance:

*Sandblasted HRS
HSP-2128 (tinted gray)
AUE-300*

	ASTM Method	Result
Salt Spray – 1000 hours	B117	
Corrosion Creep	D1654	7A – 9A
Scribe Blisters	D714	4M, 6M
Face Blisters	D714	None
Humidity – 100 hours	D2247	
Initial Adhesion	D3359	5B
5 Minute Recovery Adhesion	D3359	5B
1 Hour Recovery Adhesion	D3359	5B
24 Hour Recovery Adhesion	D3359	5B

All tests results assume proper cure and preparation of test substrates. Unless otherwise stated, all results were obtained spraying product direct to metal on Bonderite 1000.

*The application and performance property data above are believed to be reliable based on laboratory findings. It is for the buyer to satisfy itself on the suitability of the product for its particular use. Variation in environment, procedures of use, or extrapolation of data may cause unsatisfactory results.

Miscellaneous

Safety:



These materials are designed for application only by professional, trained personnel, using proper equipment under controlled conditions and are not intended for sale to the general public.

Safe application of paints and coatings requires knowledge of equipment, materials and individual training. Directions and precautionary information on both equipment and products should be carefully read and strictly observed for personal safety and property protection. Consideration must be given to eliminate conditions, which may generate hazardous atmospheres during spray application or subject operators or bystanders to injury or illness.

Special precautions must be taken when utilizing spray equipment, particularly airless equipment. High-pressure injection of coatings into the skin by airless equipment may cause serious injury requiring immediate medical attention at a hospital. Treatment advice may also be obtained from Poison Centers.

Air quality should be maintained with adequate ventilation; applicators can achieve additional protection by wearing respirators and other protective garments such as gloves and overalls. In all cases, wear protective eye equipment. During the application of all coatings materials, all flames, welding and smoking must be prohibited. Explosion proof equipment must be used when coating these materials in confined areas.

PRECAUTIONARY INFORMATION

Before using the products listed herein, carefully read each product label and follow directions for its use. Please read and observe all warnings and precautionary information on all product labels. Prevent all contact with skin and eyes and breathing of vapors and spray mist. Repeated inhalation of high vapor concentrations may cause a series of progressive effects including irritation of the respiratory system, permanent brain and nervous system damage and possible unconsciousness and death in poorly ventilated areas. Eye watering, headaches, nausea, dizziness and loss of coordination are indications that solvent levels are too high. Intentional misuse by deliberately concentrating and inhaling the contents can be harmful or fatal.

KEEP OUT OF THE REACH OF CHILDREN

MEDICAL RESPONSE

Emergency Medical or Spill Control Information (412) 434-4515; CANADA (514) 645-1320
Have label information available.



Material Safety Data Sheets for the PPG products mentioned in this publication are available through your PPG Distributor.

For additional information regarding this product, see the MSDS AND LABEL information.

PPG Industries Commercial Coatings

We're Everywhere You Look

PPG Industries
19699 Progress Drive
Strongsville, OH 44149
1-800-647-6050

PPG Canada Inc.
2301 Royal Windsor Drive, Unit #6
Mississauga, Ontario L5J 1K5
1-888-310-4762