

## JC620 Acrylic Urethane Clearcoat

### Background

SHOP-LINE® JC620 is a two component 4.1 VOC multi purpose acrylic urethane clearcoat that is fast-drying, easy to apply and designed for use in either cross flow air dry or downdraft force cure spray booths. JC620 delivers good gloss, DOI and buffability and out performs similar value priced clearcoats.

### Components

#### Clearcoat

JC620 Acrylic Urethane Clearcoat

#### Hardener

JH6265 Fast Urethane Hardener 55-65°F (13-18°C)

JH6285 Slow Urethane Hardener 75-85°F (24-29°C)

JH6295 Extra Slow Urethane Hardener 85-95°F (29-35°C)

### Compatible Products

#### Can be applied over:

JBP *Shop-Line* Plus Acrylic Urethane Basecoat

JB Acrylic Basecoat

JAU Acrylic Urethane Direct Gloss

JE Acrylic Enamel / Activated

### Preparation

Allow basecoat color to dry a minimum of 30 minutes and a maximum of 24 hours before clearing. After 24 hours the basecoat should be lightly sanded and reapplied before applying JC620.

### Mixing



Ratios:

<b>JC620</b>	:	<b>JH6265 / JH6285 / JH6295</b>
4	:	1



Pot Life:

1.5 - 2 hours at 70°F (21°C)



Additives:

JX993	Flexible Additive, 10% to RTS quart
JX994	Fisheye Eliminator, .5 oz. per RTS quart
SU4985	Universal Matting Agent, see ONECHOICE® product bulletin OC-2

### Air Pressure and Gun Setup



HVLP:

8 - 10 psi at the air cap

Compliant:

29 - 40 psi at the gun

Gun Setup:

1.3 - 1.6 mm or equivalent

Note: For best overall results, refer to spraygun manufacturer's recommendations for inlet air pressures.

---

## Application

---



**Coats:** 2 - 3 full wet coats

For optimum performance, final recommended film build is 2.0 - 2.5 mils

---

## Dry Times

---



**Between Coats:** 5 - 10 minutes at 70°F (21°C)



<b>Air Dry:</b>	<b>With JH6265</b>	<b>With JH6285/JH6295</b>	
	Dust:	5 - 10 minutes	10 - 15 minutes
	Tack:	30 - 50 minutes	50 - 60 minutes
	Tape:	2 - 4 hours	2 - 4 hours



**Force Dry:** 30 minutes at 140°F (60°C) 30 minutes at 140°F (60°C)



**IR:** 12 - 15 minutes 12 - 15 minutes



<b>Polish:</b>	<b>Air Dry</b>	
	2 - 4 hours at 70°F (21°C)	6 - 8 hours at 70°F (21°C)
	<b>Force Dry</b>	
	After cool down	After cool down



**Recoat:** **Air Dry:**  
8 hours or overnight at 70°F (21°C)  
**Force Dry:**  
After force cure and cool down  
Must lightly scuff before recoating

---

## Clean Up

---

Clean spray guns, gun cups, storage pots, etc., thoroughly with JT501 General Purpose Solvent or another appropriate clean up solvent after each use. Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

---

## Properties

---

### VOC

Package	3.57 lbs./ gal (428 g/L)
---------	--------------------------

Applied Less exempts (4:1)	4.14 lbs./ gal (496 g/L)
----------------------------	--------------------------

Volume Solids (4:1)	35.4%
---------------------	-------

Weight Solids (4:1)	42.0%
---------------------	-------

### Film Build Per Coat

Applied (4:1)	1.0 - 1.5 mils
---------------	----------------

### Sq. Ft. coverage at 1 mil

Applied (4:1)	568 sq. ft. at 100% transfer
---------------	------------------------------

---



---

**Limitations**

*Shop-Line* products should not be combined with components of other product lines.

---

**Precautionary Information:**

The contents of this package may have to be blended with other components before the product can be use. Before opening the packages be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all of its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

---

**Medical Response:**

**EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514)-645-1320**

---

**See Material Safety Data Sheet and Labels for additional safety information and handling instructions.**

Material Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG *Shop-Line* brand distributor. To the best of our knowledge, the technical information in this bulletin is accurate; however, since PPG Industries is constantly improving its coating and paint formulas, the current technical data may vary somewhat from what was available when this bulletin was printed. Contact your *Shop-Line* brand distributor or visit [www.ppgrefinish.com](http://www.ppgrefinish.com) for the most up-to-date information.

---

The PPG Logo, *Shop-Line* and *OneChoice* are trademarks of PPG Industries Ohio, Inc.