

# $\mathsf{OLYMPIC}^{\circledR}\,\mathsf{HOME}^{^{\intercal}}\,\,(\mathsf{US})$ $\mathsf{OLYMPIC}^{\circledR}\,\,\mathsf{CLASSIC}\,\,\mathsf{HOME}^{^{\intercal}}\,\,\,(\mathsf{CANADA})$

73951 Series 74422C Series

Architectural Coatings Interior Latex Semi-Gloss

## **GENERAL DESCRIPTION**

OLYMPIC HOME and CLASSIC HOME interior paint delivers a durable and washable finish, backed by a 15-year warranty. Recommended for use on properly prepared and primed or previously painted drywall, plaster, masonry, wood, and metal surfaces. Ideal for use on interior walls, trim, and ceilings.

# **RECOMMENDED SUBSTRATES**

Gypsum Wallboard-Drywall Plaster Masonry Wood Metal

#### APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

**Application Equipment:** Apply with a high quality brush, roller, paint pad, or by airless spray equipment. Where necessary, apply a second coat.

Airless Spray: Pressure 1500 - 2000 psi, tip 0.015" - 0.021"

Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush

Roller: 3/8" - 3/4" nap roller cover

**Thinning:** Thinning is not usually required. If necessary, thin with up to 1/4 pint (118mL) of water per U.S. gallon (3.78 L) of paint.

#### Permissible temperatures during application:

Material: 50 to 90°F 10 to 32°C Ambient: 50 to 90°F 10 to 32°C Substrate: 50 to 90°F 10 to 32°C

# TINTING AND BASE INFORMATION

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

73951 Base 1 / Ultra White 74422C Base 2 / White 73953 Base 3\* 74423C Base 3\* 73955 Base 5\* 74425C Base 5\*

Some colors, or drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

## PRODUCT DATA

**PRODUCT TYPE:** Vinyl Acrylic Latex

SHEEN: Semi-Gloss: 30 to 50 (60° Gloss Meter)

**VOLUME SOLIDS\*:** 25% +/- 2% **WEIGHT SOLIDS\*:** 33% +/- 2%

**VOC\*:** <50 g/L (0.4 lbs./gal.)

**WEIGHT/GALLON\*:** 9.4 lbs. (4.3 kg) +/- 0.2 lbs. (91 g)

\*Product data calculated on product 73951, 74422C.

COVERAGE: Approximately 400 sq. ft./gal. (37 sq. m/3.78L) per U.S.

Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness: 4.0 mils
Wet Microns: 102
Dry Film Thickness: 1.0 mils
Dry Microns: 25

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.

To Touch: 1 hour To Recoat: 4 hours To Full Cure: 30 days

Drying times listed may vary depending on temperature, humidity, film

build, color, and air movement.

**CLEANUP:** Clean tools with warm soapy water.

**WASHING INSTRUCTIONS:** Wait at least 14 days after painting before cleaning the surface with a non-abrasive mild cleaner.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

## FEATURES / BENEFITS

## **Features**

Durable, washable quality Acrylic latex formula Good hiding power

Smooth finish

Great for walls & ceilings

#### **Benefits**

Wipe clean with a soft, damp cloth Easy application and clean-up

Covers light colors in two coats. A primer is recommended for drastic color changes

Uniform even appearance

Versatile coating for home interiors

<sup>\*</sup>Must be tinted before use.

*OLYMPIC* 73951, 74422C Series

Architectural Coatings Interior Latex Semi-Gloss

#### **GENERAL SURFACE PREPARATION**

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding. Prime all bare walls, wood, drywall, plaster, masonry, metal, and porous substrates with an appropriate primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**CONCRETE/MASONRY BLOCK:** Mortar should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. If the material appears to be adhering tightly, a masonry sealer may be applied to seal the surface. Check adhesion by applying a piece of masking tape. If the sealer peels off and has loose particles, remove all chalking or crumbling material, re-seal and re-check adhesion.

**FERROUS METAL**: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed with an appropriate primer.

**GYPSUM WALLBOARD-DRYWALL:** Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, then prime with an appropriate primer prior to painting the substrate.

**MASONRY:** New masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming with an alkali resistant primer.

**PLASTER:** Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

**WOOD:** Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed with an appropriate primer before painting. Countersink all nails, putty flush with surface, then prime.

# LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C).

Not recommended for use on floors.

PROTECT FROM FREEZING.

## **PACKAGING**

1-Gallon (3.78 L) 5-Gallon (18.9 L)

Not all products available in all sizes.

# SAFETY PRECAUTIONS

Before using the products listed in this publication, carefully read each product label and follow directions for its use. Please read and observe all the warnings and precautionary information on the product labels. Material Safety Data Sheets are available through our Sales Representative, Retailer or by calling (412) 492-5555.

Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. High pressure injection of coatings into the skin by airless equipment may cause serious injury.

USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

The PPG logo is a registered trademark of PPG Industries, Ohio, Inc. OLYMPIC and OLYMPIC design are registered trademarks and HOME and CLASSIC HOME are trademarks of PPG Architectural Finishes, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.

