



PREMIUM

76002 Series

OLYMPIC® Premium Interior/Exterior High Gloss Latex

GENERAL DESCRIPTION

OLYMPIC® Premium Interior/Exterior High Gloss 100% Acrylic Latex is ideal for use on properly prepared interior and exterior trim, cabinets, doors, and shutters.

RECOMMENDED SUBSTRATES

Concrete/Masonry Block
Concrete/Masonry
Ferrous Metal
Gypsum Wallboard-Drywall
Plaster
Wood

CONFORMANCE STANDARDS

AIM	Architectural Industrial Maintenance
CARB	California Air Resources Board
LADCO	Lake Michigan Air Directors Consortium
OTC	Ozone Transport Commission
SCQAMD	South Coast Air Quality Management District

DIRECTIONS FOR USE

Stir thoroughly before and occasionally during use. When using more than one can of the same color, intermix to ensure color uniformity.

Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 90°F	10 to 32°C
Substrate:	50 to 90°F	10 to 32°C

APPLICATION INFORMATION

Application Method: Apply with a high quality brush, roller, or paint pad. Where necessary, apply a second coat. Allow each coat to dry before applying the next coat.

Application Equipment: For smooth surfaces, use a polyester nylon brush or 3/16" - 3/8" nap roller cover. For textured surfaces, use a nylon brush or roller designed for this purpose.

Thinning: No thinning is usually required. If necessary, thin with up to 1/4 pint (118 mL) of water per U.S. gallon (3.78L) of paint.

PRODUCT INFORMATION

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

76002	White (Also Base 2)
76003	Base 3*
76005	Base 5*

*Must be tinted before use.

Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

PRODUCT DATA

PRODUCT TYPE:	100% Acrylic Latex
SHEEN:	High Gloss: 70+ (60° Gloss Meter)
VOLUME SOLIDS*:	39% +/- 2%
WEIGHT SOLIDS*:	52% +/- 2%
VOC*:	140 g/L (1.2 lbs./gal.)
WEIGHT/GALLON*:	10.6 lbs. (4.8 kg) +/- 0.2 lbs. (91 g)

*Product data calculated on 76002.

COVERAGE: One gallon (3.78 Liters) covers about 400 sq. ft. (37.2 sq. meters) on primed, smooth non-porous surfaces.

Wet Film Thickness: 4.0 mils

Wet Microns: 102

Dry Film Thickness: 1.6 mils

Dry Microns: 41

Coverage does not include variation due to application methods, surface porosity, and/or mixing.

DRYING TIME: Dry time @77°F (25°C); 50% relative humidity.

To Touch: 1 hour

To Recoat: 4 hours

To Full Cure: 30 days

Drying times listed may vary depending on temperature, humidity, film build, color and air movement.

WASHING INSTRUCTIONS: For interior surfaces, wait at least 14 days after painting before cleaning the surface with a non-abrasive mild cleaner.

CLEAN UP: Wipe up spills immediately with a damp cloth or sponge. Wash brushes, rollers and other painting tools with soap and water immediately after use.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

FEATURES AND BENEFITS

Features

100% acrylic
Excellent adhesion
Excellent durability
Superior scrubability
Resist staining
Soap and water Cleanup

Benefits

Excellent adhesion and moisture resistance
Sticks to difficult substrates
Long lasting
Withstands repeated cleaning
Resistance to spillage or soiling from common household stains
Easy to clean-up hands and tools

OLYMPIC® Premium Interior/Exterior High Gloss Latex

GENERAL SURFACE PREPARATION

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding. Prime all bare and porous substrates with an appropriate high quality latex primer. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada, contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

CONCRETE/MASONRY BLOCK: Mortar should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. If the material appears to be adhering tightly, a masonry sealer may be applied to seal the surface. Check adhesion by applying a piece of masking tape. If the sealer peels off and has loose particles, remove all chalking or crumbling material, re-seal and re-check adhesion.

CONCRETE and MASONRY: New concrete should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming with an alkali resistant primer.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed with a high quality latex primer.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, then prime with a high quality latex primer prior to painting the substrate.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with a high quality latex alkali resistant primer.

WOOD: Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime with a high quality latex primer.

LIMITATIONS OF USE

Apply when air, product, and surface temperatures are between 50°F (10°C) and 90°F (32°C). Avoid exterior painting late in the day when dew or condensation are likely to form or if rain is expected. Not recommended for floors or for use on the bodies of homes. **PROTECT FROM FREEZING.**

PACKAGING

1-Gallon (3.78 L)

SAFETY PRECAUTIONS

Before using the products listed in this publication, carefully read each product label and follow directions for its use. Please read and observe all the warnings and precautionary information on the product labels. Material Safety Data Sheets are available through our Sales Representative, Retailer or by calling (412) 492-5555.

USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-426-6306.



Olympic® - US
PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.olympic.com

Technical Services
1-800-426-6306

Architect/Specifier:
1-888-PPG-IDEA

Olympic - Canada
PPG Canada, Inc.
Architectural Coatings
4 Kenview Blvd
Brampton, ON L6T 5E4

T.D. 3523 4/2009
(Supersedes 11/2008)