



OLYMPIC®

76413, 76415

Architectural Coatings

OLYMPIC® Interior Latex Eggshell

**GENERAL DESCRIPTION**

OLYMPIC® Interior Latex Eggshell is recommended for use on properly prepared interior walls, ceilings, and interior trim.

**RECOMMENDED SUBSTRATES**

Concrete	Gypsum Wallboard-Drywall
Concrete/Masonry Block	Plaster
Ferrous Metal	Wood

**FEATURES / BENEFITS**

Excellent hiding for a uniform finish  
Easy application to resists runs and drips  
Low VOC and lower odor  
Soap and water cleanup

**APPLICATION INFORMATION**

Stir thoroughly. When using more than one can of the same color, mix together (box) before applying.

**Application Equipment:** Apply with a high quality brush, roller, paint pad, or by airless spray equipment. Where necessary, apply a second coat.

**Airless Spray:** Pressure 2000 psi, tip 0.015" - 0.021"

**Brush:** Polyester/Nylon Brush

**Roller:** 3/16" - 3/8" nap roller cover

**Thinning:** Thinning is not usually required. If necessary, thin with up to 1/4 pint (118mL) of water per U.S. gallon (3.78 L) of paint.

**Permissible temperatures during application:**

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 90°F	10 to 32°C
Substrate:	50 to 90°F	10 to 32°C

**TINTING AND BASE INFORMATION**

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

76413	Base 3*
76415	Base 5*

\*Must be tinted before use.

Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

**PRODUCT DATA**

<b>PRODUCT TYPE:</b>	Vinyl Acrylic Latex
<b>SHEEN:</b>	Eggshell: 4 to 8 (60° Gloss Meter)
<b>VOLUME SOLIDS*:</b>	26% +/- 2%
<b>WEIGHT SOLIDS*:</b>	38% +/- 2%
<b>VOC*:</b>	<50 g/L (0.4 lbs./gal.)
Colorants added to this product may contain VOCs.	

**WEIGHT/GALLON\*:** 9.9 lbs. (4.5 kg) +/- 0.2 lbs. (91 g)

\*Product data calculated on product 76413.

**COVERAGE:** Approximately 400 sq. ft./gal. (37 sq. m) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0 mils
Wet Microns:	102
Dry Film Thickness:	1.0 mils
Dry Microns:	25.4

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

**DRYING TIME:** Dry time @ 77°F (25°C); 50% relative humidity.

To Touch:	1 hour
To Recoat:	4 hours

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

**CLEANUP:** Clean tools with warm soapy water

**WASHING INSTRUCTIONS:** Wait at least 14 days after painting before cleaning the surface with a non-abrasive mild cleaner.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

**FLASH POINT:** Over 200°F (93°C)

**CONFORMANCE STANDARDS**

VOC compliant in all regulated areas  
Can earn LEED 2009 credits

## GENERAL SURFACE PREPARATION

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, mildew, rust, product fines, and dust. Remove loose paint, chalk and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding. Prime all bare and porous substrates with the appropriate OLYMPIC® primer. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**CONCRETE:** New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming with an alkali resistant primer.

**CONCRETE/MASONRY BLOCK:** Mortar should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. If the material appears to be adhering tightly, a masonry sealer may be applied to seal the surface. Check adhesion by applying a piece of masking tape. If the sealer peels off and has loose particles, remove all chalking or crumbling material, re-seal and re-check adhesion.

**FERROUS METAL:** The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

**GYPSUM WALLBOARD-DRYWALL:** Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, then prime prior to painting the substrate.

**PLASTER:** Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

**WOOD:** Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime.

## LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50° F (10°C) and 90°F (32°C).

Not recommended for use on floors or in high humidity areas.

PROTECT FROM FREEZING.

## SAFETY PRECAUTIONS

Before using the products listed in this publication, carefully read each product label and follow directions for its use. Please read and observe all the warnings and precautionary information on the product labels. Material Safety Data Sheets are available through our Sales Representative, Retailer or by calling (412) 492-5555.

Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

## PACKAGING

5-Gallon (18.9 L)

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



Olympic - US  
PPG Industries, Inc.  
Architectural Coatings  
One PPG Place  
Pittsburgh, PA 15272  
[www.olympic.com](http://www.olympic.com)

Technical Services  
1-800-426-6306

Architect/Specifier  
1-888-PPG-IDEA

Olympic - Canada  
PPG Canada, Inc.  
Architectural Coatings  
4 Kenview Blvd  
Brampton, ON L6T 5E4

T.D. 3222 12/2011