OLYMPIC® FastHide® ULTRA Interior/Exterior Alkyd Gloss

GENERAL DESCRIPTION

OLYMPIC® FastHide® ULTRA Interior/Exterior Alkyd Gloss is recommended for use on properly prepared interior or exterior trim work, lawn and porch furniture, garden equipment, floors and general household use.

RECOMMENDED SUBSTRATES

Cement Composition Board
Concrete/Masonry Block
Concrete/Masonry
Ferrous Metal
Plaster
Wood

CONFORMANCE STANDARDS

AIM Architectural Industrial Maintenance

DIRECTIONS FOR USE

Stir thoroughly before and occasionally during use. When using more than one can of the same color, intermix to ensure color uniformity.

Permissible temperatures during application:

Material:	50 to 90ºF	10 to 32ºC
Ambient:	50 to 90ºF	10 to 32ºC
Substrate:	50 to 90ºF	10 to 32ºC

APPLICATION INFORMATION

Application Method: Apply with a high quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat. Allow each coat to dry before applying the next coat.

Application Equipment: For smooth surfaces, use a high quality brush or 3/16" - 3/8" nap roller cover. For textured surfaces, use a natural bristle brush or roller designed for this purpose. If applied by spray, back-brushing or back-rolling is recommended. For airless spray application, use tip size 0.015" - 0.021" and pressure range of 1500 - 2000 psi.

Thinning: DO NOT THIN.

PRODUCT INFORMATION

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

78640	White (Also Base 2)
78641	Base 3*
78642	Base 5*

Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

PRODUCT DATA

PRODUCT TYPE:	Alkyd
SHEEN:	Gloss: 85 to 100 (60º Gloss Meter)
VOLUME SOLIDS*:	52% +/- 2%
WEIGHT SOLIDS*:	66% +/- 2%
VOC*:	367 g/L (3.1 lbs./gal.)
WEIGHT/GALLON*:	8.9 lbs. (4.0 kg) +/- 0.2 lbs. (91 g)

*Product data calculated on 78640.

COVERAGE: One gallon (3.78 Liters) covers about 400 sq. ft. (37.2 sq. meters) on primed, smooth non-porous surfaces.

Wet Film Thickness:	4.0 mils
Wet Microns:	102
Dry Film Thickness:	2 mils
Dry Microns:	51

Coverage does not include variation due to application methods, surface porosity, and/or mixing.

DRYING TIME: Dry time @77ºF (25ºC); 50% relative humidity.

To Touch:	5 to 10 hours
To Recoat:	24 hours
To Full Cure:	30 days

On floors, allow 48 hours drying time before placing in service.
Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

CLEAN UP: Paint thinner. Danger: Rags, steel wool or waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after each use, place rags, steel wool or waste in a sealed water-filled metal container.
DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.
FLASH POINT: 110ºF (43.3ºC)

FEATURES AND BENEFITS

Features	Benefits
Excellent adhesion	Sticks to difficult substrates
Excellent flow and leveling	Provides a natural uniform appearance
Superior scrubbability	Withstands repeated cleaning
Tough, durable finish	Long lasting
Fade resistant	Longer lasting color
High solids	Better coverage

OLYMPIC® FastHide® ULTRA Interior/Exterior Alkyd Gloss

GENERAL SURFACE PREPARATION

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding. Prime all bare and porous substrates with an appropriate high quality primer. WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada, contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

CEMENT COMPOSITION BOARD: Cement composition board may present potential adhesion, alkali burn, and efflorescence problems. New board should be aged for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 and the moisture content must be less than 12% prior to priming and topcoating. All cracks and opens seams should be caulked to prevent water penetration. Pre-primed board from the manufacturer may not be uniformly or completely sealed. It is recommended that an alkali resistant primer be applied to ensure complete and uniform sealing prior to topcoating.

CONCRETE/MASONRY BLOCK: Mortar should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. If the material appears to be adhering tightly, a masonry sealer may be applied to seal the surface. Check adhesion by applying a piece of masking tape. If the sealer peels off and has loose particles, remove all chalking or crumbling material, re-seal and re-check adhesion.

CONCRETE and MASONRY: New concrete should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming with an alkali resistant primer.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

WOOD: Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime.

LIMITATIONS OF USE

Apply only when air and surface temperatures are above 50ºF (10ºC) and at least 5ºF (3ºC) above the dew point. For exterior application, avoid painting late in the day when dew or condensation are likely to form or when rain is anticipated. Not for use on galvanized steel.

PACKAGING

Quart (946 mL)
1-Gallon (3.78 L)

Not all products available in all sizes.

SAFETY PRECAUTIONS

Before using the products listed in this publication, carefully read each product label and follow directions for its use. Please read and observe all the warnings and precautionary information on the product labels. Material Safety Data Sheets are available through our Sales Representative, Retailer or by calling (412) 492-5555.

Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. High pressure injection of coatings into the skin by airless equipment may cause serious injury.

Explosion-proof equipment must be used when coating with these materials in confined areas. Keep containers closed and away from heat, sparks, and flames when not in use.

USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-426-6306.

Olympic® - US
PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.olympic.com

Technical Services
1-800-426-6306

Architect/Specifier
1-888-PPG-IDEA

Olympic - Canada
PPG Canada
Architectural Coatings
4 Kenview Blvd
Brampton, ON L6T 5E4

T.D. 3559 4/2009
(Supersedes 12/2008)