



Architectural Coatings

Speedhide Pro-EV Interior Wall & Ceiling Latex Flat

GENERAL DESCRIPTION

Speedhide Pro-EV Interior Wall & Ceiling Latex Flat is a durable, quality interior vinyl acrylic paint designed for new and repaint applications where speed of application is most important in both the commercial and multi-family markets. This low-VOC, low odor paint enables a space to be painted while occupied while delivering the durable product performance required. Speedhide Pro-EV Interior Wall & Ceiling paint has good adhesion, touch-up and application properties on walls, ceilings and trim surfaces. Speedhide Pro-EV is recommended on interior walls, ceilings and trim where a flat finish is desirable.

RECOMMENDED SUBSTRATES

Concrete	Gypsum Wallboard-Drywall
Concrete/Masonry Block	Plaster
Ferrous Metal	Wood

CONFORMANCE STANDARDS

- VOC compliant in all regulated areas
- Can help earn LEED® 2009 credits and LEED for Homes credit
- Meets NaHB Model Green Standards
- MPI® approval in Category #53, Interior Latex, MPI Gloss Level 1
- Meets MPI Green Performance Standards (GPS-1 & GPS-2)

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

Application Equipment: Apply with a high quality brush, roller, paint pad, or by airless spray equipment. Where necessary, apply a second coat.

Airless Spray: Pressure 2000 psi, tip 0.015" - 0.021" Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush

Roller: 3/8" - 3/4" nap roller cover

Thinning: Thinning is not usually required. If necessary, thin with up to 1/4 pint (118mL) of water per U.S. gallon (3.78 L) of paint.

Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 90°F	10 to 32°C
Substrate:	50 to 90°F	10 to 32°C

FEATURES / BENEFITS

Features

- Less than 50 g/L VOC
- Good hiding power and coverage
- Provides a uniform flat finish
- Better finished appearance
- Excellent uniformity
- Easy soap and water cleanup
- MPI approval in Category #53 , Interior Latex, MPI Gloss Level 1
- Can help earn LEED 2009 credits and LEED for Homes credit
- Meets NaHB Model Green Standards

TINTING AND BASE INFORMATION

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

12-110	White and Pastel Base
12-120	Midtone Base*
12-140	Neutral Base*

*Must be tinted before use.

Some colors, or drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

PRODUCT DATA

PRODUCT TYPE:	Vinyl Acrylic Latex
SHEEN:	Flat: 0 to 4 (60° & 85° Gloss Meter)
VOLUME SOLIDS*:	31% +/- 2%
WEIGHT SOLIDS*:	48% +/- 2%
VOC*:	<50 g/L (0.4 lbs./gal.)

WEIGHT/GALLON*: 11.0 lbs. (5.0 kg) +/- 0.2 lbs. (91 g)

*Product data calculated on product 12-110.

COVERAGE: Approximately 400 sq. ft./gal. (37 sq. m/3.78L) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness: 4.0 mils

Wet Microns: 102

Dry Film Thickness: 1.2 mils

Dry Microns: 32

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.

To Touch: 1 hour

To Recoat: 4 hours

To Full Cure: 30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

CLEANUP: Clean tools with warm soapy water.

WASHING INSTRUCTIONS: Wait at least 14 days after painting before cleaning the surface with a non-abrasive mild cleaner.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

Benefits

- Meets the most stringent environmental regulations nationwide
- Saves money; less material required
- Reduces labor expense
- Easy to apply
- Prevents sheen variation
- Safe waterborne formula
- Meets strict performance and aesthetic requirements
- Contributes to sustainable design
- Contributes to sustainable home design

GENERAL SURFACE PREPARATION

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding. Prime all bare and porous substrates with an appropriate primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

CONCRETE: New concrete should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming with an alkali resistant primer.

CONCRETE/MASONRY BLOCK: Mortar should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. If the material appears to be adhering tightly, a masonry sealer may be applied to seal the surface. Check adhesion by applying a piece of masking tape. If the sealer peels off and has loose particles, remove all chalking or crumbling material, re-seal and re-check adhesion.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

GYPHUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, then prime prior to painting the substrate.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

WOOD: Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime.

SOLUBLE STAINS: Apply a SEAL-GRIP® primer over the stained area prior to coating, to avoid bleeding the stain into the topcoat.

RECOMMENDED PRIMERS

Concrete	4-603, 17-921
Concrete/Masonry Block (block fillers)	6-7, 6-15
Concrete/Masonry Block (primers, sealers)	4-603, 17-921
Ferrous Metal	90-712, 90-912
Gypsum Wallboard-Drywall	6-2, 6-4, 9-900, 12-900
Plaster	4-603, 17-921
Wood	6-2, 9-900, 12-900, 17-921

LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C).

Not recommended for use on floors or in high humidity areas.

PROTECT FROM FREEZING.

PACKAGING

- 1-Gallon (3.78 L)
- 5-Gallon (18.9 L)

The PPG logo is a registered trademark and *Ecological Solutions from PPG* is a trademark of PPG Industries, Ohio, Inc. *Speedhide* is a registered trademark of PPG Architectural Finishes, Inc. *Seal-Grip* is a registered trademark of PPG Architectural Finishes, Inc. The *GREENGUARD* Indoor Air Quality Certified Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute. *LEED* is a registered trademark of the US Green Building Council. The *Master Painters Institute* and *MPI* are registered trademarks of Master Painters Institute, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.ppgpro.com

Technical Services
1-800-441-9695
1-888-807-5123 fax

Architect/Specifier
1-888-PPG-IDEA

PPG Canada, Inc.
Architectural Coatings
4 Kenview Blvd
Brampton, ON L6T 5E4

A2.35 5/2013
(Supersedes 4/2013)

Made in the
USA