

Architectural Coatings

PPG Pitt-Glaze WB1 Interior Pre-Catalyzed Acrylic Water-Borne Epoxy Eggshell

GENERAL DESCRIPTION

Pitt-Glaze WB1 Water-Borne Acrylic Epoxy is a one-component acrylic epoxy eggshell coating for interior use and is a low-odor replacement for traditional two component acrylic epoxy products providing a recoatable, impact and mildew-resistant finish. This product meets the strictest VOC regulations with a VOC content of less than 100 g/L and its minimal odor makes Pitt-Glaze WB1 suitable for hospitals, schools, cafeterias and food processing plants, or any area that cannot be taken out of service for an extended period of time. Do not use in household dwellings. This item is intended for industrial use only and should only be applied by a professional. This item is for use in areas such as office space and meeting rooms of industrial, commercial or institutional facilities exposed to repeated heavy abrasion, including mechanical wear and repeated scrubbing with industrial solvents, cleaners, or scouring agents.

RECOMMENDED SUBSTRATES

Aluminum Galvanized Steel

Concrete Gypsum Wallboard-Drywall

Concrete/Masonry Block Plaster Ferrous Metal Wood

CONFORMANCE STANDARDS

VOC compliant in all regulated areas MPI approval in category #151

PRODUCT INFORMATION

16-310 White & Pastel Base 16-340 Neutral Base*

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

PRODUCT DATA

PRODUCT TYPE: Acrylic Epoxy

SHEEN: Eggshell, 10-25 @60°; 30-50 @85°

VOLUME SOLIDS*: 38% +/- 2% **WEIGHT SOLIDS*:** 49% +/- 2%

WEIGHT/GALLON*: 10.0 lbs. (4.5 kg) +/- 0.2 lbs. (91 g)

VOC: <100 g/L (0.8 lbs./gal.) *Product data calculated on product 16-310.

COVERAGE: Approximately 400 sq. ft. (37 sq. meters) per U.S. Gallon

(3.78L) on smooth, nonporous surfaces.
Wet Film Thickness: 4.0 mils
Wet Microns: 102
Dry Film Thickness: 1.5 mils

Dry Microns: 38

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing. Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.

To Touch: 1 hour
To Recoat: 4 hours
To Full Cure: 30 days

Allow 24 hours before normal use. Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

CLEANUP: Clean tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

FEATURES / BENEFITS

Features

Single component, waterbased formula Less than 100 g/L VOC content Excellent abrasion and impact resistance Excellent chemical and stain resistance Lower odor than two-component Excellent mildew resistant coating

Ronofite

No mixing or measuring and unlimited pot life Meets the most stringent regulatory standards Longlasting protection

Extends substrates life

Can be applied in occupied areas

Resists mildew/fungus/biological growth on the paint film

PERFORMANCE DATA

ASTM D1308 Chemical Resistance Results Acid (10% hydrocholoric acid) Excellent Acid (10% phosphoric acid) Excellent Acid (10% sulfuric acid) Excellent Base (25% sodium hydroxide) Excellent Cleaner (Fantastik®) Excellent Excellent Gasoline Mineral Spirits Excellent Excellent Water **Xylene** Limited

Read Label and Safety Data Sheet prior to use. See other cautions on last page.

^{*}Must be tinted before use.

Pitt-Glaze WB1 16-310 Series

Architectural Coatings

PPG Pitt-Glaze WB1 Interior Pre-Catalyzed Acrylic Water-Borne Epoxy Eggshell

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Plaster, concrete, and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. Prime all bare wood, drywall, plaster, masonry, metal, and porous surfaces with an appropriate primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

ALUMINUM: This substrate may present potential adhesion problems. Any coating applied directly to aluminum should be spot applied, allowed to cure overnight, and then evaluated for adhesion. If adhesion is good, the application may proceed.

CONCRETE: New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming with an alkali resistant primer. Painting glazed brick is not recommended due to potential adhesion problems.

CONCRETE/MASONRY BLOCK: Mortar should cure for at least 30 days and preferably 90 days prior to painting. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. If the material appears to be adhering tightly, a masonry sealer may be applied to seal the surface. Check adhesion by applying a piece of masking tape. If the sealer peels off and has loose particles, remove all chalking or crumbling material, re-seal and re-check adhesion.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed with a metal primer.

GALVANIZED STEEL: Caution must be used when selecting coatings for use on all galvanized metal surfaces. These substrates may have a factory-applied stabilizer, which is used to prevent white rusting during storage and shipping. Such stabilizers must be removed by either brush blasting, sanding or chemical treatment prior to priming.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, prior to priming and painting the substrate.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

WOOD: Unpainted wood or wood in poor condition should be sanded smooth and wiped clean. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime.

RECOMMENDED PRIMERS

Aluminum 4020, 90-712

Concrete 4-603XI, 17-921XI, 3210-120XI

6-7, 6-15XI

Ferrous Metal 4020, 90-712, 90-912

4020, 90-712

Gypsum Wallboard-Drywall 6-2, 6-4, 9-900, 12-900XI,

3210-120XI

Plaster 4-603XI, 17-921XI, 3210-120XI Wood 6-2, 9-900, 12-900XI, 17-921XI,

3210-120XI

PACKAGING

Concrete/Masonry Block

Galvanized Steel

1-Gallon (3.78 L) 5-Gallon (18.9 L)

Not all products are available in all sizes.

LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, surface and product temperatures are between 50°F (10°C) and 90°F (32°C).

Do not use on floors, in areas of saturating humidity, or on submerged surfaces.

For professional use only. Not intended for residential use.

PROTECT FROM FREEZING.

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to painting and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae. Examples of these conditions include, but are not limited to areas that are consistently damp with little to no direct sunlight.

Pitt-Glaze WB1 16-310 Series

Architectural Coatings

PPG Pitt-Glaze WB1 Interior Pre-Catalyzed Acrylic Water-Borne Epoxy Eggshell

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply with a high-quality brush, roller, paint pad, or by spray equipment.

Airless Spray: Pressure 1500 to 2000 psi; tip 0.015" to 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush
Roller (nap roller cover): 3/8" - 3/4"

Thinning: Thinning is not required.

Permissible temperatures during application:

 Material:
 50 to 90°F
 10 to 32°C

 Ambient:
 50 to 100°F
 10 to 38°C

 Substrate:
 50 to 100°F
 10 to 38°C

PRECAUTIONS

WARNING! HARMFUL IF INHALED. HARMFUL IF SWALLOWED. MAY CAUSE EYE IRRITATION. MAY CAUSE ALLERGIC SKIN REAC-

TION. Sanding and grinding dusts may be harmful if inhaled. Do not breathe vapor or mist. Do not swallow. Do not get on skin or clothing. Avoid contact with eyes. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note:**These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information. FIRST AID: If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. In case of contact, immediately flush skin with plenty of water while removing contaminated clothing and shoes. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2019 PPG Industries, Inc. All Rights Reserved. The PPG Logo is a registered trademark of PPG Industries Ohio, Inc. Pitt-Glaze is a registered trademark of PPG Architectural Finishes. Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.

