



Architectural Coatings

PPG Exterior Stain Stripper

GENERAL DESCRIPTION

PPG Exterior Stain Stripper is a premium quality, ready to use stripper specially formulated to remove all oil and latex deck coatings, solid and semi-transparent stains, varnishes, polyurethanes, and water sealers. PPG Stain Stripper will also remove graying, mold, mildew and water stains from wood surfaces.

TINTING AND BASE INFORMATION

Not applicable

18-3

PPG Exterior Stain Stripper

RECOMMENDED SUBSTRATES / USES

Decks	Fences
Outdoor Furniture	Wood
Wood Siding	Shingles
Shakes	

FEATURES / BENEFITS

For use on Decks, Fences, Siding and More
Fast, Easy and Ready to Use
Biodegradable
Restores the Clean Natural Look

PRODUCT DATA

PRODUCT TYPE:	Water / Sodium Hypochlorite
SHEEN:	Not applicable for this product code
CLEAN UP:	Soap and Water
DFT:	0.10 minimum to 0.20 maximum mils
COVERAGE:	50 to 150 sq. ft./gal. (4 to 13 sq. m/3.78L)
Coverage does not include variation due to application methods, surface porosity, and/or mixing.	
WEIGHT/GALLON:	4.2 lbs. (1.9 kg) +/- 0.2 lbs. (91 g)
FLASH POINT:	201°F (93.9°C)

LIMITATIONS OF USE

PROTECT FROM FREEZING. Use only on exterior surfaces. Carefully read and follow all safety precautions. Walking surfaces, ladders and scaffolding which become wet with Wood Stripper or rinse water may be slippery. Thoroughly rinse these surfaces to remove all traces of Wood Stripper before using. **STORE IN AN UPRIGHT POSITION.**

DIRECTIONS FOR USE

Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our web site or by calling 1-800-441-9695.

Permissible temperatures during application:

Material:	50 to 120°F	10 to 49°C
Ambient:	50 to 100°F	10 to 38°C
Substrate:	50 to 100°F	10 to 38°C

GENERAL SURFACE PREPARATION

AREA PREPARATION: Wood surface must be dry. Apply when air, product, and surface temperatures are 50°F (10°C) or above. Thoroughly shake or stir PPG Stain Stripper prior to use. Use product full strength. Do not dilute. Test a small, inconspicuous area prior to use to ensure acceptable appearance. Apply liberally with a nylon brush or roller. Do not allow PPG Stain Stripper to come into contact with bare metal or surfaces that are to remain coated. Do not allow PPG Stain Stripper to dry. If drying occurs, mist with water and reapply Stain Stripper. Wait 5 - 45 minutes for PPG Stain Stripper to soften or dissolve coating. Coating will easily rinse off when ready. Scrub areas where needed with a stiff bristle brush. Work in the direction of the wood grain to minimize grain raising. Rinse wood thoroughly with water from a garden hose or power washer at a setting of 500 - 1200 psi to eliminate scrubbing.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

RECOMMENDED PRIMERS

None. Refer to Surface Preparation Recommendations

APPLICATION INFORMATION

Application Equipment: Apply with a nylon brush or roller.

Thinning: Use product full strength. Do not dilute.

PACKAGING

1 Gallon (3.78L)

Not all products are available in all sizes.

PPGAF believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.pittsburghpaints.com

Technical Services
1-800-441-9695
1-888-807-5123 fax

Architect/Specifier:
1-888-PPG-IDEA

PPG Architectural Finishes
400 S. 13th Street
Louisville, KY 40203

PPG Canada, Inc.
Architectural Coatings
4 Kenview Blvd
Brampton, ON L6T 5E4

B1.12 6/2006