



HOUSTON
713-680-2799 FAX 713-681-1020

DALLAS
972-258-6040 FAX 972-570-5583

2200 AQUA GLEEM ACRYLIC GLOSS HOUSE PAINT
FINISH COAT FOR PROPERLY PRIMED EXTERIOR
WOOD, MASONRY, HARDBOARD AND METAL

FEATURES

Gloss Finish
Mildew resistant paint film
Excellent weathering and color retention
Excellent blister and crack resistance
Resists peeling on properly primed surfaces
Easy soap and water clean up

RECOMMENDED USES

A premium quality 100% acrylic house paint that dries to an exceptionally durable rich gloss that lasts approximately three times longer than oil base house paint. Aqua Gleem is designed for use on properly primed or previously painted exterior wood, hardboard, masonry, concrete block, stucco.

SPECIFICATION DATA

Colors: White, black and factory manufactured ready mixed colors.

Finish: Gloss, 65-75 units @ 60°

Density: 9.95lbs/gal.

Cleanup Solvent: Soap and water

Recommended film thickness:
1.3 mils dry
3.7 mils wet

Solids:

Weight: 44.4%
Volume: 35.5%

Flash Point: Non-flammable

Drying Time at 77°F and 50% RH:
To touch - 30 minutes
To recoat - 2 hours

Coverage:

300 to 450 square feet per gallon,
depending on method of application
and texture and porosity of surface.

V.O.C. Content: 0.97 lbs/gal

All surfaces must be clean, dry and free of dust, dirt, chalking and peeling paint, wax, grease or any other contamination. Repair any surface defects before painting.

New Surfaces:

Wood - No prime coat is required over rough surfaces or non-staining woods. Prime smooth surface woods, such as cedar and redwood, with Monarch 1601 H.P. Primer or 2190 Stain Resisting Primer. More than one coat may be required.

Unprimed Hardboard Siding - Prime entire surface including all nail holes, butt joints, and drip edges with Monarch 1601 H.P. Primer, 2190 Stain Resisting Primer, 2151 Royal Acrylic Primer, or 4690 M-Prime Interior/Exterior Primer. Caulk all joints, cracks, and flashings. Avoid rupturing surface when setting nail heads.

Masonry and Stucco - Requires a 30 day curing period.

Ferrous Metals - Prime with Monarch 5512 Red Iron Oxide or 5513 Universal Primer.

Non-ferrous or Galvanized Metals - Prime with Monarch 5510 Galvanized Iron Primer.

Previously Painted Surfaces:

Remove dirt and chalk. Clean and spot prime bare areas. Sand glossy areas and dust clean. If surface is in poor condition, prime with Monarch 1601 H.P. Primer, 2190 Stain Resisting Primer, or 2151 Royal Acrylic Primer.

Weathered Masonry:

Remove chalk and loose material, pressure washing preferred. Use 5505 Monarch Masonry Conditioner on chalky surfaces.

MIXING AND THINNING

Tinting - May be tinted with Monarch's universal colorants from pastel to ultra deep shades.

Thinning - Thinning is not normally needed. If necessary, use only a small amount of water (up to 1/2 pint per gallon). Do not mix with solvent or solvent thinned paints.

APPLICATION

Method - Apply with a nylon polyester brush, 1/2" nap roller, or spray. For airless spray, use .015" or larger tip, adjust pressure as necessary.

Cleanup - Clean equipment promptly with soap and water. Wipe up spatters and drips immediately with damp cloth or sponge.

Dry Time - Under normal conditions to touch in 30 to 60 minutes and to recoat 2 hours. Low temperature or high humidity will increase this time.

PRECAUTIONS

PROTECT FROM FREEZING!

Do not apply if air or surface temperature is below 50°F (10°C).

Do not paint within two hours of dew, rain, or temperature drop.

Prior to using this product, the user is specifically directed to obtain and read the current Material Safety Data Sheet and Label for this product. If, after reading these documents, you do not understand them, do not use this product.

KEEP OUT OF THE REACH OF CHILDREN

Do not take internally.

Close container after each use.

Certain tannic acids and resin stains may require

The statements made in this brochure on product labels, or by the agents of Monarch Paint Company are for information only and are believed to be true and accurate. These statements are intended as a guide to approved construction practices and materials. Many variables that affect results (including workmanship, construction equipment, weather, and quality of other materials) are beyond our control. Consequently Monarch Paint Company does not make nor authorize any agent to make any warranty of merchantability or fitness for any purpose or for any other warranty, representation or guarantee, expressed or implied, concerning this material except that it conforms to Monarch Paint Company's quality control standards. Monarch Paint Company's only liability whatsoever to the buyer or user of this product is limited to the purchaser's cost of the product itself.