

## TRAFFIC ZONE MARKING PAINT

5502 WHITE 5503 YELLOW 5504 RED 5506 BLACK 5508 HANDICAP BLUE

**Durable and weather resistant**  
**Interior or exterior use**  
**Fast drying**  
**Adaptable to a wide variety of pavement surfaces**  
**Water Based**  
**Lead free**

An abrasion resistant traffic marking paint that needs no special equipment for application or cleanup. It provides durable line markings for streets, parking lots, factory traffic zones, warehouses, and tennis courts. For use on brick, concrete, wood, or nonbleeding asphalt surfaces. New asphalt surfaces should be checked for bleeding prior to application. Monarch performance alternate for TT-P-1952B Traffic and Airfield Marking Paint, Water Emulsion Base.

**Colors:** White, Yellow, Black, Handicap Blue or Red

**Finish:** Flat, 1.5 - 3.5 @ 60°

**Density:**

White - 12.80 lbs/gal  
Yellow - 12.45 lbs/gal  
Red - 11.81 lbs/gal  
Blue - 12.80 lbs/gal  
Black - 11.80 lbs/gal

**Cleanup Solvent:** Water

**Recommended film thickness:**

3.0 mils dry  
6.0 mils wet

**Solids:**

Weight: 70.2% (White)  
Volume: 54.2% (White)

**Flash Point:** over 200°F

**Drying Time at 77°F and 50% RH:**

To touch - 15 minutes  
To recoat - 30 minutes  
To traffic - 60 minutes

**Coverage:**

75 to 100 square feet per gallon, or 250 to 300 lineal feet of 4 inch line depending on method of application and texture and porosity of surface.

**V.O.C. Content:**

5502 - 0.39 lbs/gal  
5503 - 0.37 lbs/gal  
5504 - 0.42 lbs/gal  
5506 - 0.42 lbs/gal  
5508 - 0.54 lbs/gal

5502, 5503, 5504, 5506, 5508

**All surfaces must be clean, dry and free of grease and other foreign matter. Fresh bituminous surface should be allowed to weather a minimum of 30 days prior to application of markings.**

**Finish Coat:**

1 or 2 coats of Traffic Zone Marking Paint. Material should be strained prior to use, to avoid any clogging of equipment.

**Available in 55 gallon drums for large volume jobs.**

**Cleanup:**

Wipe up all drips and spatters with water.

**Tinting** - Not recommended.

**Thinning** - Apply at packaged consistency or reduce as needed to maintain workability with up to 1/2 pint water.

**Method** - Brush, 1/2" minimum nap roller, or mechanical coating equipment. For best wear and life, apply at 15 mil wet film thickness.

**Dry Time** - Under normal weather conditions and 6 mils wet thickness, to touch 5 minutes and to recoat 10 minutes. Will take traffic in 15 minutes.

**PROTECT FROM FREEZING!**

**Do not apply if air or surface temperature is below 50°F (10°C).**

**Do not paint within two hours of dew, rain, or temperature drop.**

**KEEP OUT OF THE REACH OF CHILDREN**

**Use with adequate ventilation.**

**Close container after each use.**

**Obtain and read MSD Sheet before using this product.**