

# **7707 ALL-PURPOSE VARNISH**

## **CLEAR FINISH COAT FOR INTERIOR AND EXTERIOR WOOD SURFACES**

**Hard tough coating**  
**Excellent resistance to abrasion, marring,**  
**chipping, detergents, grease and alcohol**  
**Natural finish**  
**High gloss wet look**

A clear liquid, polyurethane based coating for use on interior wood surfaces, such as paneling, cabinets, counter tops, etc. May be used exterior for doors, trim, patio furniture, etc. Not recommended for use over lacquer sanding sealer, shellac, or wax type stain. Monarch performance alternate for Federal Specification TTV-71h.

**Colors: Clear**

**Finish: Gloss, 85 to 95 units @ 60°**

**Density: 7.39 lbs/gal.**

**Cleanup Solvent: Monarch 7710 All Purpose  
Thinner**

**Recommended film thickness:**  
1.0 mils dry  
3.2 mils wet

**Solids:**

**Weight: 50.2%**  
**Volume: 42.6%**

**Flash Point: Over 100°F**

**Drying Time at 77°F and 50% RH:**  
To touch - 2 hours  
To recoat - 8 hours

**Coverage:**  
up to 650 square feet per gallon,  
depending on method of application  
and texture and porosity of surface.

**V.O.C. Content: 3.67 lbs/gal**

7707

**All surfaces must be clean, dry and free of dust, dirt, all paint, wax, grease or any other contamination. Repair any surface defects before varnishing.**

**New Surfaces:**

**Wood** - Apply Monarko 5525 Interior Wood Stain if desired. Fill cracks, voids, and nail holes with color putty, or suitable filler prior to using 7707. Apply a first coat of 7707 All Purpose Varnish reduced with one pint mineral spirits per gallon. Sand smooth.

**Tinting** - Not recommended.

**Method** - China bristle brush, 1/4" to 3/8" nap roller or spray. For airless spray, use fine finish .13" or larger tip. Stir well before using. Avoid lap marks by keeping a wet edge at all times. Sand between coats and dust thoroughly.

**Dry Time** - Under normal conditions to touch in 2 hours and to recoat 8 hours.

**CAUTION! COMBUSTIBLE!**

Keep away from heat, sparks, and open flame.

Use with adequate ventilation.

Avoid prolonged contact with skin and breathing of vapor or spray mist.

**Previously Varnished Surfaces:**

Must be sanded to bare wood, then use procedure described for New Surfaces. Old surfaces in good condition should be sanded and dusted clean. When used as an exterior finish, 2 coats are recommended,

**Thinning** - Apply at packaged consistency or if necessary, thin with up to 1/4 pint per gallon of Monarch 7710 All Purpose Thinner. Do not use lacquer thinner.

**Cleanup** - Wipe up drips and spatters with cloth damp with Monarch 7710 All Purpose Thinner. Clean equipment with Monarch 7710 All Purpose Thinner.

**Important** - It is recommended that this product not be applied below 50°F (10°C) air and surface temperature and if relative humidity is over 50%.

**KEEP OUT OF THE REACH OF CHILDREN**

Do not take internally.

Close container after each use.