

HOUSTON 713-680-2799 FAX 713-681-1020

DALLAS 972-258-6040 FAX 972-570-5583

9901 SAND FINISH INTERIOR WALLS-CEILING SAND FINISH

FEATURES

Pleasing low odor Minimal shrinkage Uniform appearance Economical

RECOMMENDED USES

Produces a sand finish look on drywall, cured plaster and over properly primed paneled surfaces. Asbestos

SPECIFICATION DATA

Colors: Light Gray Flash Point: none

Finish: Flat Drying Time at 77°F and 50% RH:

overnight.

Cleanup Solvent:

varies with application procedure

1/64" to 1/32" preferred

Recommended film thickness:

Package Weight: 35# bag

Coverage:

300 square feet per bag,

V.O.C. Content: complies with V.O.C.

regulations

7-93 11-2 All surfaces must be clean, dry and free of dust, dirt, chalking and peeling paint, wax, grease or any other contamination.

New Surfaces:

All new gypsum wallboard surfaces must be free of grease, dust, dirt, form release agents, stains, mildew and any other foreign substances that would adversly affect the adhesion of the product. All large cracks, holes and other surface irregularities should be filled with a suitable putty or caulking.

Previously Painted Surfaces:

Remove dirt and chalk. Clean bare areas. Sand glossy areas and dust clean. If surface is in poor condition, prime with suitable Monarch primer.

MIXING AND THINNING

Tinting - One pint of Mopako Latex Flat Wall Paint can be added to obtain desired color.

Mixing - Add full 35# bag of texture to 2 1/2 gallons of clean water with vigorous mixing until thoroughly wet and free of lumps. Let stand 15 to 20 minutes. Additional water may be added for desired texture.

APPLICATION

Method - Spray or hopper gun preferred. Homax, Goldblatt or hand held pump may be used for small repair areas.

Cleanup - Water

Dry Time - Overnight

PRECAUTIONS

PROTECT FROM FREEZING!

KEEP OUT OF THE REACH OF CHILDREN

Do not apply if air or surface temperature is below 50°F (10°C)

Do not take internally.

A protective respirator should be worn while sanding.

Prior to using this product, the user is specifically directed to obtain and read the current Material Safety Data Sheet and Label for this product. If, after reading these documents, you do not understand them, do not use this product.