



DFT-062

DELFLLEET® Evolution

F3998

2.1 VOC Primer Surfacer

Delfleet Evolution F3998 2.1 VOC Primer Surfacer is a medium gray, non-isocyanate primer surfacer that offers superior sanding, excellent gloss holdout and a ready-to-spray 2.1 VOC. F3998 must be mixed with the F3999 Activator.

Products

| | |
|-----------------------------------|-------|
| 2.1 VOC Primer Surfacer | F3998 |
| 2.1 VOC Primer Surfacer Activator | F3999 |

Compatible Surfaces

F3998 may be applied over:











- Properly cleaned and sanded aluminum or fiberglass
- Cured and sanded OEM Finishes (excluding lacquer)
- Properly cleaned and sanded steel*
- Properly cleaned and sanded galvanized steel*
- F3960 Pigmented Chrome Etch Primer
- F3963 Chrome Etch Primer
- F4921 2.1 VOC Epoxy Primer
- F4935/36/37 High Solids Epoxy Primers

*Steel and galvanized steel **must** be treated with SX579/SX520 Metal Cleaner/Conditioner or coated with F3960 or F3963 Etch Primers or F4921 Epoxy Primer before applying F3998.



F3998

Application Data

| | | | | | | | | | | | | | | | | |
|---|--|--|---------------------------------|---|--|--------------------|------------------|-------------------|--------------|--------------|----------------------|-------------------|------------------------|-----------------------------|---|---|
| Selection of Substrate Cleaner: | | Code | Product | Purpose | | | | | | | | | | | | |
| ONECHOICE® Commercial CFX Cleaners |  | CFX435LV | Low VOC Cleaner | Compliant cleaner suitable for removing dirt, grease or other contaminants before or during the painting process. | | | | | | | | | | | | |
| | | CFX436 | Wax & Grease Remover | Suitable for removing dirt, grease or other contaminants before or during the painting process. | | | | | | | | | | | | |
| | | CFX437 | Heavy Duty Wax & Grease Remover | Used to remove heavy milling oils and grease from bare substrates prior to the painting process. | | | | | | | | | | | | |
| Mixing Ratio: |  | F3998 : F3999 2 : 1 | | | | | | | | | | | | | | |
| Pot Life @ 70°F (21°C) / 50% RH: |  | 1/2 hour - <i>heat and humidity will shorten pot life.</i> Product may be reduced with 10% Acetone (by volume to RTS material). This will extend potlife to 1 hour at 70°F (21°C) | | | | | | | | | | | | | | |
| Spray Viscosity: |  | <table><tr><td></td><td>#3 ZAHN CUP</td><td>6DIN</td></tr><tr><td></td><td>35 seconds</td><td>19 seconds</td></tr></table> | | | | #3 ZAHN CUP | 6DIN | | 35 seconds | 19 seconds | | | | | | |
| | #3 ZAHN CUP | 6DIN | | | | | | | | | | | | | | |
| | 35 seconds | 19 seconds | | | | | | | | | | | | | | |
| Spray Gun Set-up: |  | <table><tr><td></td><td>HVLP</td><td>COMPLIANT</td></tr><tr><td>Fluid Tip:</td><td>1.2 – 1.7 mm</td><td>1.2 – 1.7 mm</td></tr><tr><td>Air Pressure:</td><td>10 PSI at the cap</td><td>45 – 55 PSI at the gun</td></tr><tr><td>Pressure Pot Set-up:</td><td>1.1 – 1.4 mm tip 12 – 14 fluid ounces per minute</td><td>1.1–1.4 mm tip 12 – 14 fluid ounces per minute</td></tr></table> | | | | HVLP | COMPLIANT | Fluid Tip: | 1.2 – 1.7 mm | 1.2 – 1.7 mm | Air Pressure: | 10 PSI at the cap | 45 – 55 PSI at the gun | Pressure Pot Set-up: | 1.1 – 1.4 mm tip 12 – 14 fluid ounces per minute | 1.1–1.4 mm tip 12 – 14 fluid ounces per minute |
| | HVLP | COMPLIANT | | | | | | | | | | | | | | |
| Fluid Tip: | 1.2 – 1.7 mm | 1.2 – 1.7 mm | | | | | | | | | | | | | | |
| Air Pressure: | 10 PSI at the cap | 45 – 55 PSI at the gun | | | | | | | | | | | | | | |
| Pressure Pot Set-up: | 1.1 – 1.4 mm tip 12 – 14 fluid ounces per minute | 1.1–1.4 mm tip 12 – 14 fluid ounces per minute | | | | | | | | | | | | | | |
| Number of Coats: |  | 2 – 4 wet coats | | | | | | | | | | | | | | |
| Dry Times: |     | <i>Shop conditions will affect dry times.</i> Dust-Free: 70°F (21°C) 10 minutes Dry to Sand: 70°F (21°C) 2 – 4 hours Purge Time: 70°F (21°C) 20 minutes Force Dry: 140°F (60°C) 30 minutes* Recoat: 70°F (21°C) Up to 2 days to recoat with itself (Max before sanding is required) Topcoat: 70°F (21°C) Must be sanded before topcoating. Do not use as an unsanded sealer. | | | | | | | | | | | | | | |
| <i>*Force dry times are for quoted metal temperature. Additional time should be allowed in the force-drying schedule to allow metal to reach recommended temperature.</i> | | | | | | | | | | | | | | | | |

**Force dry times are for quoted metal temperature. Additional time should be allowed in the force-drying schedule to allow metal to reach recommended temperature.*

F3998

Application Data (continued)

Film Build:

| | Wet (per coat) | Dry (total) |
|---------|-------------------|----------------|
| Minimum | 3.0 mil | 2.0 mil |
| Maximum | 9.0 mil | 6.0 mil |

Physical Characteristics:

| | F3998 (package) |
|--|--------------------|
| Total Solids By Weight (RTS): | 86.0% |
| Total Solids By Volume (RTS): | 72.0% |
| RTS Combinations: | F3998 : F3999 |
| Volume Ratio | 2 : 1 |
| Applicable Use Category | Primer |
| VOC Actual | 220 (g/L) |
| VOC Actual | 1.84 (lbs/gal) |
| VOC Regulatory (less water less exempt) | 238 (g/L) |
| VOC Regulatory (less water less exempt) | 1.99 (lbs/gal) |
| Density | 1436 (g/L) |
| Density | 11.98 (lbs/gal) |
| Volatiles wt. | 19.5% |
| Water wt. | 0.0% |
| Exempt wt. | 4.2% |
| Water vol. | 0.0% |
| Exempt vol. | 7.6% |
| Total Solids By Weight (RTS): | 82.7% |
| Total Solids By Volume (RTS): | 69.6% |
| Theoretical coverage in sq. ft. /US gal. Ready-to-spray (RTS), giving 1 mil. (25µm) dry film thickness (Assuming 100% Transfer Efficiency). | 1116 sq. ft. |

Health and Safety:

Safety Data Sheets (SDS) for the PPG products mentioned in this publication are available through www.ppgcommercialcoatings.com (Safety, SDS Search) or your PPG Distributor.

For additional information regarding this product, see the SDS and LABEL information.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320 AND IN MEXICO 01-800-00-21-400.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.



PPG Industries
Commercial Coatings
19699 Progress Drive
Strongsville, OH 44149
1-800-647-6050

PPG Canada Inc.
2301 Royal Windsor Drive, Unit #6
Mississauga, Ontario L5J 1K5
1-888-310-4762