


Aquabase Plus® Waterborne Thinner Selection Guide

Below 30% Relative Humidity

TEMPERATURE



Above 30% Relative Humidity



* Note: Using P980-5085 waterborne thinner with humidity levels above 30% can cause extremely slow flash and overall drying of the basecoat. Do not blend waterborne thinners as this will also affect overall basecoat performance. Use either P980-5000 or P980-5085 depending on humidity.