



DELTRON® Reducer Selection Guide

Low VOC



The below recommendations are only a general reference and should be used solely as a starting point for choosing the appropriate reducer. Your particular spray environment and job size may require slight adjustments.

Temperature

60°F (15°C)		65°F (18°C)		70°F (21°C)		75°F (24°C)		80°F (26°C)		85°F (29°C)		90°F (32°C)		95°F (35°C)	
	DT1845 <i>Primer / Sealer</i>														
		DT1850 <i>Primer / Sealer</i>													
	DT1845 <i>Clearcoat</i>								DT1855 <i>Primer / Sealer</i>						
		DT1850 <i>Clearcoat</i>													
	DT1855 <i>Clearcoat</i>														
<div>Tips:</div> <ul style="list-style-type: none">• A higher temp reducer in a clearcoat will allow the surface to stay open longer and provide additional leveling.• Consider the job size when selecting the appropriate reducer. Larger jobs may require a higher temp reducer in order to maintain a “wet” edge.• Where there is excessive air flow in the spray area , a higher temp reducer should be considered to minimize the potential for solvent entrapment.												SLV898* <i>Clearcoat</i>			
												*must be mixed with DT1855 reducer			