

Product Data Sheet

March 2022

INTERNATIONAL MASTER
FOR PROFESSIONAL USE ONLY



U0930V_TV

Transparent Sealer P565-755 – EHS System

Product	Description
P565-755	Transparent Sealer
P210-7644	EHS Hardener - Standard
P210-7606	EHS Plural-Mix Hardener
P852-6442	EHS Thinner - Slow
P852-6444	EHS Thinner - Medium
P852-6446	EHS Thinner - Fast
P852-6448	EHS Thinner - Extra Fast
P100-1020	Flexible Additive

Product Description

A versatile transparent wet-on-wet sealer with excellent adhesion properties. Substrates need only be cleaned and scuffed, thereby saving considerable preparation time. It is especially useful for resprays where the masking of door shuts is not as critical as with conventional non-sand primers because any overspray is transparent. The product is also useful for sealing off polyester filled areas and can act as a coloured sealer or groundcoat when tinted with TURBO VISION® 2-pack Premium High Flow EHS Topcoat. Use over complete panels only.

When used in conjunction with TURBO VISION® 2-pack Premium High Flow EHS Topcoat ancillaries, the ready-for-use VOC content of this product is lower than 540 g/l.



THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

Nexa Autocolor and design and Turbo Vision are registered trademarks of PPG Industries Ohio, Inc. © 2017 PPG Industries, Inc. All rights reserved.

Innovating Repair Solutions



Standard and Fast Process **HVLP and Conventional Application USAGE Adhesion Promoter Sealer Plural-Mix Mode** If required it is possible to tint P565-755 If required it is possible to tint P565-755 with **Tinting prior** with TURBO VISION® Tinters TURBO VISION® Tinters to activating Maximum Ratio: Maximum Ratio: 10 parts P565-755 :1 Part P600 10 parts P565-755 :1 Part P600 P565-755 6 parts P565-755 4.5 parts P210-7644 1 part P210-7606 1 part P852-644x 2.5 parts P852-644x 1.5 parts For 2K Plural Mix Equipment it is recommended that the P565-755 is prethinned 4.5:1.5 and that this pre-thinned primer is then activated 6:1 with P210-7606 Hardener Pot life at 20°C: 4 hours Pot life at 20°C: 4 hours Clean gun immediately after use Clean gun immediately after use 19-20 secs. DIN4 at 20°C 19-20 secs. DIN4 at 20°C 1.4-1.8 mm 1.4-1.8 mm 3.3-4.0 bar (50-60 psi) 3.3-4.0 bar (50-60 psi) 1.0-1.4 mm 1.0-1.4 mm Use compliant spray equipment Use compliant spray equipment 1 double or 2 single coats 1 double or 2 single coats 25-35 microns (1-1.5 thou) 25-35 microns (1-1.5 thou) 10-15 minutes between coats 10-15 minutes between coats 15-30 minutes before topcoating 15-30 minutes before topcoating **RECOAT** Follow after flash-off time with Follow after flash-off time with TURBO VISION® 2-pack Premium TURBO VISION® 2-pack Premium High Flow EHS Topcoat High Flow EHS Topcoat

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

Nexa Autocolor and design and Turbo Vision are registered trademarks of PPG Industries Ohio, Inc. © 2017 PPG Industries, Inc. All rights reserved.



NOTE:

P565-755 is NOT recommended for use over old synthetic finishes.

For more detailed information on the preparation of specific substrates, see "Preparation and Pre-treatment" PDS Q0100.

SUBSTRATES and PREPARATION

P565-755 AS WET-ON-WET ADHESION PROMOTER AND SURFACER

Substrates need to be well flatted when using P565-755 as a tinted sealer or groundcoat.

SUBSTRATES:	SUBSTRATES:	NOTES:
Bare Metal	Etch prime steel and aluminium before applying P565-755.	Small rub throughs i.e. areas flatted through to bare steel, can be directly overcoated with P565-755.
Existing 2-pack paintwork	Existing 2-pack paintwork	
Bare GRP/"Glasonite"	Clean with P273-901 BodyKleen. Flat thoroughly using P240-P320 dry sanding machine discs or P400-P600 wet and dry paper, then clean with P850-1378.	Take care not to break through the gel coat when flatting GRP.
Fillers	Flat thoroughly with P280- P320 dry sanding machine discs then clean with P850- 1378.	

RECOAT:

P565-755 may be recoated with TURBO VISION® 2-pack Premium High Flow EHS Topcoat See appropriate PDS for further details.

P565-755 is NOT recommended for use beneath synthetic topcoat lines such as EHS Hi-Gloss 383.

APPLICATION EQUIPMENT INFORMATION

HVLP

The most suitable HVLP gun for the application of Commercial Transport products is a pressure feed system.

Air cap pressure : 0.675 bar (10 psi) maximum
Paint pressure : 0.3-1.0 bar (5-15 psi) maximum

If long fluid lines are used, the paint pressure will need to be increased.

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

Nexa Autocolor and design and Turbo Vision are registered trademarks of PPG Industries Ohio, Inc. © 2017 PPG Industries, Inc. All rights reserved.

Innovating Repair Solutions



DRYING

The drying times quoted are approximate times and will vary depending on drying conditions and film thickness. Poor ventilation, temperatures below 20°C and excessive film thickness will extend the drying times.

SELECTION OF HARDENER AND THINNER

The exact choice of hardener and thinner combination will depend on the gun set up used, air movement, temperature application conditions, size of job and personal preference.

FLATTING

Normally, P565-755 can be left for 2 days without flatting prior to recoating. However, if left longer than 2 days P565-755 must be scuffed before recoating.

RECTIFICATION

If dirt pick-up or damage occurs, and rectification is required, P565-755 may be lightly flatted when hard (approximately 2 hours air-dry at 20°C).

PAINTING PLASTIC

P565-755 may be applied over prepared painted plastic. Prepare by careful cleaning and scuffing with Scotchbrite Fine when using P565-755 as an adhesion promoter. Flat thoroughly using P400-P600 wet or P280-P320 dry, when using tinted P565-755 as a coloured sealer.

P565-755 may be applied over primed plastic (see Plastics Painting System data sheet Y0100 for details). If P565-755 is applied over a flexible plastic, it must be mixed as detailed below:

	Flexible plastic	Very flexible plastic
P565-755	5 parts	2 parts
Flexible Additive for Plastics (P100-2020)	s 1 part	1 part

AFTER adding P100-2020, activate and thin in the normal way.

The addition of P100-2020 will extend the drying times.

TINTING

Where a coloured sealer is required, P565-755 can be tinted with TURBO VISION® 2-pack Premium High Flow EHS Topcoat up to a ratio of 10 parts P565-755: 1 part TURBO VISION® P600 Tinters. Then activate and thin according to the Standard P565-755 process.

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

VOC INFORMATION

The EU limit value for this product (product category: IIB.c) in ready to use form is max. 540g/litre of VOC. The VOC content of this product in ready to use form is max. 540g/litre.

Depending on the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.

Note:

Combinations of this product with P100-2020, will produce a paint film with special properties as defined by the EU Directive code.

In these specific combinations: The EU limit value for this product (product category: IIB.e) in ready to use form is max. 840g/litre of VOC. The VOC content of this product in ready to use form is max. 840g/litre.

These products are for professional use only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose.

For Heath and Safety information please refer to the material Safety Data Sheet, also available at: http://www.ppg.com/Autocolor_MSDS

For further information please contact:

Customer Service Sales Group PPG Industries (UK) Ltd Needham Road Stowmarket Suffolk IP14 2AD

Tel: 01449 771771 Fax: 01449 773472

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

Nexa Autocolor and design and Turbo Vision are registered trademarks of PPG Industries Ohio, Inc. © 2017 PPG Industries, Inc. All rights reserved.



Innovating Repair Solutions