

Product Data Sheet

August 2020

FOR PROFESSIONAL USE ONLY



V1450V

Waterborne Basecoats for Commercial Transport

Product	Description	
CT Waterborne Basecoat Ready Mix		
P935-1250	Aquabase Plus Performance Additive	
P980-5000	0 Waterborne Thinner	
P980-5050	Hi Temp Waterborne Thinner	
P980-6050	Waterborne Precleaner	

Product Description

Waterborne Basecoat for Commercial Transport is a ready mixed range of solid colour, metallic and pearlescent basecoats specifically designed to meet the requirements of the Commercial Refinish Market.

The product has been developed in accordance with European legislation and delivers a VOC of below 420g/l.

When used in conjunction with the relevant Nexa Autocolor compliant Clearcoat, this waterborne system delivers excellent gloss, appearance and durability.





Nexa Autocolor and Turbo Plus are trademarks of PPG Industries.

© 2006 PPG Industries, all rights reserved.

Copyright in the above product numbers that are original is asserted by PPG Industries.

Innovating Repair Solutions

PERFORMANCE PROCESS				
		Solid Colours	Metallic & 2-stage Pearlescent/Special Effect Basecoats	
	Ready-Mix P935-1250 Thinner	10 parts 1 part 1 part	10 parts 1 part 1,5 part	
∏s	22-26 secs DIN 4 cup (at 20°C). Viscosity may be adjusted by addition of P980-5000 or 5050 thinner. At high temperatures above 30°C, 2 parts P980-5000 or P980-5050 (i.e. an additional 10%) may be used to help with application, laydown and overspray absorption.			
	Always filter using nylon filters. (125 microns is recommended) Pot-life 2 at 20°C : 3 months			
******	Compliant HVLP Gravity: 1.3-1.5mm Pressure: 0.85-1.0mm Fluid delivery: 280-320 cc/min Air Cap Pressure 0.675 Bar (10 psi.) max			
	Clean the gun using water in a suitable gun-cleaning machine. For gravity feed guns unscrew the paint cup (and filter if fitted) and rinse separately. Rinse gun through with clean water. Finally spray through with clean Aquabase Plus thinner P980-5000 and ensure that the gun is fully dry before storing or further use.			
	2-3 single coats followed by 1 control coat for metallic and micas over uniformly matt last coat			
(†(†(Flash off between coats (20°C / 60% Humidity) -: 20-30 mins. or until uniformly matt. DRYING TIME CAN BE GREATLY REDUCED WITH THE USE OF AIRBLOWERS AND / OR FORCE DRY			
	For n	Wait until uniformly dry before cle nulti-striping work, it's recommended to force Metal Temperature -: 45°C - 30 mins		
	If necessary, may be hand denibbed with P1200 wet/dry paper. Ensure basecoat is fully dry and apply minimum pressure whilst denibbing. Recoat times (20°C)-: Minimum - 20 mins Maximum - 72 hours (after which 1 coat of basecoat has to be applied prior to clearcoating)			
Clearcoat	to relevant PDS for d Waterborne basecoa	ts may be overcoated with Autocolor cleard etails. ts can be overcoated up to 48 hours after a pearance tack the basecoat prior to clearco	pplication.	

Nexa Autocolor and Turbo Plus are trademarks of PPG Industries.

© 2006 PPG Industries, all rights reserved.

Copyright in the above product numbers that are original is asserted by PPG Industries.

Innovating Repair Solutions

General Process Notes

SUBSTRATES AND PREPARATION

Clean all surfaces with **P980-6050**. Wet flat with P800 or finer, dry machine sand with P360 or finer. Wash off residues and dry thoroughly before re-cleaning with **P980-6050** using one rag for application and another rag for wiping off. The use of a Tack rag is strongly recommended as a final stage.

Apply over the following Nexa Autocolor primer systems-:

P580-350X or P580-450x - Chromate Free Epoxy primers P565-370X – Wet On Wet Undercoat P565-1027/8 - 2K Primer Surfacer

Ensure all primers are used as per the relevant TDS.

Nexa Autocolor Commercial Transport Waterborne Basecoat should never be used over -:

Wash Primers Etch Primers Chromated Epoxy Primers Acrylic Thermoplastic Finishes

STORAGE AND HANDLING

Nexa Autocolor Commercial Transport Waterborne Basecoat mixed colours, activator, thinners and cleaner should be stored in a cool, dry place away from sources of heat. During storage and transportation, temperatures must be maintained at a minimum of +5C and a maximum of +35C.

Waterborne Basecoat should always be mixed in clean, dry containers and used in clean, dry equipment. Do not use in mixing vessels or spray equipment that contain solvent residues.

Mixing vessels should ideally be plastic; If metallic they should have an anti-corrosion lining

PERFORMANCE AND LIMITS

Dry film build should be between 15 and 25 microns.

EQUIPMENT CLEANING

After use, clean all equipment thoroughly using a dedicated waterborne cleaner or cleaning equipment. Ensure all equipment is clean and dry before storage or use.



These products are for professional use only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose.

For Heath and Safety information please refer to the material Safety Data Sheet, also available at: http://www.ppg.com/Autocolor_MSDS

VOC INFORMATION

The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420g/litre of VOC. The VOC content of this product in ready to use form is max. 420g/litre.

Depending on the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.

For further information please contact:

Customer Service Sales Group PPG Industries (UK) Ltd Needham Road Stowmarket Suffolk IP14 2AD

Tel: 01449 771771 Fax: 01449 773472

