

# **Product Data Sheet**

May 2009

## FOR PROFESSIONAL USE ONLY



# V1450V

# Waterborne Basecoats for Commercial Transport P961-Line

Product	Description	
P961Lline	CT Waterborne Basecoat Ready Mix	
P935-3006	Waterborne Basecoat Activator	
P980-5000	Waterborne Thinner	
P980-5050	Hi Temp Waterborne Thinner	
P980-6050	Waterborne Precleaner	

#### **Product Description**

Waterborne Commercial Transport (P961-Line) is a ready mixed range of solid colour, metallic and pearlescent basecoats specifically designed to meet the requirements of the Commercial Refinish Market.

The product has been developed in accordance with European legislation and delivers a VOC of below 420g/l.

When used in conjunction with the relevant Nexa Autocolor compliant Clearcoat, this waterborne system delivers excellent gloss, appearance and durability.



**Nexa Autocolor** and Turbo Plus are trademarks of PPG Industries. © 2006 PPG Industries, all rights reserved. Copyright in the above product numbers that are original is asserted by PPG Industries.

Innovating Repair Solutions

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

		PROCESS		
		Standard	Large Area	
	Ready-Mix P935-3006 Thinner	3 parts by volume 1 part by volume 0-30% by volume Notes: Shake 3006 before use Activate shortly before use	6 parts by volume 1 part by volume 0-30% by volume	
	22-26 secs DIN 4 cup (at 20°C).			
Ųs	Viscosity may be adjusted by addition of P980-5000 or 5050 thinner			
	Pot-life at 20°C	Activated – 48 Hours Unactiv	rated – 28 Days	
	Compliant HVLP			
	Gravity -: 1.4 mm Suction -: 1.8-2.0mm Pressure -: 1.0-1.2mm Fluid delivery 280-320 cc/min			
Air Cap Pressure 0.675 Bar ( 10 psi. ) max				
	Clean the gun using water in a suitable gun-cleaning machine. For gravity feed guns unscrew the paint cup (and filter if fitted) and rinse separately. Rinse gun through with clean water. Finally spray through with clean Aquabase Plus thinner P980-5000 and ensure that the gun is fully dry before storing or further use.			
	2-3 single coats plus 1 control coat for metallics and micas.			
<b>⟩</b> <sub>↑</sub> ⟩ <sub>↑</sub> ⟩	Flash off between coats (20°C / 60% Humidity) -: 20-30 mins. or until uniformly dry.			
	DRYING TIME CAN BE GREATLY REDUCED WITH THE USE OF AIRBLOWERS AND / OR FORCE DRY			
	Wait until uniformly dry before clearcoating. For multi-striping work, it's recommended to force dry prior to masking up.			
		Metal Temperature -: 45°C - 30 mins	60°C - 20 mins	
	If necessary, may be hand denibbed with P1200 wet/dry paper. Ensure basecoat is fully dry and apply minimum pressure whilst denibbing. Recoat times (20°C)-: Minimum - 20 mins Maximum – 72 hours ( after which 1 coat of basecoat has to be applied prior to clearcoating )			
Clearcoat	to relevant PDS for d	ts may be overcoated with Autocolor clear etails. ts can be overcoated up to 48 hours after		
	For optimum final ap	pearance tack the basecoat prior to clearc	oating.	

Nexa Autocolor and Turbo Plus are trademarks of PPG Industries.

© 2006 PPG Industries, all rights reserved. Copyright in the above product numbers that are original is asserted by PPG Industries.

**Innovating Repair Solutions** 

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

## **General Process Notes**

#### SUBSTRATES AND PREPARATION

Clean all surfaces with **P980-6050**. Wet flat with P800 or finer, dry machine sand with P360 or finer. Wash off residues and dry thoroughly before re-cleaning with **P980-6050** using one rag for application and another rag for wiping off. The use of a Tack rag is strongly recommended as a final stage.

Apply over the following Nexa Autocolor primer systems-:

P980-6501/2 - Waterborne Epoxies P580-2920 - High Build Epoxy P580-350X - Chromate Free Epoxies P565-1027/8 - 2K Primer Surfacer P565-755 - Transparent Sealer

Ensure all primers are used as per the relevant TDS.

Nexa Autocolor Commercial Transport Waterborne Basecoat should never be used over -:

Wash Primers Etch Primers Chromated Epoxy Primers Acrylic Thermoplastic Finishes

#### **STORAGE AND HANDLING**

Nexa Autocolor Commercial Transport Waterborne Basecoat mixed colours, activator, thinners and cleaner should be stored in a cool, dry place away from sources of heat. During storage and transportation, temperatures must be maintained at a minimum of +5C and a maximum of +35C.

Waterborne Basecoat should always be mixed in clean, dry containers and used in clean, dry equipment. Do not use in mixing vessels or spray equipment that contain solvent residues. Mixing vessels should ideally be plastic; If metallic they should have an anti-corrosion lining

#### PERFORMANCE AND LIMITS

Dry film build should be between 15 and 25 microns.

#### **EQUIPMENT CLEANING**

After use, clean all equipment thoroughly using a dedicated waterborne cleaner or cleaning equipment. Ensure all equipment is clean and dry before storage or use.



**Nexa Autocolor** and Turbo Plus are trademarks of PPG Industries. © 2006 PPG Industries, all rights reserved. Copyright in the above product numbers that are original is asserted by PPG Industries.

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

#### **CT Waterborne Basecoat**

These products are for professional use only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose.

For Heath and Safety information please refer to the material Safety Data Sheet, also available at: http://www.ppg.com/Autocolor\_MSDS

#### **VOC INFORMATION**

The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420g/litre of VOC. The VOC content of this product in ready to use form is max. 420g/litre. Depending on the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.

#### For further information please contact:

Customer Service Sales Group PPG Industries (UK) Ltd Needham Road Stowmarket Suffolk IP14 2AD

Tel: 01449 771771 Fax: 01449 773472



**Nexa Autocolor** and Turbo Plus are trademarks of PPG Industries. © 2006 PPG Industries, all rights reserved. Copyright in the above product numbers that are original is asserted by PPG Industries.

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.

Innovating Repair Solutions