

ADDITIVE 1200

1.975.1200

ADHESION PROMOTER

Additive 1200 is a ready-to-spray adhesion promoter for use in spot repair operations in the metallic two-stage system.

Additive 1200 provides a good foundation for colour blending and is applied in the area of the spot repair.

Additive 1200 will successfully fill minor preparation scratches and faults and help to reduce dust from surface.

SUBSTRATES

All fillers in MaxMeyer Car Refinish range, sanded.
Old finishes in sound condition, sanded with P320-400 or Scotch Brite Fine.

PREPARATION OF SUBSTRATE

Prime damaged area with a MaxMeyer Car Refinish range 2K undercoat.
Sand with Scotch Brite Fine. Clean with antsilicone Degreaser 3600 and tack rag.
Apply a coat of Additive 1200 on to the primed area and slightly beyond, so that the spray mist of the topcoat will cover the Additive 1200 treated area.
Allow 5-10 minutes flash off, than apply Maxicar HS, without extending beyond the Additive 1200 treated area.
Allow 30 minutes flash off before clearcoating.
Thinner 5405 is strongly recommended.

CLEAR

HS Clear 0200, MS Clear 0440, HS Clear 420, Clear 0500, UHS Clear 0260, HP Clear, UHS Clear 0330.

TECHNICAL DATA

Pack size 1 l
Storage store in a cool dry place away from heat

SAFETY AND HANDLING

These products are for professional use only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose.

For Health and Safety information, please refer to the material Safety Data Sheet, also available at :

http://www.ppg.com/Maxmeyer_MSDS

For further information please contact:
PPG Industries (UK) Limited.

MaxMeyer Division
Customer Service & Sales Group,
Needham Road,
Stowmarket,
Suffolk.
IP14 2AD,
England.
Tel: 01449 771779
Fax: 01449 773495

