




TEXTURE ADDITIVES 1.975.5500/5501

FINE TEXTURE (1.975.5500) - COARSE TEXTURE (1.975.5501)



Texture additives provide a low gloss textured effect when mixed with UHS Duralit Extra and other HS Low VOC Clears.

MIXING RATIO BY VOLUME



| UHS DURALIT EXTRA OR 1.360.0330 | Topcoat | 5500 Fine Additive | 5501 Coarse Additive | HS Hardener | Additive Thinner |
|------------------------------------|---------|-----------------------|----------------------------|----------------|---------------------|
| Fine Texture | 2 | 3 | | 1 | 2 |
| Coarse Texture | 2 | | 1.5 | 1 | 2 |

For use of 5500/1 in other Low VOC Clears refer to technical data sheet of relevant product.

USE



Apply with gravity fed gun (1.6-1.8 mm nozzle).
See also technical data sheet for relevant product.

For two-stage finishes, texture additives may be added to either basecoat or topcoat.
Do not add texture additives to both of them.

Texture additive reduces opacity and slightly changes colour.



TEXTURE ADDITIVES 1.975.5500/5501

TECHNICAL DATA

Pack size 1 Ltr
Storage Store in a cool dry place away from heat



VOC INFORMATION

The EU limit value for this product (product category: IIB.e) in ready to use form is 840 g/litre of VOC. The VOC content of this product in ready to use form is max. 840g/litre. Depending upon the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.

SAFETY AND HANDLING

These products are for professional use only and are not to be used for purposes other than those specified.

The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose.

For Health and Safety information, please refer to the material Safety Data Sheet, also available at: www.maxmeyer.com



For further information please contact:

PPG Industries (UK) Limited. MaxMeyer Division Customer Service & Sales Group, Needham Road, Stowmarket, Suffolk. IP14 2AD, England. Tel: 01449 771779 Fax: 01449 773495

MaxMeyer and the MaxMeyer logo are trademarks of PPG industries.

© 2011 PPG Industries. All rights reserved.