

Product Information



DELFLLEET F4900 / F4901

PRODUCT



Delfleet Chromate Free HS Epoxy White	F4900
Delfleet Chromate Free HS Epoxy Grey	F4901
Hardener for HS C.F. Epoxy Primer	F3297
Thinner for HS C.F. Epoxy Primer	F3391
Thinner for HS C.F. Epoxy Primer - Slow	F3392

PRODUCT DESCRIPTION

Delfleet Chromated Free High Solids Epoxy Primer is a versatile product which complies to current European VOC legislation of less than 540 g/l.

The primer is extremely versatile , is intended for use over a wide range of suitably prepared substrates and can be used as a sanding or a non-sand primer ; In non-sand mode it can be baked , air-dried or used as part of a wet-on-wet system.









SUBSTRATE PRE-TREATMENT

	<p>Prepare the substrate as follows:</p> <p>New hot / cold rolled steel / old steel</p> <p>Old steel</p>	<p>SAND</p> <p>Shot Blast</p> <p>P180-240 Dry</p>	<p>CLEANING</p> <p>The substrate to be painted must be dry, clean, and free of corrosion, grease & mould release agents.</p> <p>Substrates need to be thoroughly prepared using a combination of D845 Degreaser & D837 Spirit Wipe (or D8401 WB cleaner)</p>
	<p>Zintec Galvanised Steel Sound paint finishes Electropaint GRP</p>	<p>P180-240 Dry P240-320 Dry P180-240 Dry P120-320 Dry P320-P400 Dry.</p>	

Delfleet Epoxy primers are not recommended for use over Etch primers or thermoplastic substrates.



PREPARATION AND APPLICATION

	Ensure thorough mixing of product prior to application	HVLP / Pressure By volume		Airless / Airmix By volume	
		F4900/F4901	4	F4900/F4901	4
		F3297	1	F3297	1
		Stir Thoroughly before adding:-			
		F3391/2	0.5 – 1.5		
Potlife at 20°C -: 3 - 4 Hours					
	Viscosity:	HVLP	PRESSURE	AIRLESS / AIRMIX	
		25-35 sec.	25-35 sec.	50-55 sec. DIN4/20°C	
		DIN4/20°C	DIN4/20°C		
Drying time: 	20°C Dust free: 20°C Through dry 60°C Bake (metal temp.)	HVLP	PRESSURE	AIRLESS / AIRMIX	
		10 - 15 minutes	10 - 15 minutes	20 minutes	
		8 – 10 hours	8 – 10 hours	8 – 10 hours	
		45 – 60 minutes	45 – 60 minutes	45 – 60 minutes	
Theoretical coverage assuming 100% transfer efficiency at film builds indicated.					
	Flattening not necessary - If necessary P600-P800 or P320-P400				
	Overcoat with: Any Delfleet 2-pack topcoat system.				
	20°C Flash off: Between coats Before bake Before Recoat	10-15 minutes	10-15 minutes	20-30 minutes	
		15 -30 minutes	15 – 30 minutes	20 -30 minutes	
		60 minutes	60 minutes	60 minutes minimum,	
		minimum, 24 hours	minimum, 24	24 hours maximum	
		maximum	hours maximum		
	Gun set-up:	1.8 mm. 2 Bar Inlet	1.0 -1.2 mm. 2 Bar Inlet Fluid 380-420 cc/min	<u>Airless-</u> : 13-15 thou (0.33-0.37mm) at approx 140 bar <u>Airmix-</u> :11 – 15 thou (0.28-0.37mm) at approx 70 bar	
Dry film thickness:	Minimum Maximum Theoretical coverage:	80µm	80µm	80µm 100µm	
		At 4:1:1 4 – 5 m ² /l	At 4:1:1 4 – 5 m ² /l	At 4:1 – 6.5 m ² /l	
	Number of coats:	2	2	1 - 2	



PERFORMANCE AND LIMITATIONS

This product should not be used at a temperature lower than 15°C or a humidity higher than 80%.

The drying times quoted above are approximate times and will vary depending upon drying conditions and film thickness. Poor ventilation and excessive film thickness will extend drying times. Overnight temperatures above 15°C are essential for the primer to completely cure.

Recoating: Drying times will depend upon film thickness and drying conditions. In common with other primers, longer drying times before recoat will improve final appearance. May be recoated with PPG Commercial transport 2K primers or directly with PPG Commercial transport 2K topcoats. If overcoated with CT waterborne basecoat, it is important that F4900 / F4901 are fully baked or allowed to dry for at least 10 hours at 20°C.

Drying of this primer at temperatures below 15°C may be accelerated by adding 3% by weight of F384 Epoxy Accelerator.

This Epoxy primer can be used with plural mix application equipment using the 4:1 mixing ratio with F3297 hardener.

EQUIPMENT CLEANING

After use clean all equipment thoroughly with cleaning solvent or thinner.

TECHNICAL DATA

Solid Content by weight	72%
Solid Content by volume	52%
Density	1.5 g/litre

VOC INFORMATION

The EU limit for this product (product category:IIB.c) in ready for use form is max. 540g/l of VOC.

The VOC content of this product in ready for use form is max. 540 g/l. Depending on the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.

HEALTH AND SAFETY

These products are for professional use only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the material Safety Data Sheet, also available at: http://www.ppg.com/PPG_MSDS

PPG Industries (UK) Limited.
Auto Refinish
Customer Service and Sales Group,
Needham Road,
Stowmarket,
Suffolk.
IP14 2AD,
England.
Tel: 01449 771775
Fax: 01449 773480

