



GLOBAL REFINISH
SYSTEM



June 2014

Product Information



GRS DELTRON® UHS Rapid Clearcoat D8135

D8135 UHS Rapid Clearcoat

PRODUCTS

<i>Deltron</i> UHS Rapid Clearcoat	D8135
<i>Deltron</i> UHS Hardener	D8217, D8218
<i>Deltron</i> Thinners	D807, D812, D8717, D8718, D8719
<i>Deltron</i> Accelerated Thinner	D8714

For textured finishes:

<i>Deltron</i> Texture Additive	D843	to create a fine textured 'suede' effect
<i>Deltron</i> Leather Grain Additive	D844	to create a coarser, more pronounced textured finish

PRODUCT DESCRIPTION

Deltron UHS Rapid Clearcoat is a 2K acrylic urethane clearcoat for fast small repairs of vehicles originally finished with clearcoat over a single or multistage colour basecoat system. This Clearcoat is flexible enough to be used over rigid plastic components.

D8135 is designed for use over ENVIROBASE® High Performance basecoat colour. It may be used in 2 different modes, "One' visit application" or standard 2 coat application. This clearcoat is recommended for a maximum of 3 panels.

D8135 comes with a standard 15 minute bake option at 60°C for use on between 1 and 3 panels. There is also a rapid 10 minute bake option at 60°C for single panel / spot repair and a 30 minute bake option at 60°C, for larger repairs up to an application temperature of 25°C. For optimum final appearance the 15 or 30 minute options are recommended depending on the type of repair.

These products are for professional use only.

RLD212V
Page 1 of 6

PREPARATION OF SUBSTRATE

Deltron D8135 Clear must be applied on top of a clean and dust-free Envirobase basecoat.
The use of a tack rag is recommended.

MIXING RATIO

Mixing ratios with UHS Hardener D8217/8218:

	<u>By Volume</u>	<u>By Weight</u>
D8135	3 vol	See table, Page 4/5
UHS Hardener	1 vol	
Thinner*	0.6 vol	

*Choose Thinner according to application temperature, D8714 Accelerated Thinner is not recommended in combination with D8218 UHS Hardener.

As with all ultra high solids products, cold ready for use paint temperatures can lead to more difficult application and overspray absorption. It is strongly recommended that ready for use product is applied at a temperature greater than 15°C

HARDENER AND THINNER SELECTION

<u>Application Temperature</u>	<u>UHS Hardener</u>	<u>Thinner</u>	<u>Bake Schedule</u>
Below 25°C	D8217	D8714	10 minutes @60°C
Below 25°C	D8217	D807/D8717	15 minutes @ 60°C
Above 25°C	D8217	D812/D8719	15 minutes @ 60°C
Below 25°C	D8218	D807/D812/D8717/18/19*	30 minutes @ 60°C
Above 25°C	D8218	D812/D8718/19	30 minutes @ 60°C

*The choice of hardener and thinner should be made according to application temperature, air movement, size of repair, and the speed of Bake required.

MIXED PRODUCT DETAILS

Pot-life at 20°C: 20 - 30 minutes with D8217 / D8714
 30 - 40 minutes with D8217 / D807, D812, D8717/18/19
 40 - 50 minutes with D8218 / D807, D812, D8717/18/19

Spray viscosity at 20°C 18 - 20 seconds DIN4.

APPLICATION AND FLASH-OFF



Spraygun set-up:
Express Single Visit Process
Application

1.2 - 1.4 mm

Apply 1 medium & 1 full coat to give 50-60 microns dry film build. The first coat should be applied to all repair panels before the second coat is applied.

Flash off between spray coats

For 1 panel, 2-3 minutes flash off.

Flash off before bake or IR dry

For 2 to 3 panels, no flash off is required.

0 – 5 minutes

Conventional Two Coat Process
Application

Apply 2 single coats to give ~60 microns dry film build.

Flash off between spray coats

5 – 7 minutes

Flash off before bake or IR dry

0 – 5 minutes

These products are for professional use only.

RLD212V
Page 2 of 6



DRYING TIMES

- Dust free time at 20°C	20 - 30 minutes with D8217 30 - 40 minutes with D8218
- Dry to handle at 20°C	4 hours with D8217 6 hours with D8218
- Through dry at 20°C	12 hours with D8217 16 hours with D8218
- Through dry at 50°C*	20 minutes with D8217 40 minutes with D8218
- Through dry at 60°C*	10 minutes with D8217/D8714 15 minutes with D8217/D807, D812, D8717/18/19 30 minutes with D8218/D807, D812, D8717/18/19
- Through dry at IR (medium wave)	8 - 15 minutes (depending upon colour and equipment)



*Bake times are for quoted metal temperature. Additional time should be allowed in the bake schedule to allow metal to reach recommended temperature.

USE OF D8216 *Deltron* UHS Hardener

This Hardener can be used following the mixing recommendations above, in combination with D8714 Accelerated Thinner, but is only suitable for use below 25°C and on small areas such as small vertical panels or components where a high gloss finish is not required.

Pot Life is 15 minutes so this combination must be applied immediately after mixing and equipment must be cleaned as soon as application is finished.

Use on larger areas may lead to popping caused by the very fast cure rate.

This combination may be baked at 60°C for 10 minutes or air dried for 12 hours.

Total dry film build: 45 – 60 µm

Theoretical coverage: Assuming 100% transfer efficiency and dry film thickness as indicated: 8 m²/l

REPAIR AND RECOATING




Sanding: Essential before recoating to ensure good adhesion

- *grade wet* P800
- *grade dry* P400 - P500

Overcoat / Re-coat time:

- *Force dry at 60°C, or IR* After cooling



Overcoat with: PPG 2K Primers, *Envirobase* High Performance, *Deltron* GRS Topcoats



TEXTURED FINISHES (using D807/D812 Thinners)

To obtain a textured finish with *Deltron* D8135 UHS Rapid Clear it is necessary to include texture additives in the mix.

The additives required and the appropriate weight mix ratios are indicated in microfiches if relevant or in the tables below.

Weights in the following table are cumulative. Do not tare the balance between additions.

Substrate	Appearance	CUMULATIVE WEIGHT MIX GUIDE					
		Volume of RFU Paint (litres)	Weight D8135	Weight D843	Weight D844	Weight D8217 /D8218	Weight D807 /D812
Rigid	Gloss	1,0 L	638g	-	-	870g	984g
	Matt Textured	1,0 L	284g	639g	-	743g	957g
	Leather Grain	1,0 L	392g	-	708g	850g	967g

WEIGHT MIX TABLE FOR D8135 (using D807/D812 Thinners)

Target Volume of RFU Paint required (Litres)	Weight Clearcoat D8135	Weight UHS Hardener D8217/D8218	Weight Thinner D807/D812
0.10 L	64 g	87 g	98 g
0.20 L	128 g	174 g	197 g
0.25 L	160 g	218 g	245 g
0.33 L	213 g	291 g	326 g
0.50 L	319 g	435 g	492 g
0.75 L	478 g	653 g	738 g
1.00 L	638 g	870 g	984 g
1.50 L	958 g	1305 g	1476 g
2.00 L	1277 g	1740 g	1968 g
2.50 L	1596 g	2174 g	2460 g



TEXTURED FINISHES (using D8714 / D8717/18/19 Thinners)

To obtain a textured finish with *Deltron* D8135 UHS Rapid Clear it is necessary to include texture additives in the mix.

The additives required and the appropriate weight mix ratios are indicated in microfiches if relevant or in the tables below.

Weights in the following table are cumulative. Do not tare the balance between additions.

Substrate	Appearance	CUMULATIVE WEIGHT MIX GUIDE					
		Volume of RFU Paint (litres)	Weight D8135	Weight D843	Weight D844	Weight D8217 /D8218	Weight D8714/ D8717/18 /19
Rigid	Gloss	1,0 L	645g	-	-	875g	982g
	Matt Textured	1,0 L	287g	641g	-	745g	946g
	Leather Grain	1,0 L	392g	-	708g	850g	960g

WEIGHT MIX TABLE FOR D8135 (using D8714 / D8717/18/19 Thinners)

Target Volume of RFU Paint required (Litres)	Weight Clearcoat D8135	Weight UHS Hardener D8217/D8218	Weight Thinner D8714/D8717/18/19
0.10 L	65g	88g	98g
0.20 L	129g	175g	196g
0.25 L	161g	219g	245g
0.33 L	213g	289g	324g
0.50 L	323g	438g	491g
0.75 L	484g	656g	736g
1.00 L	645g	875g	982g
1.50 L	968g	1312g	1473g
2.00 L	1291g	1750g	1964g
2.50 L	1613g	2187g	2454g

****Note:** D8714 *Deltron* Accelerated Thinner is not recommended in combination with D8218 UHS Hardener.



POLISHING



If polishing is required, i.e. to remove dirt nibs, it is recommended that it is carried out 1 hour after baking.
Use PPG Specialty Polishing system SPP1001.

FADE - OUT REPAIR PROCEDURE

- Apply D8135 UHS Rapid Clear according to the information above
- Take care to minimise the clearcoat edge in the fade-out area
- Melt overspray edge using D8731 Aerosol Fade-Out Thinner or D8430 Rapid Blender.
- Refer to datasheet No: RLD 299V for successful repair.

EQUIPMENT CLEANING

After use, clean all equipment thoroughly with cleaning solvent or thinner.

VOC INFORMATION

The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420g/litre of VOC. The VOC content of this product in ready to use form is max. 420g/litre.
Depending on the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.

Note:

Combinations of this product with D843 or D844 will produce a paint film with special properties as defined by the EU Directive code. The EU limit for these combinations in ready for use form is 840g/litre of VOC. The VOC content of this product in these combinations is max 840g/L.

HEALTH AND SAFETY

These products are for professional use only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the material Safety Data Sheet, also available at: www.ppgrefinish.com

PPG Industries (UK) Limited.
Auto Refinish
Customer Service and Sales Group,
Needham Road,
Stowmarket,
Suffolk.
IP14 2AD,
England.
Tel: 01449 771775
Fax: 01449 773480

DELTRON® and ENVIROBASE® are registered marks of PPG Industries Ohio, Inc.
Copyright © 2014 PPG Industries Ohio, Inc. All rights reserved.
Copyright in the above product numbers that are original is asserted by PPG Industries Ohio, Inc..

