

Product Information



DELFLLEET F3994

PRODUCT

Delfleet Chromate HS Epoxy	F3994
Delfleet Epoxy Hardener	F3296
Delfleet Epoxy Thinner	F3342



PRODUCT DRSCRIPTION

Delfleet Chromated High Solids Epoxy Primer is a versatile product that complies with the current European VOC legislation of less than 540 g/l.

The primer utilises chromate based anti-corrosive pigments to deliver exceptional corrosion resistance. It is a non-sand prmer that can be baked , air-dried or used as part of a wet-on-wet system.

It is intended for use over a wide range of suitably prepared substrates.









SUBSTRATE PRE-TREATMENT

	<p>Prepare the substrate as follows:</p> <p>New hot / cold rolled steel / old steel</p> <p>Old steel</p> <p>Aluminium</p>	<p>SAND</p> <p>Shot Blast</p> <p>P180-240 Dry</p> <p>P240 dry or Scotchbrite - Not recommended over jointed aluminium sections. Please, seek advice from your local PPG representative</p>	<p>CLEANING</p> <p>The substrate to be painted must be dry, clean, free of corrosion, grease & mould release agents.</p> <p>Substrates need to be thoroughly prepared using a combination of D845 Degreaser & D837 Spirit Wipe (or D842 low V.O.C. cleaner)</p>
	<p>Zintec</p> <p>Galvanised Steel</p> <p>Sound paint finishes</p> <p>Electropaint</p> <p>GRP</p>	<p>P180-240 Dry</p> <p>P240-320 Dry</p> <p>P180-240 Dry</p> <p>P120-320 Dry</p> <p>P320-P400 Dry.</p>	

Delfleet Epoxy primers are not recommended for use over Etch primers or thermoplastic substrates.



PREPARATION AND APPLICATION

	Ensure thorough mixing of product prior to application	HVLP / Pressure By volume F3994 4 F3296 1 F3342 1	Airless / Airmix By volume F3994 4 F3296 1	
Potlife at 20°C -: .4-6 Hours				
	Viscosity:	HVLP 18-22 sec. DIN4/20°C	PRESSURE 18-22 sec. DIN4/20°C	AIRLESS / AIRMIX 71-85 sec. DIN4/20°C
	Gun set-up:	1.4-1.8 mm. 2 Bar Inlet	1.0 -1.2 mm. 2 Bar Inlet Fluid 380-420 cc/min	13-15 thou (0.33-0.37mm) <u>Airless</u> :- 2000 psi <u>Airmix</u> :- 1000psi 20-25 psi Air Cap
	Number of coats:	2	2	1-2
	20°C Flash off: Between coats Before bake Before Recoat	10-15 mins. 15 -20 mins. 40 - 50 mins.	10-15 mins. 15 – 20 mins. 40 - 50 mins.	20-30 mins. 20 -30 mins. 60 mins.
Drying time: 	20°C Dust free: 20°C Through dry 60°C Bake (metal temp.)	HVLP 15-25 mins. Overnight 1 Hour	PRESSURE 15-25 mins. Overnight 1 Hour	AIRLESS / AIRMIX 30-60 mins. Overnight 1 Hour
Dry film thickness:	Minimum Maximum Theoretical coverage:	50µm 75µm 8m ² /l	50µm 75µm 8m ² /l	75µm 100µm 5 m ² /l
Theoretical coverage assuming 100% transfer efficiency at film builds indicated.				
	NOT RECOMMENDED			
	Overcoat with: Any Delfleet topcoat system.			



PERFORMANCE AND LIMITATIONS

This product should not be used at a temperature lower than 10°C or a humidity higher than 80%.

EQUIPMENT CLEANING

After use clean all equipment thoroughly with cleaning solvent or thinner.

The EU limit for this product (product category: IIB.c) in ready for use form is max. 540g/l of VOC.

The VOC content of this product in ready for use form is max. 540 g/l. Depending on the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.

HEALTH AND SAFETY

These products are for professional use only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the material Safety Data Sheet, also available at: http://www.ppg.com/PPG_MSDS

PPG Industries (UK) Limited.
Auto Refinish
Customer Service and Sales Group,
Needham Road,
Stowmarket,
Suffolk.
IP14 2AD,
England.
Tel: 01449 771775
Fax: 01449 773480

