



Technical Data Sheet

RLD580

August 2020

International Master - for professional use only

Product List

DELFLEET ONE® MS Performance Topcoat	
Product	Description
F8080	MS Performance Binder
F7xxx	Coloured Tinters
F8286	MS Hardener - Medium
F8284	MS Hardener - Slow
F8374	MS Thinner - Slow
F8375	MS Thinner - Medium
F8376	MS Thinner - Fast

Product Description


DELFLEET ONE® MS Performance Topcoat is a 2-pack polyurethan topcoat formulated to get an optimal selection of colours and reproductibility when tinted with the latest generation of DELFLEET® tinters. It will provide good quality finish to Commercial Vehicles.

Delfleet One MS Performance Topcoat is an easy to spray topcoat providing good opacity, gloss and general appearance which meets the standards demanded for Commercial Transportation Vehicles.

Delfleet One MS Performance Topcoat can be combined with a flexible offer of ancillaries to meet the needs of both Builders and Repairers in different application conditions.

Substrates and Preparation

PREPARE THE SUBSTRATE AS FOLLOWS:



Substrates:

- Original finishes and work in sound condition need to be degreased, cleaned and dry sanded with P320-P400 (or P600 wet) prior to topcoat application.
- Steel, Aluminum, GRP & Zinc coated steel need to be pre-primed with the appropriate primer in order to ensure correct intercoat adhesion and substrate protection.
- DELFLEET ONE® MS Performance Topcoat is suitable over all PPG primers, surfacers and sealers.




Cleaning:

The substrate to be painted must be dry, clean, free of corrosion, grease & mould release agents.

Substrates need to be thoroughly prepared using a combination of D845 Degreaser & D837 Spirit Wipe (or D8401 low V.O.C cleaner).

Process

CONVENTIONAL, PRESSURE POT OR AIR ASSISTED AIRLESS APPLICATION




Mixing Ratio by Volume:

DELFLLEET ONE® MS Performance Topcoat	2
F828x MS hardener	1
F837x MS thinner	0.5-1

Recommended combinations:


Temperature	<18°C	18-25°C	>25°C
Combination	Medium/Fast	Medium/Medium	Slow/Slow
Ancillaries	F8286/F8376	F8286/F8375	F8284/F8374




Potlife at 20°C: 2 Hours

Application Process

CONVENTIONAL, PRESSURE POT OR AIR ASSISTED AIRLESS APPLICATION



Spray Viscosity at 20°C:
 18-22 seconds DIN4 for Conventional/Pressure Pot application
 19-23 seconds DIN4 for Air Assisted Airless application




1,3-1,5 mm Gravity or suction feed at 2.0-2,4 bars

OR




0,8-1mm Pressure Pot
 Air Cap Pressure: 0.68 bar
 Paint Pressure: 0.3-1.0 bar
 Fluid flow rate: 280-320 cc/min

OR




Tip Size: 9 to 11 Thou (0,23 to 0,28 mm) for Air Assisted Airless
 Paint Pressure: 90-110 bars
 Air Atomization: 2,5-3 bars




Number of Coats
 2 coats:
 1 Medium closed
 + 1 Full coat

Dry Film Thickness: 40 – 60 µm



2 coats:

Flash-Off between coats: 10-15 minutes
 Flash-Off before bake: 15-20 minutes



Drying Time:	HVLP/Pressure Pot	Air Assisted Airless
20°C Dust free:	10-20 min.	20-30 min.
20°C Through dry	24 hours	24 hours
60°C Bake (metal temp.)	30 min.	40-50 min.
IR Medium Wave	10-15 min.	N/A



Colour

COLOUR MIXING

All tinters should be thoroughly hand stirred when first opened, and then stirred on a mixing machine for 10 minutes before use. Thereafter all tinters should be machine stirred twice a day for at least 10 minutes.

COLOUR CHECKING

As with all refinish paint systems, a colour check should be carried out before painting the vehicle.

General Process Notes

RECOAT

DELFLLEET ONE® Performance Topcoat can be recoated by itself within 24 hours without sanding.

DECAL APPLICATION

It is recommended that DELFLLEET ONE® Performance Topcoat is allowed to cure for at least one week prior to any decal application.

COVERAGE

Approximately 8 to 10m² (to be calculated accurately) per litre of ready for use paint at a dry film thickness of 50 microns depending on thinning ratio used.

OTHER POINTS TO NOTE

Allow finishes to harden thoroughly before subjecting to vehicle washes. This can take a number of weeks if vehicles are air-dried in cold conditions and/or paint film thickness is excessively high.

STORAGE

Mixing Room Temperature:

Store F7xxx Toners in the Mixing Room between the following temperatures: 18 to 25°C.

Storage Temperature:

Store F7xxx Toners between the following temperatures: 5 to 35°C (41 to 95°F).

Store in accordance with local regulations. Store in original container protected from direct sunlight in a dry, cool and well-ventilated area, away from incompatible materials and food and drink. Keep container tightly closed and sealed until ready for use.

Containers that have been opened must be carefully resealed and kept upright to prevent leakage.

Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.

Always refer to the material Safety Data Sheet.



DELFLLEET
ONE®



HEALTH AND SAFETY

These products are for professional use only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the material Safety Data Sheet, also available at: www.ppgrefinish.com

For further information please contact:

Customer Service Sales Group
PPG Industries (UK) Ltd
Needham Road
Stowmarket
Suffolk IP14 2AD
Tel: 01449 771771
Fax: 01449 773472

The PPG Logo, *Delfleet*, *Delfleet One* and *PaintManager* are registered trademarks and *RapidMatch* is a trademark of PPG Industries Ohio, Inc.
© 2018 PPG Industries, all rights reserved. Copyright in the above product numbers that are original is asserted by PPG Industries.

THESE PRODUCTS ARE FOR PROFESSIONAL USE ONLY.