

## Product Information

### DELFLLEET Wet on Wet Surfacer F4942



#### PRODUCT

Delfleet Wet on Wet Surfacer	F4942
MS Hardener - Slow	F8284
MS Hardener - Medium	F8286
MS Thinner - Slow	F8374
MS Thinner - Medium	F8375
MS Thinner - Fast	F8376









#### PRODUCT DESCRIPTION

Delfleet Wet on Wet Surfacer is a fast drying isocyanate cured Acrylic primer, with excellent adhesion to a variety of substrates and very good gloss holdout under 2K topcoats.

#### SUBSTRATE PRE-TREATMENT

	<p>Thoroughly cleaned and where appropriate sanded, works primers and OE finishes, Delfleet Wash Primers, 2 pack primers and GRP.</p>	<p><b>SAND</b></p> <p>P280 - 320 Dry</p>	<p><b>CLEANING</b></p> <p>The substrate to be painted must be dry, clean, free of corrosion, grease &amp; mould release agents.</p>
	<p>Notes: Do not apply over areas of bare metal when used in refurbishment work. Do not apply over Alkyd paint finishes.</p>		<p>Substrates need to be thoroughly prepared using a combination of D845 Degreaser &amp; D837 Spirit Wipe (or D8401 low VOC cleaner)</p>

# PREPARATION AND APPLICATION

		<b>HVLP / Pressure</b>	
		<p style="text-align: right;">F4942 Surfacer      4 F828x Hardener      1 F837x Thinner        2</p>	
<p style="text-align: center;"><b>Potlife at 20°C -: 1Hour</b></p>		<p style="text-align: center;">Use F8376 at temperatures below 18°C</p>	
	<p><b>Viscosity:</b></p>	<p style="text-align: center;">15-17 sec. DIN4/20°C</p>	
	<p><b>Gun set-up:</b></p>	<p>Compliant Spraygun 1.2 – 1.4 mm 2 bar pressure</p>	<p>Pressure fed Spraygun – 1.0 – 1.1 mm Paint pressure    0.3 – 1.0 bar Air Cap pressure – 0.67 bar Max  Note: if long fluid lines are used then the pressure will need to be increased.</p>
	<p><b>Number of coats:</b></p>	<p style="text-align: center;">1 or 2 coats depending upon build required</p>	
	<p><b>20°C Flash off:</b> <b>Between coats</b> <b>Before overcoating</b></p>	<p style="text-align: center;">10 - 15 minutes 30 minutes</p>	
<p><b>Drying time:</b></p> 	<p><b>20°C Dust free:</b> <b>20°C recoat</b> <b>60°C Bake</b> <b>(metal temp.)</b></p>	<p style="text-align: center;">10 - 20 mins. 30 minutes 30 mins</p>	
	<p>Normally this surfacer does not require sanding. If however some dirt inclusion occurs, light flattening / denibbing can be carried out when hard dry using P600 (wet or dry paper) or P320 / P360 dry sanding discs.</p>		
	<p>Normally F4942 can be left for up to 2 days without flattening prior to recoating. However, if left for longer than 2 days F4942 must be scuffed before overcoating.</p> <p><b>Overcoat with:</b> Any Delfleet MS Performance Topcoat, Waterborne Basecoat and Clear</p> <p style="text-align: center;">DO NOT overcoat with solventborne basecoats.</p>		

## TINTING

F4942 may be tinted with up to 5% Delfleet One tinter to the unactivated primer, and then activate and thin as per recommendations above for F4942. When used tinted, a 40 minute flash off time before overcoating is recommended.

## PAINTING PLASTIC

F4942 may be applied over prepared painted plastic. Prepare by thorough cleaning and scuffing. It may also be applied over primed plastic. If F4942 is applied over a flexible plastic, it must be mixed as detailed below :

<b>Flexible plastic</b>	
F4942	4 parts
Flex Additive F3437	1 part
MS Hardener	1.5 parts
Thinner	1.5 parts

NOTE: The addition of F3437 will extend the drying times.

## PERFORMANCE AND LIMITATIONS

Normally F4942 can be left for 48 hours without sanding prior to recoat. If left longer than 48 hours this surfacer must be sanded before topcoating.

Do Not use any other thinners than those quoted in this datasheet, as it may adversely affect the pot life.  
This surfacer is recommended for complete panels only and should not be used for spot repairs

When using F4942 over Etch primers, it is essential that the topcoat or basecoat is applied within the specified recoat time or if left longer, be recoated after 6 hours, otherwise film lifting may occur.

This product is recommended for whole panels only and should not be used for spot or partial repairs.

## EQUIPMENT CLEANING

After use clean all equipment thoroughly with cleaning solvent or thinner.

---

## HEALTH AND SAFETY

**These products are for professional use only**, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the material Safety Data Sheet, also available at: [http://www.ppg.com/PPG\\_MSDS](http://www.ppg.com/PPG_MSDS)