

PRODUCT DESCRIPTION

7-412 Epoxy Matt Topcoat is a 2-pack epoxy enamel which offers an extremely durable finish. It is recommended for the painting of industrial equipment and machinery, particularly those situated in an aggressive environment. It should not be used on exterior surfaces exposed to sunlight if a good level of colour stability is required.

SELECTION AND PREPARATION OF SUBSTRATES



Bare steel
7-413, 7-414 primers
Sandblasted steel

Sand
P80-120 -240 (dry)
see relevant primers data sheets

Degrease thoroughly prior to painting.

APPLICATION GUIDE



Mixing ratio (by weight):

	AIRLESS		CONVENTIONAL	
Topcoat	1000		Topcoat	1000
9-010 *	200		9-010 *	200
1-410 **	200-300		1-410 **	200-300

Mixing ratio (by volume):


	AIRLESS		CONVENTIONAL	
Topcoat	3.5		Topcoat	3.5
9-010 *	1		9-010 *	1
1-410 **	1 – 1.5		1-410 **	1 – 1.5

* 9-011 Fast Hardener can be used

* 9-011 Fast Hardener can be used

** For large areas use 1-400 Slow Thinner

** For large areas use 1-400 Slow Thinner



Pot life 20 °C:

6- 8 hours

6-8 hours



Spray viscosity:


18-22 secs Din 4 20 °C

18-22 secs Din 4 20 °C

Spray gun set up:

9 - 11

1.4-1.7 mm



Spray pressure:

120-140 bar

3-4 bar

Number of coats:

2

2


Flash off between coats:

15-20 minutes 20 °C

15-20 minutes 20 °C

APPLICATION GUIDE

Drying times at 20 °C



Dust free: 20-30 minutes

Handling: 6-8 hours

Through dry: 12-18 hours



Through dry at 60 °C: 1 hour

Total dry film build: 50 microns

Overcoat/recoat time with itself 3 hours mini and 24 hours maxi 20 °C
without flattening

TECHNICAL DATA

Theoretical coverage 6.0-6.8 m² / l ready to spray giving 50µm
dry film thickness

HEALTH AND SAFETY

Please refer to Material Safety Data Sheet for full health and safety details and storage regulations

This product is for professional use only.

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

Selemix System is a brand of PPG Group

Selemix Customer Service and Sales Group, Needham Road, Stowmarket, Suffolk, IP14 2AD, England, Tel: 01449 773993, Fax: 01449 771547