


APPLICATION GUIDE



Drying times at 20°C:

Dust free:

10-15 minutes

Handling:

4 -6 hours

Through dry:

10-12 hours



Through dry at 60°C:

45 minutes

Total dry film build:

50 - 70 microns

Overcoat/recoat time with itself

Min 16 hours, Max 24 hours at 20°C
Without sanding

TECHNICAL DATA

**Slow Direct Thinner*

1-470 can be used in high temperatures
(above 35°C) to improve flow and finish

Theoretical coverage

8.0 – 8.3 m² /l ready to spray giving 60µm
dry film thickness

Solid components in RFU:

Weight:

62.46

Volume:

49.27

Density binder tinted:

1.14

HEALTH AND SAFETY

Please refer to Material Safety Data Sheet for full health and safety details and storage regulations

This product is for professional use only.

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

Selemix System is a brand of PPG Group

**Selemix Customer Service and Sales Group, Needham Road, Stowmarket, Suffolk,
IP14 AD, England, Tel: 01449 773993, Fax: 01449 771547**