

TECHNICAL DATASHEET

Issue date:
March 2021

SELEMIX[®] 1K SYNTHETIC FAST DRY MATT TOPCOAT 7-611

PRODUCT DESCRIPTION

Selemix 7-611 1K Synthetic Fast Dry Matt Topcoat is a matt 1K synthetic alkyd finish for solid colours and single-layer metallic finishes. It can be combined with 7-610 Gloss Binder to give semi-gloss and semi-matt finishes.

It is compatible with *Selemix Fast Dry* primers, giving a durable paint system. It has a matt finish with good durability. Application can be by conventional or air-assisted airless spray. It is suitable for the coating of machinery, agricultural and construction equipment, and many other industrial painting applications where a matt finish is required.

PRODUCTS

7-611 *Selemix Synthetic Fast Dry Matt Topcoat*
 NPxx *Selemix NP Tinters*

Thinners:

1-610 Synthetic Thinner
 1-215 Nitrocellulose Thinner
 1-205 Aromatic Free Thinner

Hardener (optional):

9-510 PU Hardener

SUBSTRATES AND PREPARATION



Painted Surfaces
 Polyurethane or Polyester Fillers

Machine sand with P320-400 discs and degrease



Selemix 1K primers :
 7-810, 7-820, 3-080X, 5-8851

Refer to Primer TDS for recoat time

Steel (use a primer in corrosive environments)

Machine sand with P80-120 discs and degrease

Apply only on a clean and dry surface with a temperature above the dew point to avoid condensation. In confined spaces, provide adequate ventilation during application and drying.

MIXING

Thoroughly mix paint before activating and check colour before use

	Features	Conventional	Air-Assisted Airless
	By Weight: 7-611 Topcoat 1-610/1-215/1-205 Thinner	1000 250-350	1000 80-90
	By Volume: 7-611 Topcoat 1-610/1-215/1-205 Thinner	6 2 - 3 (35-40%)	10 1 (10%)
	Viscosity (at 20°C): Pot Life (at 20°C):	18-22 secs DIN4 Unlimited	High Viscosity Unlimited

APPLICATION

	Features	Conventional	Air-Assisted Airless
	Spraygun setup:	Nozzle: Gravity: 1.3-1.4mm Suction: 1.6-1.8mm Pressure feed: 0.85-1.2mm	Nozzle: 9-11 thou 0.23-0.28mm
	Air Pressure:	HVLP: 2 Bar Standard: 2-3 Bar	2.5 Bar
	Fluid Pressure:	N/A	100-120 Bar
	Number of coats:	2	2
	Flash-off between coats:	10-15 mins	10-15 mins
	Drying:	Air dry	Air dry
	Wet Film Thickness:	120 microns	120 microns
	Dry Film Thickness:	40-50 microns	40-50 microns

DRYING TIMES



at 20°C

Dust Free:	10-15 mins
Touch Free:	1-2 hours
Tape Free:	16 hours
Handleable:	4-5 hours
Hard Dry:	24-48 hours
Overcoating time:	Minimum: 6 days Maximum: 1 month by itself without sanding
	With addition of 10% 9-510 Hardener Minimum: 1 day Maximum: 3 days by itself without sanding
	Lower temperature or film thickness higher than 50µm will extend drying times

TECHNICAL DATA

Based on ready-for-use mixed paint including thinner:	
VOC (g/L):	531-636 g/L (depending on colour and dilution)
Solid content (weight):	39-57 %
Solid content (volume):	27-38 %
Solvent content (weight):	43-61 %
Specific gravity (Ready for use)	1.10-1.26 Kg/L
Theoretical coverage:	5.3-7.6 m ² /L at 50 microns DFT
Gloss:	Matt
Note on Paint Mixing:	When mixing colours, it is recommended that binders and toners are weighed out first and mixed well before the addition of driers

PRODUCT CODES AND DESCRIPTIONS

Selemix Code	Short Code	Product Description	Packsize	
1.776.1100/E3.6K	7-611	Synthetic Fast Dry Matt Topcoat	3.6	Kg
1.776.1100/E14.4K	7-611	Synthetic Fast Dry Matt Topcoat	14.4	Kg
1.911.5610/E5	1-610	Synthetic Thinner	5	Lt
1.921.3215/E5	1-215	Nitrocellulose Thinner	5	Lt
1.991.1205/E25	1-205	Aromatic-Free Thinner	25	Lt

HEALTH AND SAFETY

For comprehensive Health, Safety and Environmental advice, please refer to the relevant Material Safety Data Sheets and Product can labels.

THIS PRODUCT IS FOR PROFESSIONAL USE ONLY

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

FOR FURTHER INFORMATION PLEASE CONTACT:

Selemix Customer Service and Sales Group
Needham Road
Stowmarket, Suffolk
IP14 2AD, England
Tel: 01449 771771