



TECHNICAL DATASHEET

Issue date: July 2020

SELEMIX® ANTI-FOAM ADDITIVE 6-570

PRODUCT DESCRIPTION

Selemix 6-570 Anti-Foam Additive can be added to Selemix 2K Polyurethane or Acrylic Topcoats in order to help eliminate foaming. Foaming can result from high pressure spray application (airless or air-assisted airless spray), which can cause pinholes and a loss of gloss in the final finish.

PRODUCTS

6-570

Selemix Anti-Foam Additive

SUBSTRATES AND PREPARATION

Refer to the relevant Selemix Topcoat Technical Datasheet

MIXING



Features	Conventional Spray Or Air-Assisted Airless	
By Weight: Selemix 7-1XX / 7-5XX 2K Acrylic / 2K Polyurethane Topcoat	1000	
6-570 Anti-Foam Additive	2	





APPLICATION

Refer to the relevant Selemix Topcoat Technical Datasheet.

TECHNICAL DATA

Data for Additive as supplied:	
Specific Gravity: Solids Content:	0.81 1%
Solvent Content:	99%
VOC (g/L)	802g/L

PRODUCT CODES AND DESCRIPTIONS

Selemix Code	Short Code	Product Description	Packs	size
1.965.7000/E1	6-570	Selemix Anti-Foam Additive	1	Ltr

HEALTH AND SAFETY

For comprehensive Health, Safety and Environmental advice, please refer to the relevant Material Safety Data Sheets and Product can labels.

THIS PRODUCT IS FOR PROFESSIONAL USE ONLY

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

FOR FURTHER INFORMATION PLEASE CONTACT:

Selemix Customer Service and Sales Group Needham Road Stowmarket, Suffolk IP14 2AD, England Tel: 01449 771771

