



PPG Architectural Coatings

PERMANIZER™ Flat Exterior Acrylic Coating

**GENERAL DESCRIPTION**

PERMANIZER FLAT Exterior Acrylic Coating No. PP759 Series is a new resin technology, 100% acrylic exterior coating. PERMANIZER is a self priming, flat, high build coating with superior adhesion, durability and the longest lasting protection. It can be used for all types of new or previously painted commercial, institutional and residential exterior wood, masonry and select metal surfaces such as siding, trim, eaves, facias, shutters, fences, properly prepared brick, block, stucco and concrete surfaces, vinyl, primed metals and metal siding, vinyl siding and trim.

**RECOMMENDED USES**

- Wood siding, trim
- Manufactured siding
- Vinyl siding, trim
- Brick
- Concrete
- Concrete block (CMU)
- Stucco
- Fencing, shutters

**FEATURES / BENEFITS**

- Lifetime Warranty against peeling on residential homes
- 100% acrylic Superior weather resistance
- High build Thicker film for better protection
- Self-priming Eliminates need for separate primer
- Blocks tannins Prevents bleed through
- Superior adhesion Resists peeling
- Application to 35° Extends painting season
- Mildew and algae resistant\*

\*This paint contains agents which inhibit the growth of mildew on the surface of this paint.

**RECOMMENDED SYSTEMS**

PERMANIZER FLAT Exterior Acrylic Coating No. PP759 series can be applied to a wide variety of primed substrates. Finish the following primed surfaces with one coat of PERMANIZER FLAT Exterior Acrylic Coating No. PP759 series:

SUBSTRATE	TYPICAL PRIMERS*
<b>Aluminum Siding,</b>	
<b>Good condition:</b>	Self-prime, PP515
<b>Badly weathered:</b>	PP74130
<b>Masonry</b>	
<b>Brick:</b>	PP898, self-prime
<b>Concrete:</b>	PP6010, self prime
<b>Concrete Block (CMU):</b>	PP896
<b>Repaint:</b>	Self-prime, PP515
<b>Steel, Galvanized:</b>	Self -prime, PP215
<b>Stucco, Cement Plaster:</b>	PP6010, self-prime
<b>Vinyl Siding*:</b>	PP515, self-prime
<b>Wood:</b>	Self-prime, PP515

\*NOTE: Do not paint vinyl with colors darker than the original vinyl color.

**TINTING AND BASE INFORMATION**

Tint with Porter DESIGN SPECTRUM® Colorants per label directions.

- PP750 White/Pastel base
- PP759 Light base
- PP758 Deep base
- PP754 Ultra Deep base

**PRODUCT DATA**

**Product Type:** Acrylic  
**VOC based on white/pastel base.** See labels for other bases.  
**VOC (theoretical):**  
**As supplied (untinted):** 0.90 lb/gal (75 g/l)  
**Sheen:** Flat  
**Percent Solids:**  
  **Weight:** 55 ± 2%  
  **Volume:** 41 ± 2%  
**Weight/Gallon:** 11.4 lb  
**Viscosity (Initial):** 105 - 115 Krebs Units  
**Thinner:**  
  **Brush/Roller:** Thinning not recommended.  
  **Spray:** Thin with clean water up to ½ pint per gallon.  
**Clean-up:** Warm, soapy water.  
**Recommended Film Thickness:**  
  **Wet:** 5.0 to 7.0 mils  
  **Dry:** 2.0 to 2.8 mils  
**Practical Rate :** 250-300 square feet per gallon  
 Coverage does not include variation due to application, surface porosity, and/or mixing.  
**Dry time (70°F @ 50% R.H.):** (35°F@ 50% R.H.):  
**To Touch:** 1 hours 2 Hours  
**To Recoat:** 4 hours 24 hours  
**Full Service:** 15-30 days 15-30 Days  
 (Drying times listed may vary depending on temperature, humidity, color, and air movement.)  
**Flash Point:** Not Applicable  
**Flame Spread Rating:** Class A (0-25)  
 (See Porter Technical Bulletin No. 9: Flame Spread Rating.)  
**Federal Specification Crossover:** TT-P-19D  
 (See Porter Technical Bulletin No. 6: Federal Specification Performance Crossover.)

**LIMITATIONS OF USE**

Do not apply in direct sunlight or when air or surface temperature is below 35°F. Do not apply in late afternoon if condensation or fog is likely to occur, nor when rain is expected within 12 hours. Surface temperature must be at least 5°F above dew point. For optimum application properties, bring material to 65-85°F (18-29°C) temperature range prior to application. Use for service below 150°F. Do not use on floors or deck walking surfaces. Protect from freezing.

PPG Architectural Coatings

PERMANIZER™ Flat Exterior Acrylic Coating

## GENERAL SURFACE PREPARATION

Paint only clean, dry (may be damp, but not dripping), deglossed and profiled surfaces. Remove dirt, oils, grease, wax, form oils, release agents, sanding dust, paint remover, etc. with Dirtex and water, Porter Paint Thinner No. 5132 or other appropriate cleaners, or by vacuuming as necessary. Remove mildew by washing with PPG MILDEW CHECK Multi-Purpose Wash18-1 or a mix of 1 part chlorine bleach to 3 parts clean water (rinse thoroughly after 15 minutes). **NEW WOOD:** Repair construction defects, sand as necessary and apply first coat of PERMANIZER PP759. After primer is dry, fill openings and nail holes with TOP GUN™ 200 Siliconized Acrylic Caulk No. 1414, or other suitable sealant. Spot prime the caulk when well set, usually 1-4 hours. Spot prime knots and sap streaks with STA-KIL™ Primer/Sealer No. PP164 or shellac. Finish with one coat of PERMANIZER Flat Exterior Acrylic Coating No. PP759 Series. Tannin containing woods, such as redwood and cedar, require application at heaviest recommended film build for maximum stain blocking performance. **REPAINT:** Remove loose and failing paint by power washing, hand scraping or power tool cleaning and sand edges smooth when applicable. Fill holes and gouges in wood and other substrates with wood patch or filler, etc. as appropriate. Sand patched areas smooth as necessary before priming bare areas and patches. Finish with one or more coats of PERMANIZER Flat Acrylic Exterior Coating No. PP759 series.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation

**NEW CONCRETE/MASONRY/STUCCO:** Let new concrete, masonry and stucco cure 28 days before painting. (NOTE: Polymer modified thin coat stucco can usually be painted within 7-14 days depending upon drying conditions. Follow stucco manufacturer's instructions.) Remove any remaining deeply embedded contaminants such as curing compounds by abrasive blasting. Remove efflorescence by pressure washing or with a dilute muriatic acid solution following manufacturer's instructions. (CAUTION: When mixing and using, always add acid to water, and wear appropriate eye and skin protection.) Fill cracks and holes with Bondex Concrete Patch or other appropriate filler. For new concrete block (CMU), apply an appropriate Porter block filler (SEE RECOMMENDED SYSTEMS) before painting.

## DIRECTIONS FOR USE

Stir thoroughly before using and occasionally during use. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

### Permissible temperatures during application:

<b>Temperature Range:</b>	35°F to 110°F (air, surface, paint) (Optimum paint temperature 65-85°F)
<b>Dew Point:</b>	Surface temperature must be at least 5°F above the dew point.
<b>Relative Humidity:</b>	Maximum 85%

**New Work:** Apply a uniform coat of appropriate primer or block filler per primer data sheet instructions (SEE RECOMMENDED SYSTEMS) at the millage specified for the application. Finish with one or more coats of PERMANIZER Flat Exterior Acrylic Coating No. PP759 series.

**Repaint:** Spot prime bare areas as required with an appropriate primer (SEE RECOMMENDED SYSTEMS), then apply one or more coats of PERMANIZER Flat Exterior Acrylic Coating No. PP759 series.

**Washing Instructions:** Protect the finish from abuse and contamination until well cured, at least 4-6 weeks. Try to avoid washing the finish for 30 days.

## APPLICATION INFORMATION

**Application Equipment:** Apply with a high quality brush, roller, or by spray equipment.

**Airless Spray:** Minimum 28:1 Pump Ratio; .015"- .019" tip; 1800-2400 psi; 1/4" High Pressure material hose.

Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

**Brushes:** Use nylon or polyester brushes.

**Rollers:** Use 3/8" to 3/4" synthetic roller covers.

**Thinning:** Thinning not recommended.

**Clean-up:** Clean tools and spray equipment with warm, soapy water immediately after use.

## SHIPPING

**Freight Classification:** PAINT OR PAINT RELATED MATERIAL

**Packaging:** 4 Gallons per carton

**Shipping Weights:** 11.5 lb/gal (47.1 lb/carton)

PPGAF believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG/Porter Paints  
400 South 13th Street  
Louisville, KY 40203  
[www.porterpaints.com](http://www.porterpaints.com)

Technical Services  
1-800-332-6270

Architect/Specifier:  
1-888-PPG-IDEA

PPG Industries, Inc.  
One PPG Place  
Pittsburgh, PA 15272  
[www.ppg.com](http://www.ppg.com)



No. PP759  
series  
(Rev 10/06)