

# DULUX® ULTRA CLASSIC DRYWALL INTERIOR LATEX PRIMER 36600

Water based product

Technical Data Sheet



## Technical Specifications (21°C (70°F))

Solids by Volume:	30% (± 1%)
Solids by Weight:	48% (± 1%)

### Volatile Organic Compounds (VOCs)\*

According to ASTM D3960-05: < 100 g/L

### Available Colour

36600 White

**Gloss Level** Not applicable (primer)

- Gloss @ 60°: Not applicable
- Sheen @ 85°: Not applicable

### Practical Coverage

32 - 46 sq. metres (345 - 500 sq. ft.) per 3.78 litres

*Coverage figures do not include loss due to surface irregularities and porosity or material losses due to application method or mixing.*

### Resin Type

- Vinyl Acrylic

**Viscosity\*** Ready to use (97 - 105 Krebs Units)

*Manufacturing specification, working viscosity may vary*

**Flammability** Non Flammable  
**Flash Point\*** Not applicable

### Film Thickness requirements\*

- Wet: 81 to 118 µm  
3.2 to 4.6 mils
- Dry: 25 to 36 µm  
0.97 to 1.4 mils

### Drying Time\* @ 77°F/25°C - 50% Relative Humidity

Touch dry: 30 minutes  
To recoat: 2 to 4 hours  
Full curing: 30 days

When relative humidity is higher than 50%, double the required time.

*Drying times listed may vary depending on temperature, humidity, film build, colour, and air movement.*

\*Technical Data Source: 36600

## Product Description

Dulux Ultra Classic 36600 is a high hiding, fast drying latex sealer, designed for use where additional sealing/filling properties are required.

## Advantages

- Easy application
- High Hide
- Fast-drying latex sealer

## Intended Uses

- New and maintenance work.
- Residential and Commercial sites.
- Walls and ceilings of any room.

## Surfaces

- New surfaces in good condition and properly prepared: drywall boards (conventional, water repellent or fire retardant), hardened and dry drywall compound, new dry plaster, wood, concrete, brick, stucco or other masonries.
- Surfaces in good condition previously painted with a water based product and properly prepared.

## Limitations Of Use

- Must be coated with a topcoat.
- Not formulated to be used on floors.
- Not formulated to be used over aged alkyd finishes.

## Certifications

- MPI #50 Primer Sealer, Latex, Interior

**LIMITED WARRANTY:** PPG Architectural Coatings Canada, Inc. warrants performance of its products to its intended use if properly applied in accordance with the label directions and the specifications of the technical data sheet. Having no control over the application methods and conditions or the circumstances related to its use, no other warranty, expressed or implied, statutory or otherwise is given. This limited warranty extends only to the original purchaser of the product and is not transferable or assignable. If the product fails to conform to this limited warranty, we will, at your option, furnish replacement product or refund the purchase price. This limited warranty excludes (1) labour or costs of labour for the application or removal of any product and (2) all other direct, indirect, incidental, special or consequential damages.



Available at Dulux Paints Stores across Canada and Bétonel-Dulux Stores in Quebec. Before use, be sure to read and follow the instructions and warnings on the label and Safety Data Sheet. See other cautions on last page.

09/2024

## SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks or open seams. Sand old alkyd paints and all glossy, rough, and patched surfaces.

**Concrete Stucco or Masonry:** Plaster, concrete, and masonry must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting.

**Bare surfaces:** Sand the joint compound. Eliminate sanding dust, any dirt or contaminant.

**Painted surfaces:** Remove loose and peeling paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Sand to smooth edges. Eliminate stains caused by mildew with a solution of household bleach (1 part household bleach to 3 parts of water). Wear rubber gloves and eye protection. Rinse thoroughly with clear water and let dry completely. Remove all surface contaminants by washing with an appropriate cleaner. Rinse thoroughly with water and allow to dry.

Sand rough areas and dull glossy surfaces or alkyd painted surfaces to ensure adhesion. Clean up carefully sanding residue.

**Wood:** unpainted wood or wood in poor condition should be sanded smooth and clean up carefully to remove dust. If wood exudes resin, scrape the excess and clean surface with alcohol or paint thinner prior to seal knots and sap streaks with shellac. Some wood types prone to stains may require two coats of primer.

**PRECAUTION:** Dry sanding will give rise to dust and/or hazardous fumes. Wear suitable respiratory protective equipment. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact a regional Health Canada office for more information.

### Application

Stir thoroughly. Do not thin. Apply with a high-quality brush (polyester/nylon), roller, paint pad, or by airless spray equipment. Apply only when air, surface, and product temperatures are between 10°C (50°F) and 32°C (90°F). For optimum results on tough stains, woods with extractives, such as cedar or redwood, or on very porous or absorbent surfaces, it is recommended to apply the suitable basecoat.

### Application Conditions

Apply with good ventilation only when air and surface temperatures are between 10°C (50°F) and 32°C (90°F).

### Tools

- Brush: synthetic bristles (nylon, polyester)
- Roller: Lint free – 10 mm
- Spray (Airless equipment)\*: tip size: 0.015 to 0.021 in.  
Pressure: 1500 – 2000 psi

\*Spray recommendations may vary from figures listed depending on equipment manufacturer.

*Spray equipment must be handled with due care and in accordance with the manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.*

## SYSTEM RECOMMENDATIONS

### All recommended surfaces:

- *Dulux Ultra Classic* Interior Latex Sealer 36600– one coat to total surface.
- Appropriate *Dulux* topcoat – 2 coats for better durability and appearance.

### Cleanup

Remove as much product quantity as possible and clean hands and tools immediately with warm, soapy water. Clean spills right away with a damp cloth.

### Storage and Transportation

Keep product cool and dry. **PROTECT FROM FREEZING.**

### Disposal

Consult your municipality about proper disposal procedure of residue in accordance with the laws and respect the environment. Do not pour down a drain or storm sewer.

### Safety Measures

**MAY BE HARMFUL IF SWALLOWED. MAY CAUSE EYE AND SKIN IRRITATION.** Avoid breathing vapours, spray or mists. Avoid contact with skin and eyes. Wear protective gloves/clothing and eye/face protection. Keep out of reach of children. **Prior to use, read and follow product-specific SDS and label information.** **FIRST AID TREATMENT:** If swallowed, call a Poison Control Centre or doctor immediately. If in eyes or on skin, rinse well with water. If breathed in, move person to fresh air. Contains: Limestone; titanium dioxide; Kaolin. Contains isothiazolinones. May cause allergic reaction. Keep container tightly closed and sealed until ready for use. For workplace use, an SDS is available from your retailer or by calling 1-800-463-7426 (Canada). **EMERGENCY SPILL INFORMATION:** (412) 434-4515 (U.S.), (514) 645-1320 (Canada).

For product information call: 1-800-387-3663  
[www.dulux.ca](http://www.dulux.ca)



PPG Architectural Coatings Canada, Inc.  
1550 rue Ampère, Suite 500  
Boucherville (Québec), J4B 7L4

*Dulux* is a registered trademark of AkzoNobel and is licensed to PPG Architectural Coatings Canada, Inc. for use in Canada only. The *Multi-Coloured Swatches Design* is a registered trademark of PPG Architectural Finishes, Inc..