



Technical Data Sheet

CWF-UV - PENETRATING WOOD FINISH FOR DECKS, FENCES AND SIDING

FLOOD CWF FLD-52XC-FLD542C

Water-based product, matte finish

Product Description

Recommended for use on any properly prepared exterior wood, including decks, fences, siding, railings, outdoor furniture and other wood surfaces. Apply to new, dry, pressure-treated wood, uncoated new or weathered wood, or wood previously stained.

Apply directly to weathered wood previously finished with FLOOD CWF-UV; other previous coatings must be completely removed.

Recommended Uses

New or maintenance work.

Residential and commercial sites.

Properly prepared vertical and horizontal wood surfaces: decks, fences, siding, railings, outdoor furniture, etc.

Exterior only.

Surfaces

Properly prepared exterior wood:

→ New, dry, pressure-treated wood, uncoated new or weathered wood.

→ Weathered wood previously finished with FLOOD CWF.

Features & Benefits

- Guaranteed 4 years on fences & siding.
- Guaranteed 2 years on decks.
- Penetrates to protect against moisture and sun damage
- Ready for use and easy to apply.
- Penetrating and quick drying.
- Water-based microporous product allowing wood to breathe.
- Water-based product which allows tool clean-up with water.
- Complies with the Canadian Volatile Organic Compound (VOC) Concentration Limits for Architectural Coatings Regulations requirements.

Colour Range

Consult your retailer for more information on product and size availability.

- FLD520C CEDAR
- FLD521C REDWOOD
- FLD542C CLEAR NATURAL

Notes

Can be apply directly to weathered wood previously finished with FLOOD CWF; other previous coatings must be completely removed.

Not to be used on torrefied wood.

This product is not to be mixed with other products.

Characteristics (21°C (70°F))

Appearance	Translucent
Finish	Matte finish
Composition	<ul style="list-style-type: none">• Diluent: Water• Binder: Polymer and penetrating oil (emulsion)
Flammability	Non-flammable under normal use conditions
Flash Point*	Not applicable
Viscosity*	Ready to use (71 ± 5 Krebs Units)
Density*	1.0 ± 0.1 kg/L
Solids by Weight*	26%
Solids by Volume*	25%
Volatile Organic Compounds (VOCs)*	According to ASTM D3960-05: < 275 g/L Canadian regulation: < 350 g/L

*Technical data source: FLD-542C

Recommendations

- Tools**
- Paintbrush: Synthetic bristles (nylon, polyester).
 - Roller: Synthetic, woven cover 3/8-3/4 inch.
 - Stain-pad applicator.
 - Spray: Airless sprayer.
- When applying by roller or spray, always back-brush for best results.

Spreading Rate per Coat

3.78 L: 14 to 23 m² (150 to 250 ft²)

(Excluding losses caused by variations in application methods or surface porosity)

Cleaning Tools

Remove as much product quantity as possible and clean tools with lukewarm soapy water immediately after use.

Drying Time*

- Touch dry: 4 hours
- Before recoating: Apply wet-on-wet before the coat has dried
- Prior to withstanding rain: 48 hours
- Prior to light foot traffic: 24 hours
- Prior to normal foot traffic: 48 hours
- Before replacing the furniture: 72 hours
- Full curing: 30 days

When relative humidity is higher than 50%, double the required drying time.

Application Conditions

Temperature: 10 to 32°C (50 to 90°F)
(ideal 20°C ± 5°C [68°F ± 9°F]).

Relative humidity: Ideal between 15 and 50%, maximum 85%.

Do not apply when dew is imminent, in direct sunlight, on a warm surface or during windy conditions.

Application conditions must be maintained during product application and drying. Apply when no rain is expected within: 48 hours.

High humidity or low temperatures extend drying time.



Technical Data Sheet
CWF-UV - PENETRATING WOOD FINISH
FOR DECKS, FENCES AND SIDING
FLOOD CWF FLD-52XC-FLD542C
Water-based product, matte finish

Surface Preparation

Surface must be dry and clean. Remove all dust, dirt, mildew, oil, patina, loose wood fibres and other contaminants.

- ▶ Use FLOOD Wood Stripper to remove any previous coatings. Previous coatings must be completely removed.
 - ▶ To ensure proper adhesion, weathered, dirty or mildewed surfaces should be cleaned with FLOOD Wood Cleaner prior to applying product.
 - ▶ After rinsing, allow wood to dry.
 - ▶ Remove grade stamps or pencil marks by sanding.
 - ▶ Can be apply directly to weathered wood previously finished with FLOOD CWF.
- Strip, scrape, or sand to remove all other old previous coatings.
- ▶ Eliminate sanding residues. **PRECAUTION:** Dry sanding of dry coatings will give rise to dust and/or hazardous fumes. Wet sanding should be used, wherever possible. Wear suitable respiratory protective equipment when exposure cannot be avoided by adequate local ventilation.
 - ▶ Old cracked or warped boards must be replaced.
 - ▶ If wood exudes resin, scrape the excess and clean surface with alcohol or paint thinner.
 - ▶ At the end of the surface preparation, rinse well with water. If water beads, surface preparation must be repeated.
 - ▶ Once the surface is free of any contaminant, apply following the recommended application conditions.
 - ▶ Allow wood to dry at least 48 hours in dry weather or until it has reached a moisture content of 15% or less before finishing.

Systems recommendation according to surfaces

New or bare wood:

- 2 coats: FLOOD CWF-UV.

Old bare weathered wood:

- 2 coats: FLOOD CWF-UV.

Weathered wood previously finished with FLOOD CWF-UV

- FLOOD CWF-UV: One or two coats as required; other previous coatings must be completely removed.

Application

Before starting, test on a small area, applying all coats required on a sample of your bare wood to confirm that the result will be according to your expectations.

This is a ready-to-use product, do not thin. Stir thoroughly the product before and periodically during application.

Intermix batches for colour consistency. Pour the quantity of product needed into another container to avoid contaminating the original container. Keep containers closed when not in use.

APPLY OUTDOORS when no precipitation is expected for 48 hours.

Apply 1 thin coat to properly prepared surfaces.

Apply in the direction of the wood grain starting at one end of the wood and continuing to the other end.

Maintain a wet edge to prevent lap marks. Saturate all end grains, nail holes, cavities, and cracks in the wood.

On vertical surfaces the product should be applied from the top down.

- Two coats are necessary for optimal protection and appearance.

APPLY THE SECOND COAT BEFORE THE FIRST COAT HAS DRIED.

- Do not apply a second coat if the first coat has dried.

CAUTION: Surfaces are slippery when humid or wet; use caution when walking on these surfaces.

For more information: visit the website at www.floodstains.ca or call our customer service: 1-800-321-3444.



Technical Data Sheet

CWF-UV - PENETRATING WOOD FINISH FOR DECKS, FENCES AND SIDING

FLOOD CWF FLD-52XC-FLD542C

Water-based product, matte finish

Safety Measures

CAUTION: Read the Material Safety Data Sheet. Avoid contact with skin and eyes. Keep out of reach of children. Do not intentionally breathe vapours. Use only in well ventilated areas.

DANGER OF COMBUSTION. MAY IRRITATE EYES. Keep away from flames or sparks. Wear eye/face protection or chemical splash goggles. Use chemical-resistant, impervious gloves. Materials such as rags used with this product may begin to burn by themselves. After use, put rags in water or lay flat to dry, then discard.

FIRST AID TREATMENT: If in eyes or on skin, rinse thoroughly with clear water for 15 minutes. If swallowed, do not induce vomiting. Inhalation: If respiratory discomfort occurs, move the person to fresh air. Call Poison Control Centre or physician immediately.

Surface Maintenance

- Wait for its full curing before washing or testing adhesion: minimum 30 days.
- The level of sun exposure, the traffic intensity and the quality of ventilation of the structures drive the maintenance frequency. Wear and colour fading are natural ageing characteristics between maintenance coats.
- Maintenance varies according to usage and place. To maintain the products protective characteristics, apply a maintenance coat when visibly required.
- High and continuous moisture content, insufficient ventilation of wood or intensive traffic (decks) prematurely reduces the product durability or can cause peeling.
- While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior the coating and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae. Examples of these conditions include, but are not limited to, under eaves, behind shrubbery and trees, and in areas that are consistently damp with little to no direct sunlight.

Storage and Transportation

Keep product in a dry and ventilated area between 10 and 32°C (50 and 90°F). PROTECT FROM FREEZING.

Limited Warranty

SATISFACTION GUARANTEED: PPG Architectural Coatings Canada, Inc. warrants your complete satisfaction with the performance of this product for a period of 4 years on fences and siding and 2 years on decks when our product has been applied and maintained according to label directions. This 4 years on fences and siding and 2 years on decks satisfaction guarantee is non-transferable. The manufacturer does not warrant against problems with the product which are caused by factors beyond its control, such as structural defects, damage to the paint film by others, poor condition of the substrate, improper application, etc. If not satisfied as warranted, return the unused portion along with sales receipt to place of purchase. You will receive as your exclusive remedy either a refund of the price paid for the product or replacement with product of equal value. This warranty specifically excludes labour or costs of labour for the removal or application of any paint and indirect, special, consequential, incidental damages.

This technical data sheet, No FLD-52XC-FLD542C, replaces all previous versions.

The PPG Logo is a registered trademark of PPG Industries Ohio, Inc. CWF-UV, PENETROL, FLOOD and the FLOOD and Paintbrush Design are registered trademarks of the PPG Group of Companies.

PPG Architectural Coatings Canada, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin.