



Architectural Coatings

PORCH & FLOOR

PF9010 Series

Glidden Interior/Exterior Paint Satin

GENERAL DESCRIPTION

Glidden Porch & Floor, interior/exterior paint helps you create a beautiful, lasting look on porches, patios and pool decks. COOL SURFACE TECHNOLOGY™ limits surface temperature when compared to products of a similar color. It does not require a primer for easy application. It is highly durable and scratch resistant.

RECOMMENDED SUBSTRATES

Concrete	Incidental Ferrous Metal
Concrete Pavers	Wood

FEATURES / BENEFITS

Cool Surface Technology - Limits Surface Temperature By Up To 20%*

For Use On Porches, Patios & Pool Decks
No Primer Needed
Highly Durable
Scratch Resistant
Easy To Apply

*Limits hot weather surface temperature spikes of pedestrian and vehicular horizontal concrete surfaces when compared to products of similar color without *Cool Surface Technology*. Temperature containment may differ due to color, ambient temperature, direct sunlight, and time of day.

CONFORMANCE STANDARDS

Compliant with all US VOC regulations as of 10/2024

TINTING AND BASE INFORMATION

PF9010	Pure White (Base 1)
PF9050	Base 2 (Must Be Tinted)*
PF9056	Steel Grey
PF9057	Summer Suede
PF9058	Clay Court

*Must be tinted before use.

This product can be tinted into 26 unique colors that utilize *Cool Surface Technology*. Colors from the Cool-Surface color pallet will reduce the surface temperature of the coating when compared to both bare concrete and similar colors not utilizing surface-cooling technology.

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

PRODUCT DATA

PRODUCT TYPE:	100% Acrylic Latex
SHEEN*:	Satin, 10-20 @ 85°
VOLUME SOLIDS*:	40% +/- 2%
WEIGHT SOLIDS*:	53% +/- 2%
WEIGHT/GALLON*:	10.7 lbs. (4.9 kg) +/- 0.2 lbs. (91 g)
VOC:	< 50 g/L (0.4 lbs./gal.)

*Product data calculated on product PF9010.

COVERAGE: Approximately 300 to 400 sq. ft. (28 to 37 sq. meters) per U.S. gallon (3.78 L) on primed, smooth, nonporous surfaces.

Wet Film Thickness:	4.0 to 5.3 mils
Wet Microns:	102 to 135
Dry Film Thickness:	1.6 to 2.1 mils
Dry Microns:	41 to 53

Coverage figures do not include loss due to surface irregularities and porosity, or material loss due to application method or mixing. Some colors, drastic color changes, or porous surfaces may require more than one coat to achieve a uniform finish.

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.

To Touch:	1 hours
To Recoat:	4 hours
To Service:	24 hours

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement. Wait at least 30 days after painting before cleaning the surface with a non-abrasive, mild cleanser.

CLEANUP: Clean tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: > 200°F (93°C)

PACKAGING

1-Gallon (3.78 L)

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, mildew, grease, oil, chalk, rust, and any other surface contaminants. Blistering and peeling issues are commonly caused by moisture behind the paint film. Problems leading to excessive moisture in the substrate must be repaired prior to painting. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. New concrete should age a minimum of 30 days. Etching with acid is usually not required, but is recommended for optimum performance over smoothly troweled or new concrete. If acid etching, follow manufacturer's recommendations. This product is self-priming in most applications. When applied to an uncoated substrate or to bare wood, two coats are required with the first coat acting as the primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted, NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

CONCRETE: New concrete should cure for at least 30 days and preferably 90 days prior to painting. The pH of the substrate must be less than 10 before painting.

CONCRETE PAVERS: Remove loose aggregate. Clean, rinse thoroughly with water and allow to dry before painting

INCIDENTAL FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed with a metal primer.

WOOD: Countersink all nails, putty flush with surface. Unpainted wood or wood in poor condition should be sanded smooth, wiped clean. Any knots or resinous areas must be primed before painting.

LIMITATIONS OF USE

Apply when air, product, and surface temperatures are above 50°F (10°C) and surface temperature is at least 5°F (3°C) above the dew point. Air and surface temperatures must remain above 50°F (10°C) for the next 24 hours. Avoid exterior application late in the day when dew and condensation is likely to form or if rain is expected. Keep standing water off of painted surface for a minimum of one week.

Some surfaces coated with this product may become slippery when wet. **Please use caution.**

Do not use on surfaces that are frequently damp. Not recommended for use on garage floors or carports that are subject to tire traffic.

PROTECT FROM FREEZING.

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply with a high quality brush, roller, paint pad, or by spray equipment. If spray applied, back-rolling or back-brushing is recommended. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat. Do not overbuild. For best final appearance, work from unpainted into painted areas. Avoid excessive brushing and reworking of painted areas.

Airless Spray: Pressure range 1500 - 2000 psi, tip 0.015" - 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: High-quality, Nylon/Polyester brush

Roller: 3/8" - 1/2" nap roller cover

Thinning: Thinning is not required. However, for the first coat over a new or porous substrate, 1/4 pint (118 mL) of water per U.S. gallon (3.78 L) may be added.

Permissible temperatures during application:

Material: 50 to 90°F 10 to 32°C

Ambient: 50 to 90°F 10 to 32°C

Substrate: 50 to 90°F 10 to 32°C

PRECAUTIONS

WARNING! HARMFUL IF INHALED. Sanding and grinding dusts may be harmful if inhaled. Do not breathe vapor or mist. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information.** **FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. **CONTAINS:** water (7732-18-5), proprietary acrylic copolymer (Not available), Nepheline syenite (37244-96-5), Limestone (1317-65-3), titanium dioxide (13463-67-7), diiron trioxide (1309-37-1), Kaolin (1332-58-7). Contains isothiazolinones. May cause allergic reaction. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. **EMERGENCY SPILL INFORMATION:** (412) 434-4515 (U.S.).

© 2024 PPG Industries, Inc., All Rights Reserved. The *PPG Logo* is a registered trademark of PPG Industries Ohio, Inc. *Glidden* and the *Glidden Logo* are registered trademarks and *Cool Surface Technology* is a trademark of PPG Architectural Finishes, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.glidden.com

Technical Services
1-800-441-9695

Architect/Specifier
1-888-PPG-IDEA

PPG Architectural Coatings Canada Inc.
1550 rue Ampère, Suite 500
Boucherville (Quebec) J4B 7L4

PF9010 - 10/2024