



Architectural Coatings

Mulco Pitch Bituminous Sealant Roof &amp; Foundation Exterior

**GENERAL DESCRIPTION**

Bituminous sealant for exterior use.

**RECOMMENDED SUBSTRATES**

Can be applied on dry surfaces to seal or patch shingles and flashing. Used to seal joints between two perpendicular or juxtaposed surfaces subject to low thermal movement.

**FEATURES / BENEFITS**

- Seals small gaps in foundations, shingles, and flashing.
- Watertight seal.
- Seals small gaps up to 12 mm.
- Weather resistant.
- Does not sag.

**PRODUCT INFORMATION / PACKAGING**

Mulco 136950 Black 300 mL Tube

**LIMITATIONS OF USE****DO NOT USE INDOORS.****Use on dry surfaces only.**

Cannot be painted.

Do not use over coal tar products.

Do not use in contact with surfaces such as insulation panels (polystyrene, etc.) which can be damaged by solvents.

Does not adhere to polyethylene, polypropylene, recycled plastic, Teflon or other comparable materials.

Do not use on a flat roof where pounding water could be present.

Do not use on frozen or damp surfaces.

Does not withstand immersion (tank) or abrasion (foot traffic).

**Adhesion to materials not specifically mentioned are not guaranteed.**

**PRODUCT DATA**

**COMPOSITION:** Asphalt (bitumen) (binder), mineral fibres, inert charges (pigments), solvents (volatile material) and other additives.

**COLOUR:** Black

**APPEARANCE:** Homogeneous paste, fibrous, free of lumps and easy to extrude.

**MATERIAL TEMPERATURE:** 10°C to 30°C (50°F to 86°F).

**APPLICATION TEMPERATURE:** Can be applied at any temperatures.

**SERVICE TEMPERATURE:** -30°C to 50°C (-22°F to 122°F).

**CONSISTENCY:** Non-sag in normal use.

**APPLICATION METHOD:** Caulking gun.

**EXTRUDABILITY:** Easy to gun at room temperature.

**MINIMUM CURE TIME:** 24 hours in most conditions at room temperature.

**DRYING TIME:** Full cure in two weeks.

**COVERAGE:** 10 m for a 1 cm bead.

**FLAMMABILITY\*:** Flammable; combustible when dry.

**FLASH POINT\*:** 43°C (109°F).

**FREEZE/THAW STABILITY:** Stable.

**SHELF LIFE:** One year from date of purchase.

**ODOUR:** Solvent.

**CLEANER (wet product):** Use mineral spirits.

**CLEANER (dry product):** Use a putty knife and mineral spirits or another effective solvent; take care not to affect the other surfaces with a solvent too strong.

**MAX VOC\*:** < 20% by weight.

**SPECIFICATIONS:** Associated to CAN/CGSB-37.5.

\*Technical data source: 136950, Black

## GENERAL SURFACE PREPARATION/APPLICATION

**SURFACE PREPARATION:** The surfaces must be firm, clean, and exempt of all loose or foreign particles. Clean rusted metal with a metal brush.

**APPLICATION:** Can be applied at any temperatures. Product must be above 10°C (50°F) when applied. Cut nozzle tip at a 90° angle and leave an orifice that will allow a bead between 6 and 12 mm in width. Pierce the seal inside the nozzle. Use a caulking gun and apply a uniform, convex bead, pulling the gun away from the bead as shown. The angle of the caulking gun should be approximately 45°. Make sure the sealant makes at least 3 mm (1/8 in.) contact with each surface of the joint. Do not tool the bead to avoid defects during drying.



**STORAGE:** Freeze/Thaw stable.

**CLEANUP:** Clean tools with mineral spirits. Wash hands with soap and water.

**DISPOSAL:** Consult your municipality about proper disposal procedure of residue in accordance with the laws and respect the environment.

**PERMISSIBLE TEMPERATURES DURING APPLICATION:**

Material:	10 to 30°C	50 to 86°F
Ambient:	Can be applied at any temperatures.	
Substrate:	Can be applied at any temperatures.	

## PRECAUTIONS

**ATTENTION CAUTION IRRITANT MAY IRRITATE EYES.** Do not get in eyes. Keep away from flames or sparks. Keep out of reach of children. Wear protective gloves and eye/face protection: Chemical splash goggles. Use chemical-resistant, impervious gloves. **Prior to use, read and follow product-specific SDS and label information.** **FIRST AID TREATMENT:** Contains: Asphalt; calcium carbonate; Stoddard solvent; Cellulose. If swallowed, call a Poison Control Centre or doctor immediately. Do not induce vomiting. If in eyes, rinse with water for 15 minutes. Inhalation of high concentrations of vapour may affect the central nervous system. Repeated exposure to high vapour concentrations may cause irritation of the respiratory system and permanent brain and nervous system damage. High vapour concentrations can cause headaches, dizziness, drowsiness and nausea and may lead to unconsciousness. Keep container tightly closed and sealed until ready for use. For workplace use, an SDS is available from your retailer or by calling 1-800-463-7426 (Canada). EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.), (514) 645-1320 (Canada).

**LIMITED WARRANTY:** This product is covered by a Limited Warranty. For details, visit [www.mulco.ca/en-ca/limited-warranty](http://www.mulco.ca/en-ca/limited-warranty) or call 1-866-660-2220.

The PPG Logo is a registered trademark of PPG Industries Ohio, Inc. Mulco is a registered trademark of AkzoNobel.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-866-660-2220.

