

*PPG Gripper Interior/Exterior Acrylic Primer + Sealer***GENERAL DESCRIPTION**

A premium interior/exterior acrylic primer formulated to meet the performance requirements of the residential and commercial segments. A whole house primer for use on properly prepared interior or exterior wood, masonry, plaster, wallboard, cement, brick, stucco, and cement composition board. Prepares surface for wall coverings and helps protect drywall. Especially formulated to kill most stains – water, smoke, ink, markers, and tannins.

**RECOMMENDED SUBSTRATES**

Aluminum Siding	Masonry
Brick	MDO Board
Concrete	Plaster
Fiber Cement	Stucco
Fiberglass	Vinyl Siding*
Gypsum Wallboard-Drywall	Wood

\*Vinyl siding and similar plastic composites should not be painted with a color darker than the original color. Painting vinyl siding or plastic composites with a darker color may cause them to warp. Color selection for use over vinyl siding is limited. For information, call 1-800-441-9695.

**FEATURES / BENEFITS**

Interior/Exterior Acrylic Primer + Sealer  
 Excellent Adhesion & Sealing  
 Outstanding Stain & Tannin Blocking  
 Great Hide  
 Great for a Variety of Hard-to-Stick Surfaces  
 Excellent Coverage  
 Fast Drying  
 Low VOC

**PRODUCT INFORMATION**

1900-0100	White
1800-0100	Grey

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

**PRODUCT DATA**

<b>PRODUCT TYPE:</b>	100% Acrylic Latex
<b>SHEEN:</b>	Low Sheen
<b>VOLUME SOLIDS*:</b>	40% +/- 2%
<b>WEIGHT SOLIDS*:</b>	52% +/- 2%
<b>WEIGHT/GALLON*:</b>	10.5 lbs. (4.8 kg) +/- 0.2 lbs. (91 g)
<b>VOC*:</b>	<100 g/L (0.4 lbs./gal.)

\*Product data calculated on product 1900-0100.

**COVERAGE:** Approximately 300 to 400 sq. ft. (28 to 37 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0 - 5.3 mils
Wet Microns:	102 - 135
Dry Film Thickness:	1.6 - 2.1 mils
Dry Microns:	41 - 53

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

<b>DRYING TIME:</b>	Dry time @ 77°F (25°C); 50% relative humidity.
To Touch:	30 minutes
To Recoat:	1 hour
To Full Cure:	30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement. For example, product applied at 35°F (2°C) would require a minimum of 24 hours before recoat. Drying is important to stain-blocking properties. For maximum stain resistance, allow 24 hours before topcoating. If drying conditions are poor (low temperature, high humidity), longer drying times are required to achieve stain blocking.

**CLEANUP:** Clean tools with warm, soapy water.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

**FLASH POINT:** Over 200°F (93°C)

**PACKAGING**

Quart (946 mL)
1-Gallon (3.78 L)
5-Gallon (18.9 L)

Not all products are available in all sizes.

**PPG Gripper Interior/Exterior Acrylic Primer + Sealer****GENERAL SURFACE PREPARATION**

Surface must be clean and dry. Remove dirt, mildew, grease and other surface contamination. Remove loose paint, excessive amounts of chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Repair all moisture problems. Blistering and peeling issues are commonly caused by moisture behind the paint film. Putty all nail holes, and caulk all cracks and open seams. Sand all rough, and patched surfaces. Sanding is not required if the surface is properly and thoroughly cleaned.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**ALUMINUM SIDING and FIBERGLASS:** Aluminum siding and fiberglass may present potential adhesion problems. Prime prior to topcoating. Primer should be spot applied, allowed to cure overnight, then evaluated for adhesion. Check adhesion by applying a piece of masking tape. If adhesion is good, the application may proceed. If the coating peels off when the masking tape is removed, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion.

**BRICK, CONCRETE, MASONRY and STUCCO:** New concrete and masonry should cure for at least 7 days and preferably 30 days prior to priming and painting. The pH of the substrate must be less than 13 before priming. Painting glazed brick is not recommended due to potential adhesion problems.

**GYPSON WALLBOARD-DRYWALL:** Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, then prime prior to painting the substrate.

**FIBER CEMENT:** Fiber cement board may present potential adhesion, alkali burn, and efflorescence problems. New board should be aged for at least 7 days and preferably 30 days prior to priming and painting. The pH of the substrate must be less than 13 and the moisture content must be less than 12% prior to priming and topcoating. All cracks and opens seams should be caulked to prevent water penetration. Pre-primed board from the manufacturer may not be uniformly or completely sealed. It is recommended that a primer be applied to ensure complete and uniform sealing prior to topcoating.

**MEDIUM DENSITY OVERLAY (MDO) BOARD:** Countersink all nails or screws and putty flush with the surface. Surface should be sanded smooth and cleaned to remove any dust or contaminates, then primed prior to painting.

**PLASTER:** Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 7 days and preferably 30 days prior to priming.

**VINYL SIDING:** Vinyl siding may present potential adhesion problems. Primer should be spot applied, allowed to cure overnight, then evaluated for adhesion. If adhesion is good, the application may proceed. Check adhesion by applying a piece of masking tape. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion. Color selection for vinyl siding is limited. Do not paint vinyl siding with a topcoat color darker than the original to prevent potential warping due to heat absorption.

**WOOD:** Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime. Staining or tannin bleeding woods (like cedar or redwood) require two coats. The first coat must be completely dry before re-coating. For optimum tannin blocking performance, allow the first coat to dry a full 24 hours prior to the application of a second coat.

**LIMITATIONS OF USE**

Apply when air and surface temperatures are 35°F (2°C) and surface temperature is at least 5°F (3°C) above the dew point. For optimum application properties, bring material to at least 50°F (10°C) prior to application. Air and surface temperature must remain above 35°F (2°C) for the next 24 hours. Avoid painting late in the day when dew and condensation are likely to form or if rain or snow is expected. Do not apply in direct sunlight.

**PROTECT FROM FREEZING.**

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to painting and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae.

## PPG Gripper Interior/Exterior Acrylic Primer + Sealer

## APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

**Application Equipment:** Apply with a high quality brush, roller, paint pad, or by spray equipment. Severe stains may require two coats of primer. Brushing is the preferred method of application over chalky substrates. If painting will be interrupted for more than 15 minutes, keep brushes and rollers wet by wrapping them in tinfoil or plastic wrap.

**Airless Spray:** Pressure 1500 - 2000 psi; tip 0.015" - 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

**Brush:** Polyester/Nylon Brush

**Roller:** 3/8" - 3/4" nap roller cover

**Thinning:** Do not thin.

**Permissible temperatures during application:**

Material:	35 to 90°F	2 to 32°C
Ambient:	35 to 100°F	2 to 38°C
Substrate:	35 to 100°F	2 to 38°C

## PRECAUTIONS

**WARNING! HARMFUL IF INHALED. HARMFUL IF SWALLOWED. CAUSES RESPIRATORY TRACT IRRITATION.** Do not breathe vapor or mist. Do not swallow. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information. FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2019 PPG Industries, Inc. All Rights Reserved. The PPG Logo is a registered trademark of PPG Industries Ohio, Inc. Gripper is a registered trademarks of PPG Architectural Finishes, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.



PPG Architectural Finishes, Inc.  
One PPG Place  
Pittsburgh, PA 15272  
www.pro.ppg.com

Technical Services  
1-800-441-9695

Architect/Specifier  
1-888-PPG-IDEA

PPG Architectural Coatings Canada Inc.  
2505, rue de la Métropole,  
Longueuil (Québec) Canada J4G 1E5

1900-0100 1/2019