

Architectural Coatings

Multi-Pro Maintenance Interior Latex Wall & Ceiling Paint Eggshell

GENERAL DESCRIPTION

Multi-Pro Maintenance Interior Latex Wall & Ceiling Eggshell is a durable, quality interior vinyl acetate ethylene paint designed for new and repaint applications where speed of application is most important in both the commercial and multi-family markets. This low-VOC, low odor paint enables a space to be painted while occupied while delivering the durable product performance required. Multi-Pro Maintenance Interior Wall & Ceiling paint has good hide and easy application properties on walls, ceilings and trim surfaces. Multi-Pro Maintenance is recommended on interior walls, ceilings and trim where an eggshell finish is desirable.

PRODUCT DATA

PRODUCT TYPE: Vinyl Acetate Ethylene
SHEEN: Eggshell, 8-12 @60°
VOLUME SOLIDS*: 30% +/- 2%
WEIGHT SOLIDS*: 43% +/- 2%
WEIGHT/GALLON*: 10.2 lbs. (4.6 kg) +/- 0.2 lbs. (91 g)
VOC*: <50 g/L (0.4 lbs./gal.)
COVERAGE: Approximately 300 to 400 sq. ft. (28 to 37 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

RECOMMENDED SUBSTRATES

Concrete/Masonry	Gypsum Wallboard-Drywall
Concrete Block (CMU)	Plaster
Ferrous Metal	Wood

Wet Film Thickness: 4.0 - 5.3 mils
 Wet Microns: 102 - 135
 Dry Film Thickness: 1.2 - 1.6 mils
 Dry Microns: 30 - 41

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing. Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

CONFORMANCE STANDARDS

VOC compliant in all regulated areas
 Can help earn LEED 2009 credits

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.
 To Touch: 1 hour
 To Recoat: 4 hours
 To Full Cure: 30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

TINTING AND BASE INFORMATION

1452-100XI White & Pastel Base

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

CLEANUP: Clean tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

FEATURES / BENEFITS

Features
 Good Hide
 Excellent uniformity
 Easy soap and water clean-up
 Easy application
 Low VOC/Low Odor
 Can help earn LEED 2009 credits

Benefits
 Provides a uniform appearance
 Prevents sheen variation
 Safe waterborne formula
 Brush, roller or spray application
 Meets the most stringent VOC regulations nationwide
 Contributes to sustainable design

GENERAL SURFACE PREPARATION

Surface must be dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough and patched surfaces. Plaster, concrete and masonry surfaces must be completely dry, free of efflorescence and allowed to cure for 30 days prior to painting. This product is self-priming on new drywall. Prime all bare wood, plaster, masonry, and porous surfaces with an appropriate PPG primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

CONCRETE/MASONRY: New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended.

CONCRETE BLOCK (CMU): Mortar should cure for at least 30 days and preferably 90 days prior to painting. Fill block with an appropriate block filler.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

GYP SUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust prior to painting the substrate.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended.

WOOD: Countersink all nails, putty flush with surface. Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be sealed before painting.

RECOMMENDED PRIMERS

Concrete/Masonry	4-603XI, 17-921XI, 3210-120XI
Concrete Block (CMU)	6-7, 6-15XI
Ferrous Metal	90-712, 90-912
Gypsum Wallboard-Drywall	Self-Priming, 6-2, 6-4, 9-900, 12-900XI, 3210-120XI
Plaster	4-603XI, 17-921XI, 3210-120XI
Wood	6-2, 9-900, 12-900XI, 17-921XI, 3210-120XI

LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C).

Not recommended for use on floors.

PROTECT FROM FREEZING.

PACKAGING

- 1-Gallon (3.78 L)
- 5-Gallon (18.9 L)

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply with a high quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

Airless Spray: Pressure 1500 to 2000 psi, tip 0.015" - 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush

Roller: 3/8" - 3/4" nap roller cover

Thinning: No thinning is usually required.

Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 90°F	10 to 32°C
Substrate:	50 to 90°F	10 to 32°C

PRECAUTIONS

Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information. FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. If experiencing respiratory symptoms call a POISON CENTER or doctor/physician. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2018 PPG Industries, Inc. All Rights Reserved. The *PPG logo* is a registered trademark and the *PPG Paints Logo & Design* is a trademark of PPG Industries Ohio, Inc. *Multi-Pro* is a registered trademark of PPG Architectural Finishes, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.ppgpaints.com

Technical Services
1-800-441-9695
1-888-807-5123 fax

Architect/Specifier
1-888-PPG-IDEA

PPG Architectural Coatings Canada Inc.
1550 rue Ampère, Suite 500
Boucherville (Quebec) J4B 7L4

1452-100XI - 7/2019