

Architectural Coatings

PITTSBURGH® Paints Accent Color Base

GENERAL DESCRIPTION

Pittsburgh Paints' Accent Color Base offers an enriched formulation that provides exceptional hiding and maximum color richness, delivering the deep, dark shades that other paints can't match. With guaranteed two coat coverage Accent Color Base provides ultra hiding power for all colors.

TINTING AND BASE INFORMATION

Use PITTSBURGH® Paints Custom Colorants to achieve hundreds of colors. Refer to THE VOICE OF COLOR® formula book for tinting instructions.

25-250 Accent Color Base

Some colors, or drastic color changes, may require more than one coat to achieve a uniform finish.

RECOMMENDED USES

Drywall	Masonry
Metal	Plaster
Wood	

FEATURES / BENEFITS

Ultra Hiding Power
Formulated for Vivid and Dark Colors
Two Coat Coverage Guaranteed
100% Acrylic

LIMITATIONS OF USE

Apply when air, surface and product temperatures are between 50°F (10°C) and 90°F (32°C). PROTECT FROM FREEZING. Product should not be used in bathrooms or other high humidity areas.

PRODUCT DATA

PRODUCT TYPE:	100% Acrylic Latex
GLOSS:	Matte
VOC:	0.8 lbs./gal (90 g/L)
DFT:	1.5 minimum to 1.8 maximum mils

COVERAGE*:	Approximately 400 sq. ft./gal. (37.2 sq. m/3.78L)
-------------------	--

Wet Film Thickness:	4.0 mils
Wet Microns:	102

Dry Film Thickness:	1.5 mils
Dry Microns:	38

Coverage does not include variation due to application methods, surface porosity, and/or mixing.

VOLUME SOLIDS:	37% +/- 2%
WEIGHT SOLIDS:	46% +/- 2%

WEIGHT/GALLON:	9.7 lbs. (4.4 kg) +/- 0.2 lbs. (91 g)
-----------------------	---------------------------------------

DRYING TIME: Dry time @77°F (25°C); 50% relative humidity.

To Touch:	2 hours
To Handle:	2 hours
To Recoat:	8 hours

Drying times listed may vary depending on temperature, humidity, color and air movement.

FLASH POINT:	Over 200°F (93°C)
---------------------	-------------------

CLEAN UP:	Warm soap and water
------------------	---------------------

GENERAL SURFACE PREPARATION

Surface to be painted must be clean, dry, smooth, and free of dirt, grease, powdery or peeling paint, and other surface contaminants. All cracks and other surface imperfections must be repaired using high quality patching compounds, then allowed to dry thoroughly. Repaired areas should be sanded smooth and then spot-primed. Slick or glossy surfaces of previously applied paint, in sound condition, must be dulled by sanding. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

NEW WOOD: New wood should be sanded smooth and wiped clean. Seal knots or resinous areas. Countersink all nails. Putty flush with surface, then prime.

NEW PLASTER: Fresh plaster, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

CONCRETE BLOCK, CINDER BLOCK, VERTICAL MASONRY: New concrete should cure for at least 30 days and preferably 90 days prior to priming. Fill block with an appropriate block filler.

METAL: Rust and other surface contaminants must be removed. Then the surface must be cleaned thoroughly to remove any dust, then prime..

WATER-SOLUBLE STAINS: Apply SEAL-GRIP® Primer 17-921 or 17-931, over stained area prior to coating, to avoid bleeding of the stain into the topcoat.

RECOMMENDED PRIMERS

Concrete Masonry Units, Masonry (Block Fillers)	6-7, 6-15
Concrete, Masonry (Primers, Sealers)	4-603, 4-808
Drywall	6-4, 6-2, 17-921
Ferrous Metal	90-712
Galvanized Steel	90-712
Plaster	4-603
Wood	17-921, 17-955, 17-956

DIRECTIONS FOR USE

Stir thoroughly before using and frequently during use. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

When using more than one container of the same color, intermix to ensure color uniformity.

Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 90°F	10 to 32°C
Substrate:	50 to 90°F	10 to 32°C

APPLICATION INFORMATION

Application Equipment: Apply with a high quality brush, roller, paint pad or by spray equipment.

Airless Spray: Pressure 2000 psi, tip 0.015" - 0.021"

Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush

Roller: 3/8" - 3/4" nap roller cover

Thinning: No thinning is required.

PACKAGING

1-Gallon (3.78 L)
Quart (946 mL)

PPGAF believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.pittsburghpaints.com

Technical Services
1-800-441-9695
1-888-807-5123 fax

Architect/Specifier:
PPG Architectural Finishes
400 S. 13th Street
Louisville, KY 40203

PPG Canada, Inc.
Architectural Coatings
4 Kenview Blvd
Brampton, ON L6T 5E4

A2.25 1/2007