

REZ®

77-860 Series

Architectural Coatings

REZ® Exterior Stain Semi-Transparent Oil - Low VOC

Generic Type

Alkyd/Oil Resin

General Description

Our premium semi-transparent oil stain is formulated to meet the performance requirements of the residential and commercial markets. REZ® Exterior Semi-Transparent Oil Stain is an alkyd-based, penetrating stain that produces a rich color while letting the wood's natural grain to show through. Recommended for exterior pressure-treated wood, decks, porches, sawn siding, beams, shakes, fences, shingles, wood trim and previously stain wood trim and previously stained wood surfaces.

Tinting and Base Information

Use PITTSBURGH® Paints custom colorants and refer to THE VOICE OF COLOR® electronic CD or formula book for tinting instructions.

77-860 Mixing Base (must be tinted before use)

77-911 Redwood 77-916 Cedar

Recommended Uses

Decks Fences
Siding Wood Trim

Features / Benefits

Excellent Adhesion

Highlights Wood's Natural Grain & Texture

Water Repellent

Penetrates and Protects

Mildew Resistant on the Stain Film

Tintable to Hundreds of Semi-Transparent Stain Colors

Product Data

Gloss: Not Applicable for this Product Code

VOC*: 4.52 lbs/gal (542.00 g/L)

DFT: 0.80 minimum to 1.60 maximum mils

Coverage: (Smooth) 250 to 350 sq. ft./gal. (28 to 56 sq. m/3.78L)

(Rough) 100 to 250 sq. ft./gal.

Note: Does not include loss due to varying application method, surface porosity, or mixing.

Volume Solids*: 30.1% +/- 2.0% Weight Solids*: 39.1% +/- 2.0%

Viscosity: 14 to 18 sec #4 Ford Cup

Weight/Gallon*: 7.4 lbs. (3.4 kg) +/- 0.2 lbs. (91 g)
Cleanup: Leptyne Paint Thinner 21-263

*Product data calculated on product 77-860.

Drying Time:

To Touch: 2 - 4 hours
To Handle: 18 hours
To Recoat: 24 hours
To Full Cure: 24 - 48 hours

Dry Time @77°F (25°C); 50% relative humidity

Flash Point: 110°F, (43.3°C)

Limitations of Use

Apply when air, surface and product temperatures are above 50°F (10°C) and surface temperature is at least 5°F (3°C) above the dew point. Avoid staining late in the day when dew and condensation are likely to form or if rain is threatening. Do not use below ground, on previously painted wood surfaces or on abraded plywood. For exterior use only. Not recommended for immersion service. Do not use on metallic or masonry surfaces. Stain effects may vary slightly in color on different species of wood. Test in a remote area before proceeding.

Architectural Coatings

REZ® Exterior Stain Semi-Transparent Oil - Low VOC

General Surface Preparation

Surface must be dry and free from dirt, sawdust, loose fibers, mildew, flaking or peeling stain, grease, and other surface contamination. Countersink and spot prime all ferrous nails and fill voids with putty. Sand surface smooth, always with the grain. For woods prone to bleeding, such as redwood or red cedar, white or light colored stains are not recommended. Remove and inhibit regrowth of mildew on exterior surfaces by using MILDEW CHECK® Multi-Purpose Wash, 18-1, by PITTSBURGH® Paints. Before use, be sure to read and follow the instructions and warnings on the label. To avoid lap marks maintain a continuous wet edge. On vertical siding, begin at the top, covering a width of several boards -- then apply continuously to the bottom. On horizontal siding, start at a corner, covering several boards, then apply continuously to a break at a door, window or corner. Different species of wood may affect the color of this product slightly due to the inherent differences in hold-out and absorption qualities of the woods. Applying the stain to a test patch on a remote area of the substrate is suggested before proceeding if different species of wood are to be stained.

Recommended Primers

none

Refer to Surface Preparation Recommendations.

Application Information

Recommended Spread Rates:

2.7 minimum to Wet Mils: 5.3 maximum 68.6 minimum to 134.6 maximum Wet Microns: Dry Mils: minimum to 1.6 maximum 20.3 minimum to Dry Microns: 40.6 maximum

Application Equipment: Apply with a high quality brush or

spray equipment.

Airless Spray: Pressure 900 psi, tip 0.016" - 0.025"

Brush: High Quality Natural Bristle Brush

Roller: Not Recommended

Thinning: DO NOT THIN.

Directions for Use

Thoroughly mix by stirring with a circular uplifting motion. If spray applied, backbrushing is required. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

Permissible temperatures during application:

Material: 50 to 90°F 10 to 32 °C 50 to 100°F Ambient: 10 to 38°C 50 to 100°F 10 to 38 °C Substrate

PPGAF believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695

Packaging: 1-Gallon (3.78L) 5-Gallon (18.9L)

Not all products are available in all sizes.



Bulletin: 77-860

Additional copies of this bulletin can be obtained from our web site or by calling 1-800-428-7806.

PPG Architectural Finishes, Inc. One PPG Place

Pittsburgh, PA 15272

www.pittsburghpaints.com

Technical Services: 1-800-441-9695

Architect/Specifier:

1-888-774-7732 International Sales: 4 Kenview Blvd. Brampton, Ontario L6T5E4

(905) 790-5336 1-877-238-6441 (412) 434-2049

Rev. 3/2003

PPG Architectural Coatings-Canada