

## Exterior 100% Acrylic Latex Flat

### GENERAL DESCRIPTION

*Lucite* Exterior Paint features a 100% acrylic latex formula that is not only durable – it's easy to apply and easy on the budget. Ideal for use on properly prepared exterior wood, brick, masonry, concrete, weathered aluminum, weathered vinyl siding, and primed metal substrates. Vinyl siding and similar plastic composites should not be painted with a color darker than the original color. Painting vinyl siding or plastic composites with a darker color may cause them to warp. Color selection for use over vinyl siding is limited. For information, call 1-800-441-9695.

### RECOMMENDED SUBSTRATES

Aluminum Siding	Ferrous Metal	Stucco
Brick	Fiber Cement Board	Vinyl
Concrete	Masonry	Wood

### FEATURES / BENEFITS

- Durable 100% Acrylic Latex
- Very Good Hide and Coverage
- Provides a Mildew Resistant Coating
- Low Temperature Application Down to 35°F Extends the Painting Season
- 15 Year Warranty
- Easy Water Clean Up

### PRODUCT INFORMATION

41-6510	Pastel Base*
41-6515	Midtone Base*
41-6517	Deep Rustic Base*
41-6520	White

\*Must be tinted before use. Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

### PACKAGING

1-Gallon (3.78 L)  
5-Gallon (18.9 L)

Not all products are available in all sizes.

### PRODUCT DATA

<b>PRODUCT TYPE:</b>	100% Acrylic Latex
<b>SHEEN*:</b>	Flat, 0-5 @60°; 0-5 @85°
<b>VOLUME SOLIDS*:</b>	34% +/- 2%
<b>WEIGHT SOLIDS*:</b>	50% +/- 2%
<b>WEIGHT/GALLON*:</b>	11.0 lbs. (5.0 kg) +/- 0.2 lbs. (91 g)
<b>VOC:</b>	< 50 g/L (0.4 lbs./gal.)

\*Product data calculated on product 41-6510.

**COVERAGE:** Approximately 300 to 400 sq. ft. (28 to 37 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0-5.3 mils
Wet Microns:	102-135
Dry Film Thickness:	1.4-1.8 mils
Dry Microns:	36-46

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing. Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

<b>DRYING TIME:</b>	Dry time @ 77°F (25°C); 50% relative humidity.
To Touch:	30 minutes
To Recoat:	4 hours
To Full Cure:	30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement. For example, product applied at 35°F (2°C) would require a minimum of 24 hours before recoat.

**CLEANUP:** Clean tools with warm, soapy water.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

<b>FLASH POINT:</b>	Over 200°F (93°C)
---------------------	-------------------

## Exterior 100% Acrylic Latex Flat

## GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, mildew, grease, oil, chalk, rust, and any other surface contaminants. Blistering and peeling issues are commonly caused by moisture behind the paint film. Problems leading to excessive moisture in the substrate must be repaired prior to painting. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Stucco, concrete, and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. An appropriate primer is recommended for all uncoated surfaces and special substrates, such as tannin staining wood, new or chalky masonry, and bare metal.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**ALUMINUM SIDING:** Aluminum siding may present potential adhesion problems. Prime prior to topcoating. A specialty primer may be required if the original painted surface has degraded to the substrate. Topcoat should be spot applied, allowed to cure overnight, then evaluated for adhesion. If adhesion is good, the application may proceed. Check adhesion by applying a piece of masking tape. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion.

**BRICK, CONCRETE, MASONRY and STUCCO:** New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended. Painting glazed brick is not recommended due to potential adhesion problems.

**FERROUS METAL:** The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed with a metal primer.

**FIBER CEMENT:** Fiber cement board may present potential adhesion, alkali burn, and efflorescence problems. New board should be aged for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 and the moisture content must be less than 12% prior to priming and topcoating. All cracks and opens seams should be caulked to prevent water penetration. Pre-primed board from the manufacturer may not be uniformly or completely sealed. It is recommended that an alkali resistant primer be applied to ensure complete and uniform sealing prior to topcoating.

**VINYL SIDING:** Vinyl siding may present potential adhesion problems. Topcoat should be spot applied, allowed to cure overnight, then evaluated for adhesion. If adhesion is good, the application may proceed. Check adhesion by applying a piece of masking tape. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion. Color selection for vinyl siding is limited. Do not paint vinyl siding with a color darker than the original to prevent potential warping due to heat absorption.

**WOOD:** Unpainted wood or wood in poor condition should be sanded smooth and wiped clean. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime.

## LIMITATIONS OF USE

**FOR EXTERIOR USE ONLY.** Apply only when air, surface, and product temperatures are between 35°F (2°C) and 90°F (32°C) and at least 5°F (3°C) above the dew point. Air and surface temperatures must remain between 35°F (2°C) and 90°F (32°C) for the next 48 hours. Avoid painting in direct sunlight or on hot surfaces. Do not apply late in the day when dew and condensation are likely to form or if rain or snow is expected. On large expanses of metal, temperatures must be 50°F (10°C) or higher.

Not recommended for use on steps, floors, or vinyl surfaces.

## PROTECT FROM FREEZING.

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to painting and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae. Examples of these conditions include, but are not limited to, under eaves, behind shrubbery and trees, and in areas that are consistently damp with little to no direct sunlight.

## Exterior 100% Acrylic Latex Flat

## APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

**Application Equipment:** Apply with a high quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

**Airless Spray:** Pressure 1500-2000 psi, tip 0.015" - 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

**Brush:** Nylon/Polyester Brush

**Roller:** 3/8" - 3/4" nap roller cover

**Thinning:** Do not thin.

**Permissible temperatures during application:**

Material:	35 to 90°F	2 to 32°C
Ambient:	35 to 90°F	2 to 32°C
Substrate:	35 to 90°F	2 to 32°C

## PRECAUTIONS

For warning information, please refer to the SDS and label. Keep container tightly closed and sealed until ready for use. SDS, spill, and emergency information are available by calling 1-833-477-1553.

© 2021 PPG Industries, Inc. All Rights Reserved. *Pittsburgh Paints & Stains* is a registered trademark of PPG Architectural Finishes, Inc. The *PPG Logo* is a registered trademark of PPG Industries Ohio, Inc. *Lucite* is a registered trademark of Ewald Doerken AG, used under license.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.

