Super Premium Stain + Sealant In One Solid

GENERAL DESCRIPTION

Paramount Super Premium Solid is ideal for use on any properly prepared exterior wood, including decks, fences, siding, railings, outdoor furniture and other wood surfaces. Apply to new, dry, pressure-treated wood, uncoated new or weathered wood, or wood previously stained or painted. Use on exotic hardwoods may affect coverage, dry time, and durability. Note: Surface may become slippery when wet.

RECOMMENDED SUBSTRATES

Wood Decks Wood Railings Wood Fences Wood Siding

FEATURES / BENEFITS

Two Coat Application
Exceptional Waterproofing Protection
Advanced UV Protection
Rain Ready in 12 Hours
Excellent Color Retention
Provides a Mildew Resistant Finish
Resists Cracking & Peeling

PRODUCT INFORMATION

41-8301 White & Pastel Base (May Be Tinted) 41-8302 Clear Base (Must Be Tinted)*

*Must be tinted before use. Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

PACKAGING

1-Gallon (3.78 L) 5-Gallon (18.9 L)

PRODUCT DATA

PRODUCT TYPE: 100% Acrylic SHEEN: Matte

VOLUME SOLIDS*: 32% +/- 2%

WEIGHT SOLIDS*: 42% +/- 2%

WEIGHT/GALLON*: 9.7 lbs. (4.4 kg) +/- 0.2 lbs. (91 g)

VOC: < 100 g/L (0.8 lbs./gal.)

*Product data calculated on product 41-8301.

COVERAGE: Approximately 350 to 500 sq. ft. (32 to 47 sq. meters) per gallon (3.78 L) depending on application, wood texture, and porosity.

DRYING TIME: Normally dries to the touch in 30 minutes when applied in optimal temperatures of 50°F (10°C) to 85°F (29°C). Allow 2 to 4 hours between coats or before recoating. Application in high humidity or in temperatures below 50°F (10°C) may prolong drying times. Allow 24 to 48 hours of drying time before light foot traffic and 72 hours before normal foot traffic or replacing furniture. Allow new stain to cure 30 days before washing.

CLEANUP: Clean brushes and tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

LIMITATIONS OF USE

FOR EXTERIOR USE. Apply when no precipitation is expected for 12 hours, and when air and surface temperatures are 35°F (2°C) to below 90°F (32°C) and will remain above 35°F (2°C) for the next 24 hours. Avoid staining in direct sunlight or on hot surfaces.USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN..

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to staining and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae.

PROTECT FROM FREEZING.

Paramount 41-8301 Series

Super Premium Stain + Sealant In One Solid

GENERAL SURFACE PREPARATION

Surface must be clean. Remove all dust, dirt, mildew, oil, loose wood fibers, and other contaminants. Remove loose, peeling stain by sanding, scraping or wire brushing. To ensure proper penetration, weathered, dirty, or mildewed surfaces should be cleaned with a wood cleaner prior to applying stain. After rinsing, ensure surface is free of standing water. Remove grade stamps or pencil marks by sanding.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted, NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

NEW WOOD - Clean and prepare all wood surfaces as specified above. Pressure treated wood must be properly seasoned, dry with a moisture content of 18% or less and free of salts and other water soluble materials. Water- repellent treated lumber requires one year minimum of weathering.

EXOTIC HARDWOOD - Ipe, mahogany, iron wood, tiger wood and teak woods exhibit a dense cell structure which may reduce the ability of a coating to penetrate the wood surface. Clean and prepare surface as specified above. Immediately prior to applying coating, wipe surface with acetone. Use on exotic hardwoods may affect coverage, dry time, and durability.

PRIME: THIS PRODUCT IS SELF-PRIMING OVER MOST SUBSTRATES. Some woods, such as cedar and redwood, contain high amounts of tannin, a colored wood extract. The first coat of stain may show some discoloration, but the tannins will be trapped in the first coat of stain. A second coat will result in a uniform appearance.

Paramount 41-8301 Series

Super Premium Stain + Sealant In One Solid

APPLICATION INFORMATION

Apply to a small area and allow stain to dry to ensure acceptable appearance and penetration. Intermix containers to ensure color uniformity. Stir thoroughly and often during use. Do not thin. Apply when no precipitation is expected for 12 hours, and when air and surface temperatures are 35°F (2°C) to below 90°F (32°C) and will remain above 35°F (2°C) for the next 24 hours. Avoid staining in direct sunlight or on hot surfaces. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply two thin coats with a high-quality brush, paint/stain pad, or with spray equipment. When applying by roller or spray, always back-brush for best results. Some colors, or drastic color changes, may require a third coat to achieve a uniform finish. To help avoid lap marks, apply to only a few boards at a time, and maintain a wet edge. Do not saturate or puddle on horizontal surfaces.

Airless Spray: Pressure 1500 to 2000 psi; tip 0.013" to 0.015". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Nylon/Polyester Brush **Roller (nap roller cover):** 3/8" - 1/2"

Thinning: Do not thin.

Permissible temperatures during application:
Material: 50 to 90°F 10 to 32°C
Ambient: 35 to 90°F 2 to 32°C

Substrate: 35 to 90°F 2 to 32°C

PRECAUTIONS

WARNING! HARMFUL IF INHALED. Do not breathe vapor or mist. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information. FIRST AID: If swallowed, rinse mouth with water (only if the person is conscious). Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. Contains isothiazolinones. May cause allergic reaction. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2024 PPG Industries, Inc. All Rights Reserved. The PPG Logo is a registered trademark of PPG Industries Ohio, Inc. Pittsburgh Paints & Stains is a trademark and Paramount is a registered trademark of PPG Architectural Finishes, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.

