

C1415

Interior and Exterior

Product Description

Top Gun 250Xi Advanced Fast Dry Sealant is a premium (proprietary) modified acrylic-based sealant that offers unmatched paintability and durability.

Top Gun 250Xi Sealant allows you to spray paint immediately or brush or roll in only 20 minutes. It forms a flexible, durable, airtight, water-resistant seal.

Top Gun 250Xi Sealant provides excellent adhesion to wood, drywall, plastic, metal, masonry, brick, glass, PVC, vinyl siding, fibreglass, marble, porcelain, and ceramic tile.

Top Gun 250Xi Sealant is ideal for a variety of applications, including door casings & jambs, baseboards, window frames, vents, siding joints, eaves, mouldings, air conditioner openings, thresholds, counters, and sinks. Cured caulk is mildew resistant.

Recommended uses

Around baseboards, crown mouldings and other mouldings.

Around siding, door and window frames.

Around sinks, countertops, showers, bathtubs and similar application.

Surfaces

Multipurpose with an excellent adhesion on many construction materials.

Can be used on various substrates for a variety of applications.

Features & Benefits

Allows to spray paint immediately after its application.

Allows to brush paint after only 20 minutes.

Ready for use and easy to apply.

Dries rapidly and has only very little odour.

Provides a flexible durable seal.

Can be applied on vertical, horizontal or overhanging surfaces without subsiding or sagging.

Water-based product, which allows tool cleanup with water.

Contains fungicide: the cured sealant is mildew resistant.

Colour choice and appearance

WHITE: C1415

Homogeneous paste without lumps, easy to use.

Application tool

Caulking gun.

Certifications

Exceeds the minimum requirements of the specification ASTM C-834, Type OP, Grade 0°C.

Notes

Around showers or bathtubs, allow at least 36 hours before exposing to water (more time is required if the ventilation is limited).

Not intended for continuous underwater joint or below grade use.

Cannot be sanded.

Not for use in installing shower doors.

Do not use on floor joints where abrasion will occur.

Not for food contact surfaces.

Paint application before the recommended drying times can result in cracking of the paint.

Does not adhere to polyethylene, polypropylene, recycled plastic, Teflon or other comparable materials.

Do not use on bare ferrous metal or on frozen or damp surfaces.

Not for use on surfaces where silicone was previously applied.

Make sure the joint variation does not exceed the product's elasticity.

KEEP FROM FREEZING.



Surface Preparation

Surface to be caulked must be clean, solid and dry. Remove all dirt, dust, oil, mildew, loose paint, old caulk and other surface contamination. Clean with an appropriate cleaner. Rinse the surface thoroughly and let dry completely.

Bare metal and exterior porous surfaces should be painted. Only apply when sealant, surface and air temperatures are above 5°C (40°F) and rising. Do not apply on surfaces that exceed 38°C (100°F) or when rain is expected.

Application

Cut nozzle at a 45° angle. Cured bead should be between 3 mm (1/8") and 13 mm (1/2"). Use backer rod for gaps deeper than 13 mm (1/2"). Proper sealant dimensions for moving joints is 2:1 width to depth ratio.

Only apply when sealant, surface and air temperatures are inside application conditions range. Immediately upon application, bead may be smoothed with finishing tool. The tooling can insure a firm contact to surfaces. DO NOT MAKE A CONCAVE SHAPE.

Clean up excess caulk with damp cloth before it dries. Allow sealant to cure 36 hours before exposing to water (longer in cool or humid conditions).

For more information, consult your retailer.

Application Conditions

Temperature: +5 to 45°C (40 to 115°F) (ideal 20°C ± 5°C [68°F ± 9°F]).

Relative humidity: Ideal between 15 and 50%, maximum 85%.

Outdoor: Surface must be at a temperature at least 3°C (5°F) higher than dew point. Do not apply in direct sunlight. Application conditions must be maintained during product application and drying. Apply when no rain is expected within 8 hours. Low temperatures extend drying time.

Cleaning

Remove as much product quantity as possible and clean tools with soap and lukewarm water immediately after use.

Surface Maintenance

Maintenance varies according to usage and place. Proper maintenance starts with visual inspection. To maintain the protective characteristics, damaged or deteriorated sealant joints must be repaired as soon as possible.

Storage and Transportation

Although the product is stable for a limited number of freeze-thaw cycles, allowing the product to freeze is not recommended. Always store it in a dry place where the temperature is between 5°C (40°F) and 30°C (86°F). Under these conditions, the sealed tubes could be preserved for 24 months from date of purchase.

Disposal

Consult your municipality about proper disposal procedure of residue in accordance with the laws and respect the environment.

Technical Specifications (21°C (70°F))

Composition

- Diluent: Water
- Binder: Modified acrylic polymer emulsion (latex)

Volatile Organic Compounds (VOCs)*

<1.5% by weight

Viscosity*

Ready to use

Density*

1.7 ± 0.1 kg/L

Solids by Volume*

72%

Solids by Weight*

83%

Flammability

Non-flammable under normal use conditions

Flash Point*

Not applicable

Freeze-thaw stability

Passes 5 cycles

(1 cycle = 16 hours at -18°C & 8 hours at 24°C)

Drying Time*

- Tack-free time: 20 to 60 minutes
- Maximum tooling time: 10 to 15 minutes
- Before painting: 20 minutes
- Prior to withstanding light rain: 8 hours
- Prior to withstanding heavy rain: 24 hours

When relative humidity is higher than 50%, double the required drying time.

Service range

Minimum: -30°C (-22°F)

Maximum: 80°C (180°F)

Coverage

16.5 metres for a 5 mm bead

Yield per tube

5 mm X 5 mm:	15 to 19 linear m
6 mm X 6 mm:	11 to 13 linear m
5 mm X 10 mm:	8 to 10 linear m
6 mm X 12 mm:	5 to 7 linear m
3/16 in X 3/16 in.:	55 to 69 linear ft.
1/4 in X 1/4 in.:	31 to 39 linear ft.
3/16 in X 3/8 in.:	28 to 34 linear ft.
1/4 in X 1/2 in.:	15 to 19 linear ft.

*Technical data source: C1415

Safety Measures

MAY BE HARMFUL IF SWALLOWED. MAY CAUSE EYE AND SKIN IRRITATION. Avoid breathing vapours. Avoid contact with skin and eyes.

Wear protective gloves/clothing and eye/face protection. Keep out of reach of children. **Prior to use, read and follow product-specific SDS and label information. FIRST AID TREATMENT:** If swallowed, call a Poison Control Centre or doctor immediately. If in eyes or on skin, rinse well with water. If breathed in, move person to fresh air. Contains: Limestone; titanium dioxide; ethanediol; crystalline silica, respirable powder (<10 microns). Sanding and grinding dusts may be harmful if inhaled. This product contains crystalline silica which can cause lung cancer or silicosis. The risk of cancer depends on the duration and level of exposure to dust from sanding surfaces. Contains isothiazolinones. May cause allergic reaction. Keep container tightly closed and sealed until ready for use. For workplace use, an SDS is available from your retailer or by calling 1-800-463-7426 (Canada). EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.), (514) 645-1320 (Canada).

Satisfaction Guaranteed

The manufacturer warrants your complete satisfaction with the performance of this product for as long as you own or reside in your home when our product has been applied and maintained according to label directions. This satisfaction guarantee is non-transferable. The manufacturer does not warrant against problems with the product which are caused by factors beyond its control, such as structural defects, damage to the coating film by others, poor condition of the substrate, improper application, etc. If not satisfied as warranted, return the unused portion along with sales receipt to place of purchase. You will receive as your exclusive remedy either a refund of the price paid for the product or replacement with product of equal value. This warranty specifically excludes labour or costs of labour for the removal or application of any coating and indirect, special, consequential and incidental damages.