

**Interior/Exterior****PRODUCT DESCRIPTION**

Top Gun 140 acrylic sealant is a painter's professional grade acrylic latex caulk for interior and exterior use. Effective on wood, drywall, plastic, metal, masonry, glass, PVC, vinyl siding, and fiberglass.

RECOMMENDED USES

Door Casings and Jambs
Baseboards
Window Frames
Vents
Siding Joints
Pipe Openings
Eaves
Moldings
Air Conditioner Openings

FEATURES & BENEFITS

40 Year Limited Warranty
Great Adhesion
Easy Water Clean-up
Paintable after 30 minutes with latex paint and after 2 hours with oil based paint under normal drying conditions.
Interior/Exterior
Cured Caulk is Mold & Mildew Resistant
Meets ASTM C834

PRODUCT INFORMATION

SAP	SKU	Product Description	Size
417944	1413/EA	Top Gun 140 Acrylic Sealant White	10.1 OZ

LIMITATIONS OF USE

Do not apply when rain is expected on exterior applications within 8 hours.
Not recommended for applications below grade or where water may stand, or for traffic bearing surfaces.
For deep cracks, always use closed-cell backer-rod.
Use backer rod in cracks larger than 1/2" x 1/2."
Not for food contact surfaces.
NOTE: Painting the sealant before the recommended dry time may result in cracking.
PROTECT FROM FREEZING.



PRODUCT TECHNICAL DATA

Specifications		White
NA		
Typical Uncured Physical Properties	Test Method	Value
Base		Acrylic Latex
Consistency		Smooth & Creamy
Odor		Slight Acrylic
Density		13.70 ±0.1 lbs./gal
Application Temperature Range		40 to 115°F
Paint Ready Time		2 to 4 hours
Full Cure Time (based on 3/16 inch bead size)		24 -72 hours
Water Ready time		24 hours
% Solids by Weight	ASTM C1250	69
Slump (sag)	ASTM C693	Passed
Tack Free Time	ASTM C697	< 20 min
Freeze-Thaw Stability	ASTM C731	Passed / 5 Cycles
VOC (excluding water & exempt compounds)		< 50 g/l
CARB Non-Chem Curing (n-a VOC)		< 1.0% by weight
Typical Cured Physical Properties	Test Method	Value
Service Temperature		-22 to 180°F
Paintable		Latex & Oil Based
Coverage (3/16" bead)		55 linear ft
Clean-up		Water and Soap
Joint Movement Capability	ASTM C719	No Data Available
Tensile Elongation	ASTM D412	No Data Available
Artificial Weathering	ASTM C793	No Data Available
Cracking & Chalking	ASTM C792	None - Passed
Peel Adhesion (Dry/Wet)	ASTM C794	No Data Available
Stain / Color Change	ASTM C510	No Data Available
Hardness (Shore A)	ASTM C661	>35
Shelf Life (from manufacture date)		24 Months

GENERAL SURFACE PREPARATION

Where applicable, remove old sealant or caulking. Thoroughly dry the joints or surfaces, where the *Top Gun 140* will be applied. Remove all dirt, dust, oil, mildew, loose paint or other contaminants. Bare surfaces should be primed before caulking.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

DIRECTIONS FOR USE

USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Permissible temperatures during application:

Temperature Range: Air and surface
40°F to 100°F (4°C to 38°C)
Optimum product temperature
60°F to 80°F (16°C to 27°C)

Dew Point: Surface must be at least 5°F (3°C) above the dew point.

Application Information: Install backer-rod uniformly into deep cracks to control sealant depth. For cracks up to 1/2 inch wide, set the backer-rod from 1/4 to 1/2 inch deep. Bond breaker tape may be used for joints not deep enough for backer-rod.

Cut nozzle at a 45° angle.

Fill joints and cracks by holding the nozzle in the opening and filling completely from the bottom up. Cured bead should be between 1/8" and 1/2". Smooth immediately with a damp sponge or towel, or other tool as required.

Remove excess material with a wet cloth.

Dry excess sealant may be cut away.

Disposal: Contact your local environmental regulatory agency for guidance on disposal of unused product.

PRECAUTIONS

WARNING! HARMFUL IF SWALLOWED. Sanding and grinding dusts may be harmful if inhaled. This product contains crystalline silica which can cause lung cancer or silicosis. The risk of cancer depends on the duration and level of exposure to dust from sanding surfaces. Do not breathe vapor. Do not swallow. Do not get on skin or clothing. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust or particulates, arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information.**
FIRST AID: If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. If experiencing respiratory symptoms call a POISON CENTER or doctor/physician. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

SHIPPING

Freight Classification: PAINT OR PAINT RELATED MATERIAL

Packaging: 12-10.1 Ounce Tubes per carton

© 2020 PPG Industries, Inc. All Rights Reserved. The PPG Logo is a registered trademark of PPG Industries Ohio, Inc. Top Gun is a registered trademark of PPG Architectural Finishes, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.ppgpaints.com
www.ppgpittsburghpaints.com

Technical Services
1-800-441-9695

Architect/Specifier
1-888-PPG-IDEA

PPG Architectural Coatings Canada Inc.
1550 rue Ampère, Suite 500
Boucherville (Quebec) J4B 7L4

1413 2/2020