



Architectural Coatings

PPG Mopako Flat Latex Interior Wall Paint

**GENERAL DESCRIPTION**

Mopako is a high quality latex wall paint designed to produce an even, flat finish for interior walls and ceilings. Mopako is recommended for use in residences, offices, apartments, hotels, schools, hospitals and manufacturing facilities. Ideal for use on interior walls and ceilings where a flat finish with excellent touch-up properties is required.

**RECOMMENDED SUBSTRATES**

Concrete/Masonry	Gypsum Wallboard-Drywall
Concrete Block (CMU)	Plaster
Ferrous Metal	Wood

**CONFORMANCE STANDARDS**

VOC compliant in all regulated areas

**TINTING AND BASE INFORMATION**

66-110	White & Pastel Base
66-114	HVT Santa Fe
66-115	HVT Caravan
66-116	New Spiced Vinegar
66-119	HVT Desert Castle
66-120	Midtone Base*
66-128	HVT Toasted Almond
66-145	HVT White Chip
66-146	HVT Summertime
66-190	HVT Mocha
66-191	HVT Decorator White

\*Must be tinted before use.

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

**PACKAGING**

- 1-Gallon (3.78 L)
- 5-Gallon (18.9 L)

**FEATURES / BENEFITS****Features**

- Uniform, Flat Finish
- Excellent Touch-Up
- Easy Clean Up
- Good Hiding
- Low VOC, <50 g/L

**PRODUCT DATA**

<b>PRODUCT TYPE:</b>	Vinyl Acrylic Latex
<b>SHEEN:</b>	Flat: 1.8-2.6 @60°; 1.6-2.6 @85°
<b>VOLUME SOLIDS*:</b>	32% +/- 2%
<b>WEIGHT SOLIDS*:</b>	50% +/- 2%
<b>WEIGHT/GALLON*:</b>	11.3 lbs. (5.1 kg) +/- 0.2 lbs. (91 g)
<b>VOC:</b>	<50 g/L (0.4 lbs./gal.)

\*Product data calculated on 66-110.

**COVERAGE:** Approximately 400 sq. ft. (37 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0 mils
Wet Microns:	102
Dry Film Thickness:	1.3 mils
Dry Microns:	33

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing. Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

<b>DRYING TIME:</b>	Dry time @ 77°F (25°C); 50% relative humidity.
To Touch:	30-60 minutes
To Recoat:	2-4 hours
To Full Cure:	30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

**CLEANUP:** Clean tools with warm, soapy water.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

**FLASH POINT:** Over 200°F (93°C)

## GENERAL SURFACE PREPARATION

Surface must be dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough and patched surfaces. Plaster, concrete and masonry surfaces must be completely dry, free of efflorescence and allowed to cure for 30 days prior to painting. This product is self-priming on new drywall. Prime all bare wood, plaster, masonry, and porous surfaces with an appropriate PPG primer.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**CONCRETE/MASONRY:** New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended.

**CONCRETE BLOCK (CMU):** Mortar should cure for at least 30 days and preferably 90 days prior to painting. Fill block with an appropriate block filler.

**FERROUS METAL:** The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

**GYP SUM WALLBOARD-DRYWALL:** Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust prior to painting the substrate.

**PLASTER:** Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended.

**WOOD:** Countersink all nails, putty flush with surface. Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be sealed before painting.

## RECOMMENDED PRIMERS

Concrete/Masonry	4-603XI, 17-921XI
Concrete Block (CMU)	6-7, 6-15XI
Ferrous Metal	90-712, 90-912
Gypsum Wallboard-Drywall	Self-Priming, 6-2, 6-4, 9-900, 12-900XI
Plaster	4-603XI, 17-921XI
Wood	6-2, 9-900, 12-900XI, 17-921XI

## LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C).

Not recommended for use on floors.

PROTECT FROM FREEZING.

## APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

**Application Equipment:** Apply with a high quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

**Airless Spray:** Pressure 1500 - 2000 psi, tip 0.015" - 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

**Brush:** Polyester/Nylon Brush

**Roller:** 3/8" - 3/4" nap roller cover

**Thinning:** No thinning is usually required.

**Permissible temperatures during application:**

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 90°F	10 to 32°C
Substrate:	50 to 90°F	10 to 32°C

## PRECAUTIONS

**WARNING! HARMFUL IF INHALED. HARMFUL IF SWALLOWED.** Sanding and grinding dusts may be harmful if inhaled. This product contains crystalline silica which can cause lung cancer or silicosis. The risk of cancer depends on the duration and level of exposure to dust from sanding surfaces or mist from spray applications. Do not breathe vapor or mist. Do not swallow. Do not get on skin or clothing. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information.** **FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. Contains isothiazolinones. May cause allergic reaction. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2019 PPG Industries, Inc. All Rights Reserved. The PPG logo is a registered trademark of PPG Industries Ohio, Inc. Mopako is a trademark of PPG Architectural Finishes, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.  
Architectural Coatings  
One PPG Place  
Pittsburgh, PA 15272  
www.ppgpaints.com

Technical Services  
1-800-441-9695  
1-888-807-5123 fax

Architect/Specifier  
1-888-PPG-IDEA

PPG Architectural Coatings Canada Inc.  
1550 rue Ampère, Suite 500  
Boucherville (Quebec) J4B 7L4

66-110 - 12/2019