



PPG Architectural Coatings

TOP GUN® 250 Modified Acrylic Sealant

**GENERAL DESCRIPTION**

TOP GUN® 250 Fast Dry is a premium (proprietary) modified acrylic based sealant that offers unmatched paintability and durability. TOP GUN 250 allows you to spray paint immediately or brush in only 30 minutes. It forms a flexible, durable, airtight, water-resistant seal. TOP GUN 250 provides excellent adhesion to wood, drywall, plastic, metal, masonry, brick, glass, PVC, vinyl siding, fiberglass, marble, porcelain and ceramic tile. TOP GUN 250 is ideal for a variety of applications, including door casings & jambs, baseboards, window frames, vents, siding joints, eaves, moldings, air conditioner openings, thresholds, counters and sinks.

**RECOMMENDED USES**

- Windows and Doors
- Siding and Trim
- Sinks and Counters

**FEATURES / BENEFITS**

- 55 year warranty
- Spray Paint Immediately
- Brush in 30 Minutes
- Excellent Adhesion & Durability
- Exceptional Paintability
- Interior/Exterior
- Exceeds ASTM C-834

**LIMITATIONS OF USE**

Not designed for use in engineered "expansion joints." Do not apply when rain is expected on exterior applications within 8 hours. Not recommended for applications below grade or where water may stand, or for traffic bearing surfaces. For deep cracks, always use closed-cell backer-rod. Do not use in cracks larger than 1/2" x 1/2." Not for food contact surfaces. NOTE: Painting the sealant before the recommended dry time may result in cracking. PROTECT FROM FREEZING.

**PRODUCTS**

1415 White

**PRODUCT DATA**

Data below is based on White 1415.

<b>Product Type:</b>	Proprietary Modified Acrylic (Siliconized)
<b>Volume Per Tube:</b>	10.1 oz.
<b>VOC (actual):</b>	1%
<b>Weight Per Gallon:</b>	14.1 lbs.
<b>Solids by Weight:</b>	83% minimum
<b>Freeze/Thaw:</b>	5 Cycles
<b>Adhesion:</b>	Excellent

Dry Time to Paint@ 70°F / 50% relative humidity):

Latex Paint:	30 minutes
Oil Base Paint:	2 to 4 hours

(Expect longer dry times at lower temperatures and higher relative humidity.)

<b>Estimated Coverage:</b>	1/8" x 1/4" bead - 60 linear feet per tube
	1/4" x 1/4" bead - 30 linear feet per tube.

**Clean Up:** Clean spills immediately with clean water and a soft cloth. Clean tools immediately after use with clean water.

**Flash Point:** >200°F (>93°C)

**ASTM Specification:** Exceeds ASTM-C-834, Type OP, Grade - 18°C

Note: This product is not formulated with lead or mercury containing materials.

PPG Architectural Coatings

TOP GUN® 250 Modified Acrylic Sealant

## GENERAL SURFACE PREPARATION

Where applicable, remove old sealant or caulking. Thoroughly dry the joints or surfaces, where the TOP GUN 250 will be applied. Remove all dirt, dust, oil, mildew, loose paint or other contaminants. Before painting, it is highly recommended to test an area first and do not over paint joint (5 mils wet). Certain primers may cause paint film cracking if primer is applied over caulking. Bare surfaces should be primed before caulking.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

## DIRECTIONS FOR USE

Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

### Permissible temperatures during application:

Temperature Range:      Air and surface  
                                    40°F to 110°F (43.3°C)  
                                    Optimum product temperature  
                                    60°F to 80°F (16°C to 27°C)

Dew Point:                      Surface must be at least 5°F (3°C) above the dew point.

**Application Information:** Install backer-rod uniformly into deep cracks to control sealant depth. For cracks up to 1/2 inch wide, set the backer-rod from 1/4 to 1/2 inch deep. Bond breaker tape may be used for joints not deep enough for backer-rod.

Cut nozzle at a 45° angle.

Fill joints and cracks by holding the nozzle in the opening and filling completely from the bottom up. Cured bead should be between 1/8" and 1/2". Smooth immediately with a damp sponge or towel, or other tool as required.

Remove excess material with a wet cloth.

Dry excess sealant may be cut away.

## SHIPPING

**Freight Classification:** PAINT OR PAINT RELATED MATERIAL

**Packaging:** 12-10.1 Ounce Tubes per carton

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG/Porter Paints  
400 South 13th Street  
Louisville, KY 40203  
[www.porterpaints.com](http://www.porterpaints.com)

Technical Services  
1-800-332-6270

Architect/Specifier:  
1-888-PPG-IDEA

PPG Industries, Inc.  
One PPG Place  
Pittsburgh, PA 15272  
[www.ppg.com](http://www.ppg.com)



No.1415 5/2009  
(Supersedes 1/2008)