



PPG Architectural Coatings

TOP GUN® 300 Elastomeric Siliconized Acrylic Sealant

GENERAL DESCRIPTION

TOP GUN® 300 Elastomeric Acrylic Sealant is a premium grade sealant that forms a flexible, durable, airtight, water-resistant seal that offers exceptional protection from environmental conditions and features high elongation and superior recovery. TOP GUN 300 is designed to be used on some of the most difficult applications, including crown molding, windows/doors, baseboards, pipes/vents, brick/masonry, siding/trim, drywall, countertops, glass, tuck pointing.

RECOMMENDED USES

- Windows and Doors
- Siding and Trim
- Sinks and Counters
- Hardboard and Flashing
- Stucco and EIFS
- Penetrations
- Crown Molding

FEATURES / BENEFITS

- 60 year warranty
- Exceptional Adhesion
- Excellent Flexibility
- Paintable
- Interior/Exterior
- TT-S 00230 Performance

LIMITATIONS OF USE

Not designed for use in engineered "expansion joints." Do not apply when rain is expected on exterior applications within 8 hours. Not recommended for applications below grade or where water may stand, or for traffic bearing surfaces. For deep cracks, always use closed-cell backer-rod. Do not use in cracks larger than 1/2" x 1/2." Not for food contact surfaces. NOTE: Painting the sealant before the recommended dry time may result in cracking. PROTECT FROM FREEZING.

PRODUCTS

1416 White

PRODUCT DATA

Data below is based on White 1416.

- Product Type:** Siliconized acrylic
- VOC (actual)** 1%
- Volume Per Tube:** 10.1 oz.
- Weight Per Gallon:** 13.1 lbs.
- Solids by Weight:** 82% minimum
- Elongation:** Excellent
- Freeze/Thaw:** 5 Cycles
- Adhesion:** Excellent

Dry Time to Paint@ 70°F / 50% relative humidity):

- Latex Paint: 4 to 6 hours
- Oil Base Paint: 4 to 6 hours

(Expect longer dry times at lower temperatures and higher relative humidity.)

- Estimated Coverage:** 1/8" x 1/4" bead - 60 linear feet per tube
1/4" x 1/4" bead - 30 linear feet per tube.

Clean Up: Clean spills immediately with clean water and a soft cloth. Clean tools immediately after use with clean water.

Flash Point: >200°F (>93°C)

ASTM Specification: Exceeds Federal Specs TT-00230C, Type S, Class B; ASTM C-920, Grade NS, Class 12.5 and ASTM C-834, Type OP, Grade - 18°C.

Note: This product is not formulated with lead or mercury containing materials.

PPG Architectural Coatings

TOP GUN® 300 Siliconized Acrylic Sealant

GENERAL SURFACE PREPARATION

Where applicable, remove old sealant or caulking. Thoroughly dry the joints or surfaces, where the TOP GUN 300 will be applied. Remove all dirt, dust, oil, mildew, loose paint or other contaminants. For maximum adhesion, dull glossy surfaces. Bare surface should be primed before caulking.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

DIRECTIONS FOR USE

Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

Permissible temperatures during application:

Temperature Range: Air and surface
 40°F to 110°F (43.3°C)
 Optimum product temperature
 60°F to 80°F (16°C to 27°C)

Dew Point: Surface must be at least 5°F (3°C) above the dew point.

Application Information: Install backer-rod uniformly into deep cracks to control sealant depth. For cracks up to 1/2 inch wide, set the backer-rod from 1/4 to 1/2 inch deep. Bond breaker tape may be used for joints not deep enough for backer-rod. Use a non-gassing foam backer rod or bond breaker tape to avoid 3 point adhesion.

Cut nozzle at a 45° angle.

Fill joints and cracks by holding the nozzle in the opening and filling completely from the bottom up. Cured bead should be between 1/8" and 1/2". Smooth immediately with a damp sponge or towel, or other tool as required.

Remove excess material with a wet cloth.

Dry excess sealant may be cut away.

SHIPPING

Freight Classification: PAINT OR PAINT RELATED MATERIAL

Packaging: 12-10.1 Ounce Tubes per carton

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG/Porter Paints
400 South 13th Street
Louisville, KY 40203
www.porterpaints.com

Technical Services
1-800-332-6270

Architect/Specifier:
1-888-PPG-IDEA

PPG Industries, Inc.
One PPG Place
Pittsburgh, PA 15272
www.ppg.com



No.1416 5/2009
(Supersedes 1/2008)