

PPG Architectural Coatings

VINYL FLAT™ Interior Latex Wall Paint

GENERAL DESCRIPTION

VINYL FLAT Interior Latex Wall Paint No. PP979 Series is a superior professional quality flat interior latex wall paint used for new and previously painted commercial, institutional and residential walls and ceilings where exceptional durability in a flat wall paint is required. This product outperforms most premium and super-premium residential flat paints in stain resistance and scrubability. It is perfect for high traffic and rough duty areas where low sheen is required. Also excellent for homeowner application.

RECOMMENDED USES

- Drywall
- Plaster
- · Primed metal
- Masonry
- Wallboard

FEATURES / BENEFITS

Saves time and money Good hiding Excellent uniformity Prevents flat and glossy spots

 Excellent touch-up Extends time to repaint

· Non-yellowing Colors stay true longer · Easy soap & water clean-up No Solvent disposal issues

RECOMMENDED SYSTEMS

VINYL FLAT Interior Latex Wall Paint No. PP979 series can be applied to a wide variety of primed substrates. Finish the following primed surfaces with one or two coats of VINYL FLAT Interior Latex Wall Paint No. PP979 series:

SUBSTRATE TYPICAL PRIMERS

Aluminum: 17-921

Drywall*: PP335, PP867, PP1129

Masonry

Brick: PP335, PP1129 PP335 Concrete:

Concrete Block (CMU): 6-7, 6-15 PP335, PP1129

Plaster:

90-712 Ferrous Metal:

Galvanized Steel: 17-921, 90-712 Wood: PP335, PP1129

*NOTE: Although flat finish paint is often used as a primer for new drywall, drywall primers are better designed to seal the surface providing better appearance with a two coat system.

TINTING AND BASE INFORMATION

Refer to the appropriate color formula book, automatic tinting equipment and/or computer color matching system for color formulas and tinting instructions.

PP975 Pastel Base PP979 Light Base* PP978 Deep Base* PP984 Ultra Deep Base*

*Must be tinted before use.

Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

PRODUCT DATA

Product Type: Vinyl acrylic

VOC based on Light Base. See labels for other bases.

VOC (theoretical):

As supplied (untinted): 0.8 lb/gal (97 g/l)

Sheen, 85°: Flat (Typical range: 1 - 5)

Reflectance: 96 ± 1%

Percent Solids:

Weight: 48 ± 2% Volume: 31 ± 2% Weight/Gallon: 11.4 lb

Viscosity (Initial): 90 - 95 Krebs Units

Thinner:

Brush/Roller: If necessary, thin sparingly with clean

water up to ½ pint per gallon.

Thin with clean water up to ½ pint per Spray:

gallon.

Clean-up: Warm, soapy water.

Recommended Film Thickness:

Wet: 3.4 mils Drv: 1.1 mils

Spread Rate (Theoretical):

Smooth Surfaces: Up to 470 sq. ft./gal. 250-300 sq. ft./gal. **Rough Surfaces:**

Coverage does not include variation due to application, surface porosity, and/or mixing.

Dry time (70°F @ 50% R.H.):

To Touch: 1 hour To Recoat: 4 hours 15-30 days Full Service:

(Drying times listed may vary depending on temperature,

humidity, color, and air movement.)

Flash Point: >200°F (>93°C) Flame Spread Rating: Class A (0-25)

(See Porter Technical Bulletin No. 9: Flame Spread Rating.)

Federal Specification Crossover: TT-P-29J

(See Porter Technical Bulletin No. 6: Federal Specification Performance Crossover.)

LIMITATIONS OF USE

Do not apply when air or surface temperature is below 50°F or above 110°F. Surface temperature must be at least 5°F above dew point. For optimum application properties, bring material to 65-85°F (18-29°C) temperature range prior to mixing or application. Use for service below 150°F. Do not use on floors. Protect from freezing.

VINYL FLAT™

PPG Architectural Coatings

VINYL FLAT™ Interior Latex Wall Paint

GENERAL SURFACE PREPARATION

Paint only clean, dry, deglossed and profiled surfaces. Remove dirt, oils, grease, wax, crayon and ink marks (or seal with SEAL GRIP® Premium Quick Dry Primer/Sealer No. 17-964 or shellac), sanding dust, paint remover, etc. with PREP125 DURAPREP® WB Cleaner & Degreaser, Dirtex and water, PPG Paint Thinner No. 5132 or other appropriate cleaners, or by vacuuming as necessary. Remove loose paint by hand scraping or power tool cleaning and sand smooth. Fill cracks and gouges in drywall and plaster with ready mix spackling paste. Fill holes and gouges in wood and other substrates with wood patch or filler, etc. as appropriate. Sand smooth as necessary before painting.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation

Let new plaster or masonry cure 28 days before painting. Fill cracks and holes in masonry with appropriate filler. Test plaster for water absorption prior to painting (paint will not adhere if water does not wet out the surface and absorb into the plaster). If necessary, sand or acid etch the surface. Retest for surface wetting before painting.

DIRECTIONS FOR USE

Stir thoroughly before using and occasionally during use. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

Permissible temperatures during application:

50°F to 110°F (air, surface, paint) Temperature Range:

(Optimum paint temperature 65-85°F)

Dew Point: Surface temperature must be at least

5°F above the dew point.

Relative Humidity: Maximum 85%

New Work: Apply a uniform prime coat per primer data sheet instructions (SEE RECOMMENDED SYSTEMS) at the millage specified for the application. NOTE: Specified drywall sealers are specially designed to seal the surface better than finish paints, and to help reduce the appearance of tape joints and other surface imperfections. Finish with one or more coats of VINYL FLAT Interior Latex Wall Paint No.PP979 series.

Repaint: Spot prime bare areas as required with an appropriate primer (SEE RECOMMENDED SYSTEMS), then apply one or more coats of VINYL FLAT Interior Latex Wall Paint No. PP979 series.

Washing Instructions: Protect the finish from abuse and contamination until well cured, at least 4-6 weeks. Try to avoid washing the finish for 30 days. For large areas, wash with a soft sponge and a solution of PREP125 DURAPREP® WB Cleaner & Degreaser, Dirtex or TSP. For marks, pencil, etc., clean with a damp sponge and powdered cleanser. (See Porter Technical Bulletin #5: "How to Wash Flat Wall Paint.")

APPLICATION INFORMATION

Application Equipment: Apply with a high quality brush, roller, or by spray equipment.

Airless Spray: Minimum 1 gallon per minute pump; .015"-.018" tip; 1800-2400 psi; 1/4" high pressure material hose.

Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brushes: Use nylon or polyester brushes.

Rollers: Use 3/8" to 3/4" synthetic roller covers.

Thinning: Thin sparingly with clean water as necessary for proper application. Do not exceed ½ pint per gallon.

Clean-up: Clean tools and spray equipment with warm, soapy water immediately after use.

SHIPPING

Freight Classification: PAINT OR PAINT RELATED MATERIAL Packaging: 6 Quarts per carton; 4 Gallons per carton; 5-Gallon

Shipping Weights: 3.1 lb/qt (19.3 lb/carton); 12.2 lb/gal (49.8

lb/carton); 59.9 lb/5-gal

PPGAF believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-

