



Architectural Coatings

HIGH ENDURANCE® PLUS

9401GP Series

Glidden High Endurance Plus Exterior Paint + Primer Semi-Gloss

GENERAL DESCRIPTION

Glidden High Endurance Plus Exterior is a 100% acrylic paint and primer* in one that provides excellent adhesion and hide, great dirt resistance, and resists fading, cracking and peeling. Semi-Gloss is an ideal finish for trim, rails and doors.

*Separate primer or multiple coats may be required. See COVERAGE for details.

RECOMMENDED SUBSTRATES

Aluminum Siding	Ferrous Metal	Stucco
Brick	Fiber Cement	Vinyl Siding*
Concrete	Masonry	Wood

*Vinyl siding and similar plastic composites should not be painted with a color darker than the original color. Painting vinyl siding or plastic composites with a darker color may cause them to warp. Color selection for use over vinyl siding is limited. For information, call 1-800-441-9695.

FEATURES / BENEFITS

100% Acrylic
Excellent Hide & Adhesion
Resists Fading, Cracking and Peeling
Great Dirt Resistance
Provides a Mildew Resistant Coating
Application Down to 35°F

CONFORMANCE STANDARDS

VOC compliant in all regulated areas

TINTING AND BASE INFORMATION

9401GP	Base 1 (White & Pastel Base)
9402GP	Base 2 (Midtone Base)*
9403GP	Base 3 (Neutral Base)*

*Must be tinted before use.

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

PRODUCT DATA

PRODUCT TYPE:	100% Acrylic
SHEEN*:	Semi-Gloss, 45-55 @ 60°
VOLUME SOLIDS*:	38% +/- 2%
WEIGHT SOLIDS*:	51% +/- 2%
WEIGHT/GALLON*:	10.5 lbs. (4.8 kg) +/- 0.2 lbs. (91 g)
VOC:	< 50 g/L (0.4 lbs./gal.)

*Product data calculated on product 9401GP.

COVERAGE: Up to 400 sq. ft. (37 sq. meters) per U.S. gallon (3.78 L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0 mils
Wet Microns:	102
Dry Film Thickness:	1.5 mils
Dry Microns:	38

Coverage figures do not include loss due to surface irregularities and porosity, or material loss due to application method or mixing. Some surfaces including uncoated substrates, repaired surfaces, porous surfaces, stained areas, and drastic color changes may require a primer or more than one coat to achieve a uniform finish and complete hide.

DRYING TIME:	Dry time @ 77°F (25°C); 50% relative humidity.
To Touch:	30-60 minutes
To Recoat:	2-4 hours
To Full Cure:	30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement. For example, product applied at 35°F (2°C) would require a minimum of 24 hours before recoat.

CLEANUP: Clean tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

PACKAGING

Quart (946 mL)
1-Gallon (3.78 L)

Not all products available in all sizes.

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, mildew, grease, oil, chalk, rust, and any other surface contaminants. Blistering and peeling issues are commonly caused by moisture behind the paint film. Problems leading to excessive moisture in the substrate must be repaired prior to painting. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Stucco, concrete, and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. When applied to an uncoated substrate or to bare wood, two coats are required with the first coat acting as the primer. For metal, tannin staining woods, fresh concrete or masonry (less than 30 days cure), or chalky surfaces, use of an appropriate specialty primer is recommended for best results.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

ALUMINUM SIDING: Aluminum siding may present potential adhesion problems. Prime prior to topcoating. A specialty primer may be required if the original painted surface has degraded to the substrate. Topcoat should be spot applied, allowed to cure overnight, then evaluated for adhesion. If adhesion is good, the application may proceed. Check adhesion by applying a piece of masking tape. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion.

BRICK, CONCRETE, MASONRY and STUCCO: New concrete and masonry should cure for at least 30 days and preferably 90 days prior to painting. The pH of the substrate must be less than 10. Painting glazed brick is not recommended due to potential adhesion problems.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed with a metal primer.

FIBER CEMENT: Fiber cement board may present potential adhesion, alkali burn, and efflorescence problems. New board should be aged for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 and the moisture content must be less than 12% prior to painting. All cracks and opens seams should be caulked to prevent water penetration. Pre-primed board from the manufacturer may not be uniformly or completely sealed.

VINYL SIDING: Vinyl siding may present potential adhesion problems. Topcoat should be spot applied, allowed to cure overnight, then evaluated for adhesion. If adhesion is good, the application may proceed. Check adhesion by applying a piece of masking tape. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion. Color selection for vinyl siding is limited. Do not paint vinyl siding with a color darker than the original to prevent potential warping due to heat absorption.

WOOD: Countersink all nails, putty flush with surface. Unpainted wood or wood in poor condition should be sanded smooth and wiped clean. Any knots or resinous areas must be primed before painting.

LIMITATIONS OF USE

FOR EXTERIOR USE ONLY. Apply only when air, surface, and product temperatures are between 35°F (2°C) and 90°F (32°C) and at least 5°F (3°C) above the dew point. Air and surface temperatures must remain between 35°F (2°C) and 90°F (32°C) for the next 48 hours. Avoid painting in direct sunlight or on hot surfaces. Do not apply late in the day when dew and condensation are likely to form or if rain or snow is expected. On large expanses of metal, temperatures must be 50°F (10°C) or higher.

Not recommended for use on steps or floors.

Vinyl siding and similar plastic composites should not be painted with a color darker than the original color. Painting vinyl siding or plastic composites with a darker color may cause them to warp. Color selection for use over vinyl siding is limited. For information, call 1-800-441-9695.

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to painting and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae.

PROTECT FROM FREEZING.

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply with a high quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

Airless Spray: Minimum pressure 2000 psi, tip 0.015" - 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Nylon/Polyester Brush

Roller: 3/8" - 3/4" nap roller cover

Thinning: Do not thin.

Permissible temperatures during application:

Material:	35 to 90°F	2 to 32°C
Ambient:	35 to 90°F	2 to 32°C
Substrate:	35 to 90°F	2 to 32°C

PRECAUTIONS

WARNING! HARMFUL IF INHALED. Do not breathe vapor or mist. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information. FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. Contains isothiazolinones. May cause allergic reaction. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© AkzoNobel, revisions © 2022 PPG Industries, Inc. All Rights Reserved. The PPG Logo is a registered trademark of PPG Industries Ohio, Inc. The Glidden Logo is a registered trademark of PPG Architectural Finishes, Inc. Endurance and High Endurance are registered trademarks of AkzoNobel.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Architectural Finishes, Inc.
One PPG Place
Pittsburgh, PA 15272
www.glidden.com

Technical Services
1-800-441-9695

Architect/Specifier
1-888-PPG-IDEA

PPG Architectural Coatings Canada Inc.
1550 rue Ampère, Suite 500
Boucherville (Quebec) J4B 7L4

9401GP - 12/2022