



Highlights

PPG SilverSan™ antimicrobial-protected powder coatings are specially formulated with silver* ionic technology. SilverSan powder coating slowly releases silver ions, which are known to inhibit the growth of bacteria on powder-coated surfaces.

In research and development since 2001 – and a proven product in the marketplace since 2007 – SilverSan powder coating with silver ionic technology is engineered for use on fitness equipment, metal furniture, home appliances, restroom accessories, air conditioning /air vents, building materials, and laboratory equipment.

*Silver is a registered pesticide with the U.S. Environmental Protection Agency (EPA), which states that pesticides are used to prevent, destroy, repel or mitigate any pest ranging from insects and animals and weeds to microorganisms such as fungi, bacteria and viruses.

Antimicrobial is limited to the treated surface to provide mold and mildew resistance on the paint film and to inhibit the growth of stain and order-causing bacteria that may affect the surface of the coating. The use of these products does not protect users of any such treated article or others against food-borne or disease-causing bacteria, viruses, germs or other disease-causing organisms.

Product Features

Available in a wide range of colors and glosses

Exterior durability

Good chemical resistance

Technical Properties

| Property | Test Method | Value |
|-------------------|-------------|--|
| Color | | RAL 5012 LIGHT BLUE ABP |
| Appearance | | Smooth |
| Gloss | ASTM D-523 | 80 Minimum @ 60° |
| Adhesion | ASTM D-3359 | 100% (5B Pass) |
| Hardness | ASTM D-3363 | 2H Pencil (Eagle) |
| Impact Resistance | ASTM D-2794 | 100 In.-lbs. Direct |
| Conical Mandrel | ASTM D-522 | 1/8" Mandrel - No Cracking |
| Salt Spray | ASTM B-117 | 1000 Hrs. Pass <1/8" Scribe Creep - No Blisters |
| Humidity | ASTM D-1735 | 1000 Hrs. Pass <1/16" Scribe Creep - No Blisters |

Film Properties were determined using 2.5 - 3.5 mils powder film over iron phosphated, chrome rinse pretreated, 22 gauge, unpolished cold rolled steel test panels.

Application Data

| | |
|---|--|
| Application Type: | Electrostatic Spray |
| Recommended Bake: | 10 Minutes at 400 °F Metal Temperature See Cure Curve PCT-001 |
| Specific Gravity: | 1.50 ± .05 |
| Theoretical Coverage: | 128 Sq. Ft. per pound at 1.0 mil |
| Shelf Life from Date of Manufacture (@40-60% RH): | 80 °F Maximum - 12 Months |

*PPG recommends that all material be used in FIFO order (first in - first out).
Materials that exceed the recommended shelf life should be tested prior to use.*

* Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. ("PPG"). Any statements or methods mentioned herein are general suggestions only and are not to be construed as representations or warranties as to safety, performance, or results. Since the suitability and performance of the product is highly dependent on the product user's processes, operations, and numerous other user-determined conditions, the user is solely responsible for, and assumes all responsibility, risk and liability arising from, the determination of whether the product is suitable for the user's purposes, including without limitation substrate, application process, pasteurization and/or processing, and end use. No testing, suggestions or data offered by PPG to the user shall relieve the user of this responsibility. PPG does not warrant freedom from patent infringement in the use of any formula or process set forth herein. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin. Contact your PPG representative for the most up to date information.

SILVERSAN is a trademark of PPG Industries Ohio, Inc. The PPG logo is a registered trademark of PPG Industries Ohio, Inc.

